



Features:


- Black conductive bags made from blow molded LDPE with carbon
- The black bag is light tight and effectively avoids accumulation of electric charge on the bag and its contents
- Protects contents from damage of electromagnetic wave and static
- This product can be heat sealed and offers medium level static protection
- Surface resistance is 10^4 - $10^6\Omega$

Additional Notes:

We recommend that all of our black conductive bags be used within 2 years from the date of manufacture. Store this product in its original packaging in a climate-controlled environment where temperature ranges from 21°C - 23°C and relative humidity is 45 - 50%.



Carbon Loaded Polyethylene



Construction:

Our black conductive bags are constructed from a conductive material made out of a 4 mil single layer of carbon loaded polyethylene, creating a Faraday Cage effect. Conforms to military specification MIL-PRF-81705D Type II.

Configuration(s):

Our bags are available in custom sizes or in several industry standard sizes. Bags are offered with a single seal or bottom fold, extruded from a PE tube.

BLACK CONDUCTIVE BAG
ANT006BCB

THIS BAG IS ROHS COMPLIANT

ATTENTION

OBSERVE PRECAUTIONS
FOR HANDLING ELECTROSTATIC
DISCHARGE SENSITIVE DEVICES



Standard Bag Artwork:

Our black conductive bags are produced with the following sample artwork as standard.

Important Notice: This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp is the registered trademark of the Group. © Premier Farnell plc 2011.

Black Conductive Bag_ANT006BCB



Test Conditions:

The following results were taken under the following environmental test conditions: Temperature: 22.1°C / Humidity: 47.8%

Technical Parameters:

| Item: | Test Standard: | Result: |
|-----------------------------------|----------------|--|
| Melt Index | GB3682 | 2.1 g/10min |
| Inner / Outer Surface Resistivity | GJB2605-1996 | $10^4 - 10^6 \Omega$ |
| Static Voltage Attenuation Period | IEC61340-5-1 | ≤ 2 secs |
| Water Absorption Rate | GB/96-04-01 | 0.5% |
| Density | GB1033 | 0.92 g/cm |
| Tensile Strength | GB/96-04-01 | MD: 33 MPa TD: 34.85 MPa |
| Breaking Elongation Rate | GB/96-04-01 | MD: 1180% TD: 689% |
| Friction Coefficient | GB/96-04-01 | Outer Surface: 0.08 Us Inner Surface: 0.08 Ud |
| Heat Seal Temperature | GB/96-04-01 | 250-375 F |
| Size | GB/96-04-01 | Thickness: $\pm 10\%$ Length: ± 3 mm Width: ± 2 mm |
| Appearance | GB/96-04-01 | Black Sheet (No powder or oil) |

Test Conclusion: (Date of Issue: 2009-04-25)

The black conductive PE bag is tested accordant with the relevant test standard and requirements.

| Test Item: | Test Method: | Measured Equipment(s): | MDL: |
|--|-----------------------------|------------------------|--------|
| Lead (Pb) | IEC 62321:2008 Ed.1 Sec.8 | ICP-OES | 2mg/kg |
| Cadmium (Cd) | IEC 62321:2008 Ed.1 Sec.8 | ICP-OES | 2mg/kg |
| Mercury (Hg) | IEC 62321:2008 Ed.1 Sec.7 | ICP-OES | 2mg/kg |
| Hexavalent Chromium (Cr(VI)) | IEC 62321:2008 Ed.1 Annex C | UV-Vis | 2mg/kg |
| Polybrominated Biphenyls (PBBs) | IEC 62321:2008 Ed.1 Annex A | GC-MS | 5mg/kg |
| Polybrominated Diphenyl Ethers (PBDEs) | IEC 62321:2008 Ed.1 Annex A | GC-MS | 5mg/kg |

| Product Code: | Description: | Size (inches): | Size (mm): | Additional Notes: |
|---------------|----------------------|----------------|------------|-----------------------------|
| 1687809 | Black Conductive Bag | 6 x 24 | 152 x 610 | Pack of 100 (Ref: 006-0016) |

Important Notice: This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp is the registered trademark of the Group. © Premier Farnell plc 2011.