

EVO-STIK SERIOUS STUFF

A SINGLE-PART, MS POLYMER ADHESIVE

Evo-Stik Serious Stuff is a high performance, single component, moisture curing, Modified Silane (MS) Polymer based. It will bond most surfaces even if both are impervious. The product will bond damp surfaces and may even be used underwater. It has very low odour, cures to form a hard elastic rubber, with almost no shrinkage and low hazard; it does not contain any water or solvent, making it ideal for bonding foam polystyrene sheets. When fully cured the product may be painted with most types of paints.

APPLICATIONS

- Bonds to most surfaces including wood, concrete, brick, plaster, glass, ceramics, metals, rigid pvc, grp, insulation boards and foam polystyrene.
- Bonds panels, signs, wallboards, skirtings etc. of the above surfaces.

LIMITATIONS

- Will not bond Polythene, polypropylene & Teflon.
- It should not be used on bitumen contaminated surfaces.

METHOD OF USE

PREPARATION

- Any loose or weak layers on the surface must be removed.
- Surfaces must be clean and preferably dry.
- Surfaces that are damp MUST be checked for weak or loose matter on the surface that the damp might hide.

APPLICATION

- Apply parallel beads of sealant to one of the surfaces, Then bring the two surfaces together, within 10 minutes.

- 5mm diameter. Beads are generally sufficient. For close fitting surfaces these may be reduced to 3mm.
- The degree of separation of the beads of Evo-Stik Serious Stuff will depend upon the rigidity and weight of the panel, board or sign being bonded. If beads are separated by more than 200mm a perimeter bead should be applied.
- For rigid sheets 100 -150mm separation between beads is generally sufficient for high loading, but may be increased if the load is low (such a wallboards and foam polystyrene) where 200 - 500mm is acceptable.
- For less rigid boards the separation may need to be quite small and it is important to choose the correct bead size.

CLEANING

1. Uncured product may be removed using cloths lightly moistened with white spirit, after carefully scraping off the bulk.
2. Cured product requires mechanical removal.

COVERAGE

44 metres of 3mm diameter bead. Per 290ml
14 metres of 5mm diameter bead. Per 290ml

Date: 04 June 2006

Information Sheet No.: ZE0445

SHELF LIFE: 18 months when stored in the original unopened containers.

STORAGE: Store, in dry conditions, between 5°C & 25°C.

COLOUR: Warm White.

PACKAGING: **Code:** _____
663572 290ml cartridges x12

HEALTH & SAFETY

Available separately in file named as the packaging code to the left.

TYPICAL CHARACTERISTICS

Constitution: Moisture curing MS Polymer system
Skin time: About 5-15 minutes at 25°C
Full cure: 17-24 hours
Colour: Warm White
Density (SG): 1.5
Shore A hardness 50-55
Tensile strength 1.5-1.8 MPA
Elongation at break 200-300%
Movement Will accommodate up to ± 12% of the mean joint width
Shrinkage Less than 3%
Temperature resistance: -40 to 100°C
Water: Excellent resistance.
Oil & Petrol: Good resistance.
Chemicals: Good resistance.
Abrasion: Good resistance.
Paint-ability Cured product may be overpainted with most types of paints. In some rare cases the surface may retain slight tack which, often, another coat of the paint will cure.
UN Class; # Not designated as hazardous

| Sales & Technical contacts at Bostik | Telephone | Facsimile | Email addresses |
|--------------------------------------|--------------|--------------|--------------------------------------------------------------------------------|
| Sales | 01785 272700 | 01785 241818 | customer.service@bostik.com |
| Technical advice | 01785 272764 | 01785 272867 | technical.service@bostik.com |
| Technical Data & COSHH (MSDS) sheets | 01785 272827 | 01785 212962 | gatehouse@bostik.com |

This Product Data Sheet covers just one of a large range of products supplied by Bostik Limited. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This Product Data Sheet supersedes all previous technical information on this product, and users of it are cautioned to ensure that it is the current issue. Destroy all previous Product Data Sheets, and if any doubt, contact Bostik Limited, quoting the code number in the top right hand corner on the front of this document. This leaflet is for general guidance only and may contain inappropriate information under particular conditions of use. The company cannot accept any responsibility for loss or damage that may result from the use of this information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.