



# Scotch-Weld™ Cyanoacrylate Adhesive RT300B

## Product Data Sheet

Updated :February 2010  
Supersedes: September 2008

### Product Description

Scotch-Weld RT300B is a medium viscosity, black, rubber-toughened Cyanoacrylate adhesive. RT300B displays excellent peel and impact strength and is well suited to applications involving vibration, thermal shock, temperature cycling and high humidity.

RT300B is specially formulated to provide a more flexible bond than standard cyanoacrylates. RT300B can be used up to 105°C and has intermittent temperature resistance up to 125°C. Scotch-Weld RT300B can be used to bond a wide variety of substrates including metals, plastics, rubbers, etc.

### Physical Properties

<b>Base</b>	Modified Ethyl
<b>Soluble In</b>	Acetone, MEK
<b>Viscosity (cps)</b>	Range 300-1000 Typical Value 600
<b>Specific Gravity</b>	1.1
<b>Colour</b>	Black

### Performance Characteristics

<b>Maximum Gap Fill</b> (best results are obtained with very thin bond lines)	0.20mm
<b>Fixture Time</b>	5-50secs
<b>Tensile Strength</b> (ISO 6922)	20 N/mm <sup>2</sup>
<b>Full Cure</b>	24hrs
<b>Speed of Cure</b>	The speed of cure of cyanoacrylates varies according to the substrate to be bonded. Acidic surfaces such as paper and leather will have longer cure times than most plastics and rubbers.
<b>Moisture Resistance</b>	Low resistance to high levels of moisture and humidity over time.
<b>Service Temperature Range</b>	-50 to +105°C

---

<b>Additional Product Information</b>	Scotch-Weld Activators AC11 and AC12 may be used in conjunction with Scotch-Weld cyanoacrylates where cure speed needs to be accelerated. Cure speeds of less than 2 seconds can be obtained with most Scotch-Weld cyanoacrylates. The use of an activator can reduce the final bond strength by up to 30%.
<b>Application Techniques</b>	Bond speed is very fast so ensure that parts are properly aligned before bonding. Scotch-Weld Activators may be required if there are gaps or porous surfaces. Some plastics may require application of Scotch-Weld AC77 Primer. Ensure parts are clean, dry and free from oil and grease. Product is normally hand applied from the bottle. Apply sparingly to one surface and press parts firmly together until handling strength is achieved. As a general rule, as little cyanoacrylate as possible should be used – over application will result in slow cure speed and lower bond strength.
<b>Storage Conditions</b>	Keep the adhesive in a cool, dry place away from direct sunlight. Under such conditions shelf life at room temperature will be 6 months.  Refrigeration to 0-5°C gives optimum storage stability.
<b>Shelf Life</b>	6 months from date of despatch by 3M when stored in the original carton at 0-5°C
<b>Precautionary Information</b>	Refer to product label and material Safety Data Sheet for health and safety information before using the product. For information please contact your local 3M Office. <a href="http://www.3M.com">www.3M.com</a>
<b>For Additional Information</b>	To request additional information or to arrange for sales assistance, call 0870 6080050 Address correspondence to: 3M United Kingdom PLC, 3M House, 28 Great Jackson Street, Manchester, M15 4PA
<b>Important Notice</b>	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

---

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.  
This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

---

3M and Scotch-Weld are trademarks of the 3M Company.

3M United Kingdom PLC  
3M House,  
28 Great Jackson Street,  
Manchester,  
M15 4PA

Product Information :  
Tel 0870 60 800 50  
Fax 0870 60 700 99

3M Ireland Limited  
The Iveagh Building  
The Park, Carrickmines  
Dublin 18,  
Ireland

Customer Service :  
Tel (01) 280 3555  
Fax (01) 280 3509