



Safety Data Sheet according to (EC) No 1907/2006

Page 1 of 5

sds no. : 267026
V003.3

TEROSON MS 930 BK known as TEROSTAT MS 930 SCHWARZ

Revision: 21.02.2012
printing date: 15.08.2013

SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1. Product identifier

TEROSON MS 930 BK known as TEROSTAT MS 930 SCHWARZ

1.2. Relevant identified uses of the substance or mixture and uses advised against

Intended use:

1-Component sealant

1.3. Details of the supplier of the safety data sheet

Henkel Limited
2 Bishop Square Business Park
AL109EY Herfordshire Hatfield

Great Britain

Phone: +44 1606 593933

Fax-no.: +44 1606 863762

ua-productsafety.uk@uk.henkel.com

1.4. Emergency telephone number

24 Hours Emergency Tel: +44 (0)1442 278497

SECTION 2: Hazards identification

2.1. Classification of the substance or mixture

Classification (CLP):

No data available.

Classification (DPD):

No classification required.

2.2. Label elements

Label elements (CLP):

No data available.

Label elements (DPD):

The product is not subject to classification according to the calculation methods of the "General Classification Guideline for Preparations of the EC" as issued in the last version.

2.3. Other hazards

None if used properly.

SECTION 3: Composition/information on ingredients

General chemical description:

1-Component moisture-curing adhesive

Base substances of preparation:

Silane-modified polyether

Declaration of the ingredients according to CLP (EC) No 1272/2008:

No data available.

Declaration of ingredients according to DPD (EC) No 1999/45:

Contains no dangerous substances exceeding the limits of the EU-Regulation

SECTION 4: First aid measures

4.1. Description of first aid measures

Inhalation:

Move to fresh air, consult doctor if complaint persists.

Skin contact:

Rinse with running water and soap. Apply replenishing cream. Change all contaminated clothing.

Eye contact:

Rinse immediately with plenty of running water (for 10 minutes). Seek medical attention if necessary.

Ingestion:

Rinse mouth, drink 1-2 glasses of water, do not induce vomiting, consult a doctor.

SECTION 5: Firefighting measures

5.1. Extinguishing media

Suitable extinguishing media:

All common extinguishing agents are suitable.

Extinguishing media which must not be used for safety reasons:

High pressure waterjet

5.2. Special hazards arising from the substance or mixture

In the event of a fire, carbon monoxide (CO) and carbon dioxide (CO₂) can be released.

5.3. Advice for firefighters

Wear protective equipment.

Wear self-contained breathing apparatus.

SECTION 6: Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures

Wear protective equipment.

6.2. Environmental precautions

Do not empty into drains / surface water / ground water.

6.3. Methods and material for containment and cleaning up

Remove mechanically.

Dispose of contaminated material as waste according to Chapter 13.

6.4. Reference to other sections

See advice in chapter 8

SECTION 7: Handling and storage**7.1. Precautions for safe handling**

Hygiene measures:

- Do not eat, drink or smoke while working.
- Wash hands before work breaks and after finishing work.

7.2. Conditions for safe storage, including any incompatibilities

- Ensure good ventilation/extraction.
- Store in a cool, frost-free place.
- Storage at 15 to 25°C is recommended.

7.3. Specific end use(s)

- 1-Component sealant

SECTION 8: Exposure controls/personal protection**8.1. Control parameters**

Valid for

Great Britain

Basis

UK EH40 WELs

Ingredient	ppm	mg/m3	Type	Category	Remarks
DIISONONYL PHTHALATE 28553-12-0		5	Time Weighted Average (TWA):		EH40 WEL

8.2. Exposure controls:

Engineering controls:

- Ensure good ventilation/extraction.

Respiratory protection:

- Ensure adequate ventilation.

Hand protection:

Chemical-resistant protective gloves (EN 374). Suitable materials for short-term contact or splashes (recommended: at least protection index 2, corresponding to > 30 minutes permeation time as per EN 374): Polychloroprene (CR; ≥ 1 mm thickness) or natural rubber (NR; ≥ 1 mm thickness) Suitable materials for longer, direct contact (recommended: protection index 6, corresponding to > 480 minutes permeation time as per EN 374): Polychloroprene (CR; ≥ 1 mm thickness) or natural rubber (NR; ≥ 1 mm thickness) This information is based on literature references and on information provided by glove manufacturers, or is derived by analogy with similar substances. Please note that in practice the working life of chemical-resistant protective gloves may be considerably shorter than the permeation time determined in accordance with EN 374 as a result of the many influencing factors (e.g. temperature). If signs of wear and tear are noticed then the gloves should be replaced.

Eye protection:

- Protective goggles

Skin protection:

- Wear protective equipment.

Advices to personal protection equipment:

- Use only personal protection that's CE-labelled according to the regulation no. 819 of 19 August 1994.

SECTION 9: Physical and chemical properties**9.1. Information on basic physical and chemical properties**

Appearance	solid material pasty black
Odor	characteristic
pH	No data available / Not applicable
Initial boiling point	No data available / Not applicable
Flash point	not applicable
Decomposition temperature	No data available / Not applicable
Vapour pressure	No data available / Not applicable
Density (20 °C (68 °F))	1,50 g/cm ³
Bulk density	No data available / Not applicable
Viscosity (; 20 °C (68 °F); Conc.: 100 % product)	120 - 210 pa.s
Viscosity (kinematic)	No data available / Not applicable
Explosive properties	No data available / Not applicable
Solubility (qualitative) (20 °C (68 °F); Solvent: Water)	Insoluble
Solidification temperature	No data available / Not applicable
Melting point	No data available / Not applicable
Flammability	No data available / Not applicable
Auto-ignition temperature	No data available / Not applicable
Explosive limits	No data available / Not applicable
Partition coefficient: n-octanol/water	No data available / Not applicable
Evaporation rate	No data available / Not applicable
Vapor density	No data available / Not applicable
Solid content (105 °C)	98 %
Oxidising properties	No data available / Not applicable

9.2. Other information

No data available / Not applicable

SECTION 10: Stability and reactivity**10.1. Reactivity**

None if used for intended purpose.

10.2. Chemical stability

Stable under recommended storage conditions.

10.3. Possibility of hazardous reactions

See section reactivity

10.4. Conditions to avoid

None if used for intended purpose.

10.5. Incompatible materials

None if used properly.

10.6. Hazardous decomposition products

No decomposition if used according to specifications.

SECTION 11: Toxicological information**11.1. Information on toxicological effects****General toxicological information:**

To the best of our knowledge no harmful effects are to be expected if the product is handled and used properly.

SECTION 12: Ecological information

General ecological information:

Do not empty into drains, soil or bodies of water.

SECTION 13: Disposal considerations

13.1. Waste treatment methods

Product disposal:

The valid EEC waste code numbers are not product-related but are largely source-related. These can be requested from the manufacturer.

In consultation with the responsible local authority, must be subjected to special treatment.

SECTION 14: Transport information

General information:

Not hazardous according to RID, ADR, ADNR, IMDG, IATA-DGR.

SECTION 15: Regulatory information

15.1. Safety, health and environmental regulations/legislation specific for the substance or mixture

VOC content 0 %
(VOCV 814.018 VOC regulation
CH)

VOC Paints and Varnishes (EU):

Product (sub)category:

This product is not a subject of the Directive 2004/42/EC

SECTION 16: Other information

Further information:

This information is based on our current level of knowledge and relates to the product in the state in which it is delivered. It is intended to describe our products from the point of view of safety requirements and is not intended to guarantee any particular properties.