

FLEXANE 60 LIQUID

PRODUCT INFORMATION

	<u>Stock No.</u> 15200 15210	<u>Package Size</u> 500g 5Kg
Description	A tough pourable rubber compound for part encapsulation, rugged flexible moulds and patterns, holding fixtures and forming die pads. It can also used to form equipment linings that are abrasion resistant and noise reducing.	
Recommended Applications	<ul style="list-style-type: none"> • Pads for press brake forming • Lines process equipment to dampen noise • Protects equipment surfaces from wear and corrosion • Pouring concrete expansion joints • Casting flexible parts and moulds 	
Flexibility	High	

PRODUCT DATA

Typical Physical Properties	Colour	Black		
	Mix Ratio by Volume	1.6:1		
	Mix Ratio by Weight	1.67:1		
	% Solids by Volume	100		
	Pot life at 25°C (mins)	15		
	Specific Volume (cc/kg)	956		
	Cured Shrinkage (cm/cm)	0.0005		
	Specific Gravity	1.046		
	Temperature resistance	Wet 49°C Dry 82°C		
	Coverage	0.95m ² /Kg @ 1mm		
	Cured Hardness (Shore A)	65		
	Tensile Strength (MPa)	5.1		
	Tear Resistance (N/mm)	19		
	Elongation (%)	300		
	Dielectric Strength (kV/mm)	14		
	Thickness per Coat (mm)	As Required		
	Functional Cure Time (Hours)	16		
	Recoat Time (Hours)	12-24		
	Mixed Viscosity (cps)	5,000		
Chemical Resistance	7 days room temperature cure (30 days) - Testing carried out 30 days immersion at 21°C			
	Ammonia	Very Good	Methylene Chloride	Poor
	Cutting Oil	Fair	Sodium Hypochlorite 5% (Bleach)	Very Good
	Isopropyl Alcohol	Poor	Sodium Hydroxide 10%	Very good
	Gasoline (Unleaded)	Poor	Sulphuric Acid 10%	Very Good
	Hydrochloric Acid 10%	Very Good	Xylene	Poor
	Methyl ethyl Ketone (MEK)	Poor		
		Excellent = +/- 1% weight change Very Good = +/- 1-10% weight change Fair = +/- 10-20% weight change Poor = > 20% weight change		

APPLICATION INFORMATION

Cure	<p>Allow the Flexane to cure for 6 hours before returning equipment to light service. Once cured, the repair may be ground flush using a 24 or 36 grit open coat-sanding disc. Be careful to keep the grinder moving and do not overheat the work surface. De-mould Flexane Liquids in approximately 5-10 hours.</p> <p>Note: To shorten the cure time of all Flexanes, add Devcon's Flexane Accelerator (see Flexane Accessories Technical Data Sheet).</p>
Surface Preparation	<p><u>Metal Surfaces:</u> Thoroughly clean the area that is to be repaired, rebuilt or lined by using Devcon Fast Cleaner 2000 Spray/Cleaner Blend 300. All oil, grease and dirt must be removed before applying Flexane material. All surfaces must be roughened by grinding with a coarse wheel or an abrasive disc pad.</p> <p><u>Rubber Surfaces:</u> Thoroughly clean the rubber area with an abrasive pad and Devcon Fast Cleaner 2000 Spray/Cleaner Blend 300. You may take a grinding wheel and roughen the surface. The rubber surface must be coarse and free from oil and dirt clogged in the 'pores' of the rubber. Using Devcon Fast Cleaner 2000 Spray/Cleaner Blend 300, wipe or roughen surface until the colour of the rubber substrate no longer appears on cloth. The rubber should look new or a deeper black in colour.</p> <p><u>Concrete Surfaces:</u> Concrete being a very porous substrate requires multiple cleaning. Degrease the area with Devcon Fast Cleaner 2000 Spray/Cleaner Blend 300 and rinse the area. A power washer or steam cleaner is useful for quicker and efficient cleaning. Let the floor dry thoroughly before applying the Primer and Flexane.</p> <p><u>Priming Surfaces</u></p> <p><u>Metal Surfaces:</u> On metal surfaces apply two coats of FL-10 Primer and allow to dry tack free for 15 minutes.</p> <p><u>Rubber Surfaces:</u> On rubber and urethane surfaces apply a coat of FL-20 Primer and allow to dry tack free for 15 – 20 minutes. On porous rubber surfaces, it may be necessary to do multiple coats.</p> <p><u>Concrete Surfaces:</u> Concrete being a "porous" substrate may need multiple coats for proper adhesion. Let Primer dry for 30 minutes between coats.</p> <p><u>Wood & Fibreglass:</u> Use FL-20 Primer for all Wood and Fibreglass products. Softwoods will need two coats because of their absorption characteristics.</p> <p><u>Immersion Substrates:</u> Use Primers FL-10 and FL-20 to coat any metal substrate that will be immersed in any aqueous solution. First apply the FL-10 Primer and let it dry for 60 minutes. Next coat with FL-20 Primer. Let it dry for 30 minutes before applying the Flexane material</p>
Mixing	<p>Add curing agent to the Flexane resin container and stir vigorously for 2 minutes. Ensure that the two parts are fully mixed by scraping along the bottom and side of the container. For quantities larger than 500g use an electric drill and mixer to mix the Flexane material. Make sure the mixer attachment is completely submerged during the mixing process. If not you will be mixing in large amounts of air and this will sometimes cause bubbles in the finished product.</p>
Application	<p><u>Mouldmaking</u></p> <ul style="list-style-type: none"> • First ensure good surface preparation and coat the entire "box" with Devcon's Release Agent. Let it dry for 10 minutes. Apply a second coat, and let this dry for 10 minutes. • Now take a small brush and apply a thin coat of mixed product over the surface. This helps to alleviate any "air bubbles" in the curing process.

Flexane 60 Liquid

Application cont.

- Then pour the liquid into the “box”. It is recommended to tilt the “box” slightly onto one side when pouring to let the air escape easily and produce no “blow holes” in the finished product.
- After the Flexane has been poured, it helps to “wave” a hot air gun back and forth over the top of the mould to help release air bubbles that want to get to the surface.
- De-mould time is 8 hours when cured at room temperature.

Lining Applications/Noise Reduction

Flexane has an outstanding quality of having “elasticity”. This is beneficial for applications requiring impact resistance such as feeder bowls in production plants, chutes in cement, coal or mining plants and cyclones. Lining applications require a good depth of coating along with the proper primer for good adhesion.

- For good adhesion follow the cleaning method for the appropriate surface. A good surface profile is required for excellent adhesion.
- Abrade the surface of the wear area with an abrasive disc pad and clean thoroughly.
- Apply a coating of FL-10 Primer and allow it to dry thoroughly and follow with a coating of FL-20 Primer. Let it dry for 30 minutes before continuing.
- Before applying the Flexane material ensure the substrate has a defined “butt joint”. Leaving an edge will create the possibility of the aggregate “undercutting” the material. Apply the Flexane to the substrate. Apply at least 1/16” of the material if possible for better wear resistance to the substrate.

Note: Applying multiple coats to the substrate will “build up” the wearing ability of the coating.

Shelf life & Storage

A shelf life of 2 years from date of manufacture can be expected when stored at room temperature (22°C) in their original containers.

Precaution

For complete safety and handling information, please refer to Material Safety Data Sheets prior to using this product.

Warranty

ITW Devcon will replace any material found to be defective, because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

For product information visit www.devconeurope.com alternatively for technical assistance please call +44 (0) 870 458 7388 (UK) or +49 431 718830 (Germany)