

ER1448 Epoxy Resin

Product Code: ER1448

PRODUCT DESCRIPTION

This material is a fast curing epoxy resin of low viscosity. The cured product is tough and exhibits good adhesion to a variety of substrates.

The standard colour is black, although a range of colours is available. The system may be supplied in bulk, kit or resinpack form.

PRODUCT FEATURES

- * High water resistance
- * Excellent adhesive properties
- * Good electrical properties
- * Non toxic
- * Easy to use
- * Good thermal cycling characteristics

HANDLING INSTRUCTIONS

If in Resinpack form, resin and hardener are mixed by removing the clip (grip each end of the pack and pull gently) and moving the contents around inside the pack until thoroughly mixed. Take special care to push unmixed material from the corners. Mixing normally takes from two to four minutes depending on the skill of the operator. Resin and hardener are evacuated prior to packing so the system is ready for use immediately after mixing. The corner may be cut from the pack so that it may be used as a simple dispenser.

If in bulk form the resin (Part A) should be mixed with the hardener (Part B) in the ratio:

2.51 : 1 by weight

2.17 : 1 by volume


If excessive amounts of air are introduced during this mixing operation then it may be necessary to re-evacuate before use.

For best performance the mix ratio tolerance by weight should be controlled to + or - 5%

TECHNICAL
DATA
SHEET

Copyright Electrolube 2003

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.



ER1448 Epoxy Resin – Page 2

TECHNICAL
DATA
SHEET

When mixing bulk resin and hardener, once again avoid introducing excessive amounts of air. Automatic mixing equipment is available from **Electrolube** which will accurately mix resin and hardener in the correct proportions without introducing air.

Bulk material or Resinpacks must be thoroughly mixed before use - incomplete mixing will result in erratic or even partially incomplete cure.

Cure the **ER1448** system for at least:

12 hours @ 20°C
or 2 hours @ 50°C
or 0.5 hours @ 80°C

Very small castings may be hot cured immediately - in other cases it is advisable to gel at room temperature before hot curing.

TYPICAL PROPERTIES OF SYSTEM (@ 20 to 22°C)

Part A Resin

Appearance	Black liquid
Viscosity	200 - 300 centipoise
Density	1.11 g/ml

Part B Hardener

Appearance	Amber to dark coloured liquid
Viscosity	100 - 500 centipoise
Density	0.96 g/ml

Mixed System


Gel time (150g sample)	20 -30 minutes
Mixed System Viscosity	100 - 300 centipoise

Cured System

Shore Hardness (BS2782 method 365B)	>A70 minimum (target D45 to D60)
Dielectric Constant (BS7663, 10 kHz)	4.7 +/-20%
Loss Tangent (BS7663, 10 kHz)	0.08 +/-20%
Specific Gravity (ISO1183)	1.10 +/-0.05
Operating Temperature range geometry dependent)	-50 to +150°C (application and
Coefficient of thermal expansion	70 - 80 ppm/.C

Copyright Electrolube 2003

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.



ER1448 Epoxy Resin – Page 3

TECHNICAL
DATA
SHEET

CLEANING

It is far easier for machines & containers to be cleaned before the resin has been allowed to cure. Electrolube's RRS is suitable for cleaning machines and containers and cured resin may be slowly softened and removed by soaking in our RRS.

STORAGE

Resinpacks stored between 20 and 30°C in a dry place will have a shelf life of at least 18 months. Bulk material stored in the original sealed containers between 20 and 30°C will have a shelf life of at least two years. The hardener used in the ER1448 system reacts with atmospheric water, so it is especially important to keep containers tightly closed.

With prolonged storage below 15°C the hardener may crystallise resulting in a waxy / buttery texture. In extreme conditions the hardener may solidify completely. Crystallised material is recovered by heating to a maximum of 80°C for 1 to 4 hours depending on the amount of material. Loosen container seal before heating and do not breathe vapour created in this process. After heating secure lid and shake or stir contents. Allow hardener to cool before use. If crystallisation persists contact Electrolube.

HEALTH & SAFETY NOTES

The ER1448 resin and hardener are IRRITANT/CORROSIVE respectively, and both resin and hardener if handled carelessly can cause dermatitis. Gloves overalls and eye protection must be worn. If heating resin or hardener extract volatiles to the outside. Do not smoke and take care not to contaminate food stuffs. Contact Electrolube Sales Department for more information.

Copyright Electrolube 2003

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

