

Dissipative Refuse Sack - Pink



Features:

- Our ESD refuse sacks are made of antistatic polyethylene
- Printed in black with ESD caution logo and text onto polyethylene
- Complies to standards ANSI/ESD S20.20:2007 and BS EN 61340-5-1:2007



Homogeneous, non-amine antistatic polythene film which is effective at low relative humidity (less than 12%)

Specifically designed for the particular need of the electronics industry.

The special additives used do not affect the film clarity or quality, and it is therefore most economical in use, as the standard film thickness can be selected

Product Code:	Description:	Size:	Additional Notes:
091-0055	Dissipative Refuse Sack - Pink	450 x 600mm	Pack of 500

Technical Specifications:

Technical Properties:	Details:
Thickness	130 Gauge – 32.5 Microns
Tensile Strength (ASTM D 882)	1500 to 3000 psi
Tear Strength (ASTM D 1004)	65 to 450lbs/inch
Elongation (ASTM D 882)	MD: 550
Dart Impact (ASTM D 3420)	250-750 grms
Burst (Mullen) (ASTM D 3420)	20 – 60 psi
Heating Sealing (ASTM D 882)	Temperature: 250-375°F
Time	.25 – 3.5 seconds
Pressure	30-60 psi
Electrical Properties:	
Surface Resistivity	(Inside/Outside) at 28.8°C and 12% RH < 1011ohms/sq
Static Decay Rate	(5000 volts O volts at 28.8°C and 12% RH) <2 seconds

Important Notice: This data and its contents (the "Information") belong to the members of the Premiere Farnell group of companies (the "Group") or are licensed to it. No license is granted for the use of it other than for information purposes in connection with the products to which it relates. No license of any intellectual property rights is granted. The information is subject to change without notice and replaces all data sheets previously supplied. The information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on the information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp is the registered trademark of the Group. © Premiere Farnell plc 2011.