



PRODUCT/PROCESS CHANGE NOTIFICATION

PCN IPG-IPC/14/8696
Dated 23 Sep 2014

New DIE for Darlington Array ULQ2003 and ULN2003

Table 1. Change Implementation Schedule


Forecasted implementation date for change	15-Dec-2014
Forecasted availability date of samples for customer	16-Sep-2014
Forecasted date for STMicroelectronics change Qualification Plan results availability	16-Sep-2014
Estimated date of changed product first shipment	23-Dec-2014

Table 2. Change Identification

Product Identification (Product Family/Commercial Product)	see attached list
Type of change	Product design change
Reason for change	New equipment utilization, capacity optimization, better performance
Description of the change	Following Divisional Commitments towards a continuous improvement philosophy, a new DIE for Darlington Array ULQ2003 and ULN2003 has been introduced. Same diffusion, assembly and testing location are maintained. No process change. Quality and electrical performances are guaranteed
Change Product Identification	QA number
Manufacturing Location(s)	

Table 3. List of Attachments

Customer Part numbers list	
Qualification Plan results	



Customer Acknowledgement of Receipt		PCN IPG-IPC/14/8696					
Please sign and return to STMicroelectronics Sales Office		Dated 23 Sep 2014					
<input type="checkbox"/> Qualification Plan Denied <input type="checkbox"/> Qualification Plan Approved <input type="checkbox"/> Change Denied <input type="checkbox"/> Change Approved	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr><td style="padding: 2px;">Name:</td></tr> <tr><td style="padding: 2px;">Title:</td></tr> <tr><td style="padding: 2px;">Company:</td></tr> <tr><td style="padding: 2px;">Date:</td></tr> <tr><td style="padding: 2px;">Signature:</td></tr> </table>		Name:	Title:	Company:	Date:	Signature:
Name:							
Title:							
Company:							
Date:							
Signature:							
Remark							

DOCUMENT APPROVAL

Name	Function
Riviera, Antonio	Marketing Manager
Naso, Lorenzo	Product Manager
Moretti, Paolo	Q.A. Manager

WHAT:

Following Divisional Commitments towards a continuous improvement philosophy, a new DIE for Darlington Array ULQ2003 and ULN2003 has been introduced. Same diffusion, assembly and testing location are maintained. No process change. Quality and electrical performances are guaranteed.

For the complete list of the part numbers affected by the change, please refer to the attached Products list.

WHY:

New equipment utilization, capacity optimization, better performance. This manufacturing change will improve service to ST Customers.

HOW:

The qualification program mainly consist of reliability tests and comparative electrical characterizations.

The related reliability report is annexed to this document.

WHEN:

The implementation will be finalized within Week 50-14

Marking and traceability:

Unless otherwise stated by customer specific requirement, the traceability of the parts assembled with the new die will be ensured by the Q.A. number.

The changed here reported will not affect the electrical, dimensional and thermal parameters keeping unchanged all information reported on the relevant datasheets.

There is as well no change in the packing process or in the standard delivery quantities.

Lack of acknowledgement of the PCN within 30 days will constitute acceptance of the change. After acknowledgement, lack of additional response within the 90 day period will constitute acceptance of the change (Jedec Standard No. 46-C).

In any case, first shipments may start earlier with customer's written agreement.

Reliability Report
Reliability Qualification on
T.V.:ULQ2003D1013TR
New die with layout optimization

General Information	
Product Line	L20303
Product Description	SEVEN DARLINGTON ARRAYS
P/N	ULQ2003D1013TR
Product Group	IPG
Product division	IND.& POWER CONV.
Packages	SO16
Silicon Process technology	BIPOLAR

Locations	
Wafer fab	Ang Mo Kio
Assembly plant	SHENZHEN
Reliability Lab	ST Catania

DOCUMENT INFORMATION

Version	Date	Pages	Prepared by	Approved by	Comment
1.0	August 2014	8	Angelo Basile	Giovanni Presti	Final Report

Note: This report is STconfidential and is a summary of the reliability trials performed in good faith by STMicroelectronics in order to evaluate the potential reliability risks during the product life using a set of defined test methods.
 This report does not imply for STMicroelectronics expressly or implicitly any contractual obligations other than as set forth in STMicroelectronics general terms and conditions of Sale. This report and its contents shall not be disclosed to a third party without previous written agreement from STMicroelectronics.



TABLE OF CONTENTS

1 APPLICABLE AND REFERENCE DOCUMENTS3
2 GLOSSARY.....3
3 RELIABILITY EVALUATION OVERVIEW.....3
 3.1 OBJECTIVES3
 3.2 CONCLUSION3
4 DEVICE CHARACTERISTICS.....4
 4.1 DEVICE DESCRIPTION.....4
 4.2 CONSTRUCTION NOTE4
5 TESTS RESULTS SUMMARY.....5
 5.1 TEST VEHICLE.....5
 5.2 TEST PLAN AND RESULTS SUMMARY5
6 ANNEXES6
 6.1 DEVICE DETAILS.....6

1 APPLICABLE AND REFERENCE DOCUMENTS

Document reference	Short description
JESD47	Stress-Test-Driven Qualification of Integrated Circuits

2 GLOSSARY

DUT	Device Under Test
SS	Sample Size

3 RELIABILITY EVALUATION OVERVIEW

3.1 Objectives

Qualifications of the New die *with layout optimization*

3.2 Conclusion

Qualification Plan requirements have been fulfilled without exception. It is stressed that reliability tests have shown that the devices behave correctly against environmental tests (no failure)

The present reliability final report is positive

4 DEVICE CHARACTERISTICS

4.1 Device description

The ULQ2001A, ULQ2002A, ULQ2003 and ULQ2004A are high voltage, high current darlington arrays each containing seven open collector darlington pairs with common emitters. Each channel is rated at 500 mA and can withstand peak currents of 600 mA. Suppression diodes are included for inductive load driving and the inputs are pinned opposite the outputs to simplify board layout. The four versions interface to all common logic. These versatile devices are useful for driving a wide range of loads including solenoids, relays, DC motors, LED displays, filament lamps, thermal printheads and high power buffers. The ULQ2001A/2002A/2003A and 2004A are supplied in 16 pin plastic DIP packages with a copper leadframe to reduce thermal resistance. They are available also in small outline package (SO-16) as ULQ2001D1/2002D1/2003D1/2004D1.

4.2 Construction note

P/N	ULQ2003D1013TR
Wafer/Die fab. information	
Wafer fab manufacturing location	Ang Mo Kio
Technology	BiP > 6um
Die finishing back side	CHROMIUM/NICKEL/GOLD
Die size	2280, 1200 micron
Passivation type	SiN (nitride)
Prod. Mask Set Rev.	CL203D REV A for DIE CODE : PL
Wafer Testing (EWS) information	
Electrical testing manufacturing location	Ang Mo Kio EWS
Tester	ASL1000
Test program	CL203CB6_0200.ZIP
Assembly information	
Assembly site	SHENZHEN
Package description	SO 16
Molding compound	Epoxy
Frame material	FRAME SO 16L 94x150 SHD OpC 8fus 4Layers
Die attach material	Epoxy
Wires bonding materials/diameters	WIRE Cu D1.0
Final testing information	
Testing location	SHENZHEN
Tester	ASL 1000
Test program	L203_STE_FA_01.prg

5 TESTS RESULTS SUMMARY

5.1 Test vehicle

Lot #	Diffusion Lot	Assy Lot	Techn code	Process/ Package	Product Line	Comments
1	641107HD#25	GK420TV01	PZQ7*L203DA6	SO16	L20303	

5.2 Test plan and results summary

P/N


Test	PC	Std ref.	Conditions	SS	Steps h=hours cy=cycles	Failure/SS	Note
						LOT 1	
Die Oriented Tests							
HTOL	N	JESD22 A-108	Tj = 125° C BIAS= Vin=+ 50V	77	168h	0/77	
					500h	0/77	
					1000h	0/77	
HTSL	N	JESD22 A-103	Ta = 150°C	45	168h	0/45	
					500h	0/45	
					1000h	0/45	
Package Oriented Tests							
PC	Y	JESD22 A-113	Drying 24 H@ 125° C Store 168H @ Ta=85°C Rh=85% Over Reflow @ Tpeak=260° C 3 times	231	168H	PASS	
AC	Y	JESD22 A-102	Pa=2Atm / Ta=121°C	77	168h	0/77	
THB	Y	JESD22 A-101	Ta = 85°C, Rh=85% Vbias +35V	77	168h	0/77	
					500h	0/77	
					1000h	0/77	
TC	Y	JESD22 A-104	Ta = -65°C to 150°C	77	100cy	0/77	
					300cy	0/77	
					500cy	0/77	
Other Tests							
ESD	N	JEDEC JS001	HBM	3	+/- 3KV	Pass	
		JESD22- C101	CDM	3	+/- 500V	Pass	

6 ANNEXES

6.1 Device details

6.1.1 Pin connection

Figure 2. Pin connections (top view)




6.1.2 Package information

Table 6. SO-16 narrow mechanical data

Dim.	mm.			Inch.		
	Min.	Typ.	Max.	Min.	Typ.	Max.
A			1.75			0.069
a1	0.1		0.25	0.004		0.009
a2			1.6			0.063
b	0.35		0.46	0.014		0.018
b1	0.19		0.25	0.007		0.010
C		0.5			0.020	
c1			45°	(typ.)		
D(t)	9.8		10	0.386		0.394
E	5.8		6.2	0.228		0.244
e		1.27			0.050	
e3		8.89			0.350	
F(t)	3.8		4.0	0.150		0.157
G	4.60		5.30	0.181		0.208
L	0.4		1.27	0.150		0.050
M			0.62			0.024
S	8° (max.)					

Figure 20. SO-16 package dimensions



0016/020 D

6.1.3 Test description

Test name	Description	Purpose
Die Oriented		
HTOL High Temperature Operative Life	The device is stressed in static or dynamic configuration, approaching the operative max. absolute ratings in terms of junction temperature and bias condition.	To determine the effects of bias conditions and temperature on solid state devices over time. It simulates the devices' operating condition in an accelerated way. The typical failure modes are related to, silicon degradation, wire-bonds degradation, oxide faults.
HTSL High Temperature Storage Life	The device is stored in unbiased condition at the max. temperature allowed by the package materials, sometimes higher than the max. operative temperature.	To investigate the failure mechanisms activated by high temperature, typically wire-bonds solder joint ageing, data retention faults, metal stress-voiding.
Package Oriented		
PC Preconditioning	The device is submitted to a typical temperature profile used for surface mounting devices, after a controlled moisture absorption.	As stand-alone test: to investigate the moisture sensitivity level. As preconditioning before other reliability tests: to verify that the surface mounting stress does not impact on the subsequent reliability performance. The typical failure modes are "pop corn" effect and delamination.
AC Auto Clave (Pressure Pot)	The device is stored in saturated steam, at fixed and controlled conditions of pressure and temperature.	To investigate corrosion phenomena affecting die or package materials, related to chemical contamination and package hermeticity.
TC Temperature Cycling	The device is submitted to cycled temperature excursions, between a hot and a cold chamber in air atmosphere.	To investigate failure modes related to the thermo-mechanical stress induced by the different thermal expansion of the materials interacting in the die-package system. Typical failure modes are linked to metal displacement, dielectric cracking, molding compound delamination, wire-bonds failure, die-attach layer degradation.
THB Temperature Humidity Bias	The device is biased in static configuration minimizing its internal power dissipation, and stored at controlled conditions of ambient temperature and relative humidity.	To evaluate the package moisture resistance with electrical field applied, both electrolytic and galvanic corrosion are put in evidence.
ESD Electro Static Discharge	The device is submitted to a high voltage peak on all his pins simulating ESD stress according to different simulation models. HBM: Human Body Model CBM: Charged Device Model	To classify the device according to his susceptibility to damage or degradation by exposure to electrostatic discharge.

Please Read Carefully:

Information in this document is provided solely in connection with ST products. STMicroelectronics NV and its subsidiaries ("ST") reserve the right to make changes, corrections, modifications or improvements, to this document, and the products and services described herein at any time, without notice.

All ST products are sold pursuant to ST's terms and conditions of sale.

Purchasers are solely responsible for the choice, selection and use of the ST products and services described herein, and ST assumes no liability whatsoever relating to the choice, selection or use of the ST products and services described herein.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted under this document. If any part of this document refers to any third party products or services it shall not be deemed a license grant by ST for the use of such third party products or services, or any intellectual property contained therein or considered as a warranty covering the use in any manner whatsoever of such third party products or services or any intellectual property contained therein.

UNLESS OTHERWISE SET FORTH IN ST'S TERMS AND CONDITIONS OF SALE ST DISCLAIMS ANY EXPRESS OR IMPLIED WARRANTY WITH RESPECT TO THE USE AND/OR SALE OF ST PRODUCTS INCLUDING WITHOUT LIMITATION IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE (AND THEIR EQUIVALENTS UNDER THE LAWS OF ANY JURISDICTION), OR INFRINGEMENT OF ANY PATENT, COPYRIGHT OR OTHER INTELLECTUAL PROPERTY RIGHT.

ST PRODUCTS ARE NOT DESIGNED OR AUTHORIZED FOR USE IN: (A) SAFETY CRITICAL APPLICATIONS SUCH AS LIFE SUPPORTING, ACTIVE IMPLANTED DEVICES OR SYSTEMS WITH PRODUCT FUNCTIONAL SAFETY REQUIREMENTS; (B) AERONAUTIC APPLICATIONS; (C) AUTOMOTIVE APPLICATIONS OR ENVIRONMENTS, AND/OR (D) AEROSPACE APPLICATIONS OR ENVIRONMENTS. WHERE ST PRODUCTS ARE NOT DESIGNED FOR SUCH USE, THE PURCHASER SHALL USE PRODUCTS AT PURCHASER'S SOLE RISK, EVEN IF ST HAS BEEN INFORMED IN WRITING OF SUCH USAGE, UNLESS A PRODUCT IS EXPRESSLY DESIGNATED BY ST AS BEING INTENDED FOR "AUTOMOTIVE, AUTOMOTIVE SAFETY OR MEDICAL" INDUSTRY DOMAINS ACCORDING TO ST PRODUCT DESIGN SPECIFICATIONS. PRODUCTS FORMALLY ESCC, QML OR JAN QUALIFIED ARE DEEMED SUITABLE FOR USE IN AEROSPACE BY THE CORRESPONDING GOVERNMENTAL AGENCY.

RESTRICTIONS OF USE AND CONFIDENTIALITY OBLIGATIONS:

THIS DOCUMENT AND ITS ANNEXES CONTAIN ST PROPRIETARY AND CONFIDENTIAL INFORMATION. THE DISCLOSURE, DISTRIBUTION, PUBLICATION OF WHATSOEVER NATURE OR USE FOR ANY OTHER PURPOSE THAN PROVIDED IN THIS DOCUMENT OF ANY INFORMATION CONTAINED IN THIS DOCUMENT AND ITS ANNEXES IS SUBMITTED TO ST PRIOR EXPRESS AUTHORIZATION. ANY UNAUTHORIZED REVIEW, USE, DISCLOSURE OR DISTRIBUTION OF SUCH INFORMATION IS EXPRESSLY PROHIBITED.

Resale of ST products with provisions different from the statements and/or technical features set forth in this document shall immediately void any warranty granted by ST for the ST product or service described herein and shall not create or extend in any manner whatsoever, any liability of ST.

ST and the ST logo are trademarks or registered trademarks of ST in various countries.

Information in this document supersedes and replaces all information previously supplied.

The ST logo is a registered trademark of STMicroelectronics. All other names are the property of their respective owners

© 2014 STMicroelectronics - All rights reserved.

STMicroelectronics group of companies

Australia - Belgium - Brazil - Canada - China - Czech Republic - Finland - France - Germany - Hong Kong - India - Israel - Italy - Japan - Malaysia - Malta - Morocco - Philippines - Singapore - Spain - Sweden - Switzerland - United Kingdom - United States of America

www.st.com

