Spiral Binding

pro-**Power**

RoHS Compliant



Specifications:

Material : Polyethylene Halogen Free

Density : 920 kg/m3
Tensile Strength : 12 MPa
Ultimate Elongation : 550%

Temperature of use : -50°C to +85°C

Melting Point : +112°C

Dielectric Strength : >25 kV/mm

Water Absorption : Lower than 0.1%

Chemical Resistance : Very Good

Flame Resistance : None

Part Number Table

Description	Part Number
Spiral Binding 3mm Natural, 50m	0819 0001 018
Spiral Binding 6mm Natural, 25m	0819 0002 018
Spiral Binding 12mm Natural, 25m	0819 0003 018
Spiral Binding 22mm Natural, 25m	0819 0021 018
Spiral Binding 3mm Black, 50m	0819 0004 010
Spiral Binding Black, 25m	0819 0005 010
Spiral Binding 12mm Black, 25m	0819 0006 010
Spiral Binding 22mm Black, 25m	0819 0022 010

Important Notice: This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. pro-POWER is the registered trademark of the Group. © Premier Farnell plc 2012.

www.element14.com www.farnell.com www.newark.com www.cpc.co.uk

