

<b>Vermason</b>		Product Information No: PIS 174		
	Page 1 of 1	Issue No 3	Date : 12 March 2002	Approved by:

## MOISTURE BARRIER BAGS

Code BW9xx

Moisture barrier bags are used to pack IC trays, tubes, and reels of components. The bags are made from a five-layer metalised polyester/polyethylene structure that offers high puncture resistance, high barrier properties and superior vacuum packing performance. The low MVTR of the material results in a reduced desiccant requirement and offers a very good cost/performance relationship for packing moisture sensitive components. Moisture barrier bags meet or exceed the requirements of MIL-B-81705C, EIA 583.

### Construction:

Outer layer	Static dissipative metalised polyester
Middle layer	Static dissipative metalised polyester
Inner layer	Static dissipative polyethylene

### Physical Properties:

Moisture vapour transmission rate	<0.3g/sqm/24hrs or <0.02g/100in <sup>2</sup> /24 hours. ASTM F-1249 (at 37°C and 90% RH) pre flexed.		
Puncture resistance	18 lbs	FTMS 101C	
Tensile strength	>20 lbs/in	ASTM D882	
Tear strength	>2 lbs	ASTM D1004	
Seal strength	No delamination (160°F)	MIL 81705C	

### Electrical Properties:

Surface resistance	Inner surface	<1 x 10 <sup>11</sup> Ohms	EOS/ESD S.11.11
	Outer surface	<1 x 10 <sup>11</sup> Ohms	EOS/ESD S.11.11
Static decay	<2.0 sec (5000-50 Volts)		FTMS 101C
EMI shielding	>40 dB		Mil B-81705C
Capacitance probe	<10V		EIA 541

### Chemical Properties:

Corrosion	No effect on aluminium, copper, silver, Pb-Sn coated foil, stainless steel, Kevlar®, low carbon steel.
Polycarbonate	Compatible

*For further information, please contact*

**Vermason Ltd, 1 Avenue One, Letchworth, Hertfordshire SG6 2HB. UK**

**Tel: +44(0)1462 672005 Fax: +44(0)1462 670440**

**e-mail : [sales@vermason.co.uk](mailto:sales@vermason.co.uk)**

**[www.vermason.co.uk](http://www.vermason.co.uk)**