Dual Wall Tubing (4X)

Anti-UV Light, Soft, Highly Flame Retardant, Excellent Waterproof, Moisture-Proof, Sealing Performance, Adhesive-Lined, Heat Shrinkable For Automotive Wiring Harness

oro-**power**





Description

High Flame-retardant adhesive-lined heat shrinkable tube for Automotive Wiring Harness 4:1 produced by high quality polyolefin and flame retardant hot melt adhesive through double-layer Co-extrusion process. The outer layer of this tube has high physical and chemical properties, and good contraction, and so on. The inner layer of this tube made of high quality holt melt in white colour which has low melting point, waterproof sealing and good Mechanical strain buffering.

It is Widely used in automotive wiring harness connected waterproof; anti gas and electricity leakage; stranded harness waterproof seal (such as home appliance wiring harness, electrical equipment wiring harness and so on); wire and cable branch at sealing waterproofing, corrosion protection for metal pipes, wire and cable repairing, water pump, submersible pump wiring waterproofing and other applications.

Specifications

Operating temperature	: -45°C to +125°C
Minimum Full Recovery Temperature	: 125°C
Minimum shrink temperature	: 70°C
Shrink Ratio	: 4:1
Colour	: Outer layer Black
	Inner layer White (Adhesive-lined layer)

Outer Layer - Technical Data

Property	Test Method	Typical Data	
Tensile Strength	ASTM D 2671	≥10.4MPa	
Elongation at breaking	ASTM D 2671	≥300%	
Tensile Strength after Aging	UL 224 158°C×168hrs	≥7.3	
Elongation at break after heat aging	UL 224 158°C×168hrs	≥100	
Axial shrinkage rate	ASTM D 2671	-8% to +8%	
Flammability	SAE-AMS-DTL-23053/5	Self-distinguish within 30s	
Dielectric strength	IEC 243	≥15kV/mm	
Volume resistance	IEC 93	≥1x10¹⁴Ω·cm	

Adhesive - Technical Data

Property	Test Method	Typical Data
Water Absorption	ASTM D 570	≤0.2%
Softening Point	ASTM D E28	85°C
Peel Strength (to PE)	ASTM D 1000	120N/25m
Peel Strength (to AL)	ASTM D 1000	80N/25m

www.element14.com www.farnell.com www.newark.com www.cpc.co.uk



oro-**power**

Product Dimensions

	Siz	e.	As supplied	After recovery(mm)		
Part Number	Inch	mm	Internal Diameter(mm)	Internal Diameter	Total Wall Thickness	Adhesive thickness
PP001987	5/32	4	4	≤0.95	1.2 ±0.2	0.5 ±0.2
PP001988	1/4	6	≥6	≤1.27	1.3 ±0.2	0.56 ±0.2
PP001989	5/16	8	≥8	≤1.65	1.65 ±0.2	0.76 ±0.2
PP001986	1/2	12	≥12	≤2.41	2 ±0.2	1.02 ±0.2

Part Number Table

Description	Part Number
Tubing, Heat Shrink, Dual Wall, Adhesive Lined, 4:1, 12mm, Black, 1.2m	PP001986
Tubing, Heat Shrink, Dual Wall, Adhesive Lined, 4:1, 4mm, Black, 1.2m	PP001987
Tubing, Heat Shrink, Dual Wall, Adhesive Lined, 4:1, 6mm, Black, 1.2m	PP001988
Tubing, Heat Shrink, Dual Wall, Adhesive Lined, 4:1, 8mm, Black, 1.2m	PP001989

Important Notice : This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. pro-POWER is the registered trademark of the Group. © Premier Farnell Limited 2016.

www.element14.com www.farnell.com www.newark.com www.cpc.co.uk

