# productinformation

## tesa® 62934

## Double-sided PE-foam mounting tape

tesa® 62934 is a double-sided PE-foam tape for constructive mounting applications. It consists of a highly conformable PE-foam backing and a tackified acrylic adhesive.

### Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

## Main Application

- Decorative aluminium cover screens on brown goods
- Doorhandles in kitchen furniture
- Moulded plastic parts
- Mirrors and coloured glass panels

#### Technical Data

	Backing material	PE foam		Type of adhesive	tackified acrylic
	Color	black/white	•	Elongation at break	250 %
٠	Total thickness	800 μm	•	Tensile strength	8 N/cm

#### Adhesion to

•	Steel (initial)	17.0 N/cm	•	Steel (after 14 days)	17.0 N/cm
	ABS (initial)	17.0 N/cm	•	ABS (after 14 days)	17.0 N/cm
	Aluminium (initial)	17.0 N/cm	•	Aluminium (after 14 days)	17.0 N/cm
	PC (initial)	15.0 N/cm	•	PC (after 14 days)	17.0 N/cm
	PE (initial)	2.7 N/cm	•	PE (after 14 days)	2.8 N/cm
	PET (initial)	12.5 N/cm	•	PET (after 14 days)	17.0 N/cm
	PP (initial)	2.8 N/cm		PP (after 14 days)	5.5 N/cm
	PS (initial)	15.0 N/cm	•	PS (after 14 days)	17.0 N/cm
	PVC (initial)	17.0 N/cm		PVC (after 14 days)	17.0 N/cm

For latest information on this product please visit <a href="http://l.tesa.com/?ip=62934">http://l.tesa.com/?ip=62934</a>



## tesa® 62934

## Double-sided PE-foam mounting tape

## **Properties**

Temperature resistance short term	80 °C	<ul> <li>Humidity resistance</li> </ul>	••••
Temperature resistance long term	80 °C	<ul> <li>Softener resistance</li> </ul>	• •
Tack	• • •	<ul> <li>Static shear resistance at 23°</li> </ul>	C •••
Ageing resistance (UV)	• • •	<ul> <li>Static shear resistance at 40°</li> </ul>	C •••

Evaluation across relevant tesa® assortment: ••• very good •• good • medium • low

#### Additional Information

Liner variants:

PV0 brown glassine paper (71  $\mu$ m) PV14 white PE-coated paper (120  $\mu$ m) PV10 red filmic liner (120  $\mu$ m)

tesa® 62934 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 / 61646 climate tests and a 85°C temperature resistance. (TÜV report number 21209595).

#### Peel Adhesion:

- immediate: foam splitting on Steel, Aluminium, ABS
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC