

Moldable Plastic - PolyMold Series



Overview

The PolyMold moldable plastic is made from a type of plastic called Polycaprolactone (PCL). PCL is nontoxic, biodegradable, and has a low melting point of 136°F - 140°F (58°C - 60°C). When melted, it becomes a moldable putty-like material. It is perfect for making models, replacement parts, robotics, toys, sculptures, and much more. Its plastic properties are similar to Nylon.

Instructions

Heat-up PolyMold

Hot Water Method (recommended)

- Heat water to approximately 150°F ~ 170°F in a ceramic or metal container suitable for hot water. Do not overheat.
- Place the desired amount of PolyMold beads into the hot water bath (any excess can always be reused). The beads will quickly become translucent and will bond together. Let soak for up to 2 minutes.
- Remove the soft clump of plastic with a metal or disposable utensil (tongs, wooden kabob stick, etc.). The PolyMold is now ready to use.

Heat Gun (useful for reheating material already in use)

- On a heat-safe surface, hold a heat gun or hair dryer on the material.
- Once the material nears 140+°F, it will begin to soften. Continue to heat until the material reaches the desired moldable consistency. Do no overheat.

Mold PolyMold

- Be careful, the material will be hot.
- Simply mold the PolyMold plastic like clay. If a water method was used to heat the substance, the water will work itself out without thinning the material.
- PolyMold can also be pressed into molds, cut, tapped (after hardened), and much more.
- Use your imagination.

Harden PolyMold

- The PolyMold will harden by itself as it cools and returns to room temperature.
- To speed the process, dip the molded PolyMold into a bath of cold water.

Colour PolyMold

- To add some colour to your PolyMold, add 1-10 pellets of the colourant (sold separately) to the batch of beads before you melt the PolyMold using the Hot Water method. Use the colourant beads sparingly.



Moldable Plastic - PolyMold Series

- TIP: Start with 1-2 beads, adding more later for richer colours. Feel free to mix colours to create new colours.
- When you remove the PolyMold with colourant from the hot bath, knead the PolyMold until the desired colour effect is achieved.

Reuse PolyMold

- To reuse extra PolyMold, add additional colourant, or even start over on a project, simply heat it back up!

Part Number Table

Description	Part Number
Moldable Plastic, PolyMold Series, 8.85oz, Jar	21-12825
Moldable Plastic, PolyMold Series, 17.6oz, Jar	21-12830
Moldable Plastic, PolyMold Series, 35.2oz, Jar	21-12835

Important Notice : This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. MCM is the registered trademark of the Group. © Premier Farnell Limited 2016.

