Spiral Binding





Description

The limited fire hazard properties of this product make it ideally suited for use in special applications such as rail and aviation, public buildings and railway stations, where public safety is critical.

Low smoke, low toxicity and zero halogen, the compound meets the requirements of DIN/VDE 2007 and BS6724.

Applications

For protecting cable looms before and after installation.

Specifications

Material : Nylon, Low Smoke, Halogen-Free

Service Temperature Range : -20°C to +90°C

After Heat Ageing

for 7 Days at 110°C : Tensile strength 16MPa, Elongation 140%

Smoke Density : Pass ASTM E-662 Standards : DIN/VDE 0207. BS 6724.

Part Number Table

Description	Size OD (mm)	Wall Thickness (mm)	Part Number
Spiral Binding, LSZH, Grey, 50m	3	0.4	PP002662
Spiral Binding, LSZH, Grey, 50m	6	0.6	PP002663
Spiral Binding, LSZH, Grey, 25m	12	0.8	PP002664

Important Notice: This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. pro-POWER is the registered trademark of the Group. © Premier Farnell Limited 2016.

www.element14.com www.farnell.com www.newark.com www.cpc.co.uk

