



L969 Plyvolt® Linerless High Voltage Insulating Tape

Technical Data Sheet

October 2017

Description and Features

L969 Plyvolt® is an ethylene rubber based high voltage tape with excellent electrical, chemical and physical properties. **L969 Plyvolt®** is a linerless, self-bonding tape that permits much quicker taping speeds than a tape with a liner and yields a uniform, void-free build-up. The excellent stretch of **L969 Plyvolt®** allows conformability to the most complex shapes and contour. **L969 Plyvolt®** is compatible with all extruded cable insulations and is specially formulated to have excellent thermal conductivity that will allow the heat to dissipate from a joint. It is flame retardant and meets typical industry standards.

- Linerless
- Self-bonding
- Outstanding corona and ozone resistance
- High thermal conductivity and flame retardant
- Excellent moisture, corrosion and chemical resistance. UV resistance
- Lead free

Materials	Backing	Adhesive	Color	Standard Sizes
	EPR Rubber	Acrylic adhesive	Black	Width x Length 19 mm x 9,1 m (0.75 in. x 30 ft.) 38 mm x 9,1 m (1.5 in. x 30 ft.) Other sizes available upon request

Technical Properties	Characteristic	Typical Value	Test Method
	Thickness, (mm)	0,76	ASTM D 4325
	Breaking strength (MPa)	2,3	ASTM D 412
	Elongation at break (%)	890	ASTM D 412
	Fusion (2,0 mm max.)	No flag	ASTM D 4325
	Heat Resistance °C	130	ASTM D 4325
	Operating Temp.:		
	Continuous (°C)	90	ASTM D 4325
	Emergency Overload (°C)	130	ASTM D 4325
	Water Absorption (%)	0,06	ASTM D 570
	Ozone Resistance (visual)	Pass	ASTM D 4325
	UV Resistance (visual)	Pass	ASTM D 4325
	Dielectric Strength (kV/mm)	39	ASTM D 149
	Dissipation Factor		
	After water immersion	0,005	ASTM D 150
	After hot water immersion	0,015	
	Dielectric Constant:		ASTM D 150
	After water immersion	2,9	ASTM D 150
	After hot water immersion	3,1	ASTM D 150
	Volume Resistivity (Ω.cm)		
	96h @ 23°C and 50% RH	1x10 ¹⁶	ASTM D 257
	96h @ 23°C and 96% RH	1x 10 ¹³	ASTM D 257

Recommended Uses For insulating and jacketing of splices on power cable from 600 volts through 69,000 volts and for building stress cones and jacketing of terminations on power cable from 600 volts through 35,000 volts. Insulate and protect bus bars and joints.

Storage In original packaging, placed in horizontal position under cover and temperature between 5°C and 35 °C.

Shelf Life 60 months from date of manufacture.

Data in table represents average test results and are not to be used for specification purpose. The product users should make their own tests to determine the products' suitability for the intended use.

LIMITED WARRANTY: Plymouth warrants that its Product will substantially conform to that products written specifications for a period of one (1) year from the date of shipment, (Unless provided otherwise). Plymouth makes no warranty to the distributor, its customers, or the product's end user for the products merchantability and/or suitability for his/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proved to be defective within the terms described above, and provided buyer shall have first complied with all return policies of Plymouth, PLYMOUTH'S SOLE OBLIGATION AND BUYER'S EXCLUSIVE REMEDY UNDER THIS PRODUCT WARRANTY SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT AS IS PROVED TO BE DEFECTIVE WITHIN THE TIME PERIOD SPECIFIED ABOVE. EXCEPT AS EXPRESSLY SET FORTH HEREIN, PLYMOUTH MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED. In no event shall Plymouth be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products. (rev. 1/2017-2019)