

	VITAL TECHNICAL SDN. BHD.	 
	Technical Data Sheet	
	VT-180 Vital Gum	

Issuance date: 31/03/08

Revision date: 30/11/17

Revision No.: 04

Product Specification:

Appearance	: Dark grey paste
Chemical type	: Sodium silicate
Odor	: No odor
Shelf life	: 12 months @ 30°C
Features	: For all exhaust system : Fast and easy assembly : Heat and shock resistance
Content	: 150 g tube



Product Description:

Vital Gum is a thick, non-slumping paste type repair material. It cures by evaporation of water and further cures with heat. It will expand and set when heated, ensuring a perfect seal against all noxious fumes. It is also useful for kiln repairs and any industrial applications where a seal is required to withstand intense heat up to 300°C.

Applications:

Specially formulated for the assembly of all joint of exhaust system, including Mufflers, Tailpipes, Catalytic Converters etc

Directions:

1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
2. Wet the surface to be repaired with water.
3. Apply the Gum directly over the hole.
4. Allow to dry for 30 minutes then start engine and allow to run fast for at least 10 minutes.
5. For new installation, apply the Gum around inside of the larger pipe. Complete and seal the connection.
6. Clean up with water prior to material drying.

Caution:

Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Storage:

- Store in dry and cool place with temperature below 30 °C.
- Use within 12 months from date of production.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.

- END -