

# vydyne 21SPF/21SPG data sheet

Natural and Black general purpose high productivity

## Product Description

**Vydyne® 21SPF/21SPG are general purpose Nylon 66 resins available in natural color and black.** They are designed principally for injection molding fabrication. These grades offer a well-balanced combination of engineering properties characterized by high strength; rigidity; good toughness; high melt point; good surface lubricity; abrasion resistance; and resistance to many chemicals, solvents, gasoline, and machine and motor oils. In addition to these attributes, Vydyne 21SPG also offers an enhanced lube package, which is designed for fast cycling and is ideal for use in applications where the part is intended to be decorated during secondary operations, such as vacuum metallization or printing. This mold release package also provides stability during processing, resulting in more efficient cycle times due to the material's moderate level of nucleation and high flow.

**Vydyne 21SPF/21SPG Series resins** permit production of molded parts with good initial color plus good property and color retention when using regrind. These resins are recognized by Underwriters Laboratories and conform to the requirements of many industrial, federal, and military specifications for premium-quality, general purpose Nylon 66 resins.

**Vydyne 21SPF/21SPG Series resins** are internally and externally lubricated for improved machine feed and exceptional mold release. They are intended for use in high-productivity applications. In many applications, the molding cycle can be reduced because parts may be removed from the cavity at higher temperatures. In difficult molds where parts have a tendency to stick in the cavity, Vydyne 21SPF/21SPG can reduce or eliminate the need for mold release sprays. Critical molded part dimensions should be checked against specifications before implementing shorter molding cycles on a routine production basis.

## Typical Applications/End Uses

Vydyne 21SPF/21SPG Series resins have been used in many molding applications such as terminal blocks, bearings, bushings, cams, electrical connectors and housings, electrical cable ties/tie straps and many other hardware and general industrial parts.

Find more information or contact us at [www.vydyne.com](http://www.vydyne.com)



## Vydyne 21SPF/21SPG Specifications and Regulations

### ASTM

Conforms to ASTM D-4066 PA0111  
Conforms to ASTM D-6779 PA0111

### Federal\*

Conforms to Federal Specification LP-410a

### Military\*

Conforms to Military Specification MIL-M-20693B

### FDA

Complies with 21 CFR 177-1500

\* Superseded by ASTM D-4066



# Typical Properties for Vydyne 21SPF/21SPG Series

Test temperature 23°C unless otherwise noted

Physical Properties	Test Conditions	Dry as Molded	Conditioned 2.5% Moisture
Specific Gravity (g/cm <sup>3</sup> )	ISO 1183	1.14	—
Mold Shrinkage (%)	ISO 294-4		
2 mm - Parallel		1.6	—
2 mm - Normal		2.1	—
Water Absorption @ 23°C (%)	ISO 62		
24 Hours		1.3	—
Equilibrium at 50% RH		2.4	—
Mechanical Properties	Test Conditions	Dry as Molded	Conditioned 2.5% Moisture
Tensile Strength @ Yield (MPa)	ISO 527	85	62
Tensile Strength @ Break (MPa)	ISO 527	—	—
Elongation @ Yield (%)	ISO 527	4.5	20
Elongation @ Break (%)	ISO 527	25	160
Tensile Modulus (MPa)	ISO 527	3,400	1,500
Poisson's Ratio	ISO 527	0.42	—
Flexural Modulus (MPa)	ISO 178	3,000	1,350
Flexural Strength (MPa)	ISO 178	89	23
Notched Charpy Impact (KJ/M <sup>2</sup> )	ISO 179		
23°C		6.1	—
-30°C		4.9	—
Unnotched Charpy Impact (KJ/M <sup>2</sup> )	ISO 179		
23°C		NB	—
-30°C		NB	—
Notched Izod Impact (KJ/M <sup>2</sup> )	ISO 180	5.5	—
Thermal Properties	Test Conditions	Dry as Molded	Conditioned 2.5% Moisture
Melting Point (°C)	ISO 3146	260	—
Heat Deflection Temperature (°C)	ISO 75		
1.82 MPa		74	—
0.45 MPa		205	—
Vicat @ 50N (°C)	ISO 306	239	—
Coefficient of Linear Thermal Expansion	ISO 11359		
2 mm - Parallel, 23°C-55°C (10 <sup>-6</sup> mm/mm/°C)		1.1	—
2 mm - Normal, 23°C-55°C (10 <sup>-6</sup> mm/mm/°C)		1.2	—
Electrical Properties	Test Conditions	Dry as Molded	Conditioned 2.5% Moisture
Dielectric Strength (kV/mm) (step-by-step) 3.0 mm	IEC 60243	12	—
Volume Resistivity (ohm-cm x 10 <sup>15</sup> ) 3.0 mm	IEC 60093	6	—
Comparative Tracking Index (volts) 3.0 mm	IEC 60112	> 600	—

# Flammability Properties for Vydyne 21SPF/21SPG

Flammability Properties	Test Conditions	Dry as Molded
<b>Glow Wire Flammability Index (GWFI/°C)</b>	IEC 60695-2-12	
0.71 mm		—
1.5 mm		—
3.0 mm		—
<b>Glow Wire Ignition Temperature (GWIT/°C)</b>	IEC 60695-2-12	
0.71 mm		—
1.5 mm		—
3.0 mm		—
<b>Limiting Oxygen Index (%)</b>	ASTM D-2863	<b>26</b>

## Typical Molding Conditions for Vydyne 21SPF/21SPG Series

Optimal processing conditions will depend on such features as machine size, screw design, die design, and material residence time. The settings below are a guide to achieving stable processing and good part quality. It is best to use a hand-held pyrometer to measure stock melt temperature in an air shot.

## Underwriters Laboratories Recognized Component Ratings

Yellow Card File Number E70062

## Suggested Machine Conditions

### Color: All

Parameters	Test Conditions	Thickness (mm)			
		0.4	0.71	1.5	3.0
Temperature Index (°C)	UL 746B				
Electrical		130	130	130	130
Mechanical w/Impact		75	75	75	75
Mechanical w/o Impact		75	85	85	85
Hot Wire Ignition (Rating)	UL 746A	—	4	3	3
UL94 Flammability Class (Rating)	UL Flame Test	V-2	V-2	V-2	V-2
High Amperage Arc Ignition (Rating)	UL 746A	—	0	0	0
High Volt Track Rate (Rating)	UL 746A	—	—	—	0
D495 Arc Resistance (Rating)	UL 746A	—	—	—	5
UL 746A Track Rate (CTI) (Rating)	UL 746A	—	—	—	0

Parameters	Machine Settings
Melt Temperature, °C	275 to 305
Cylinder Settings, °C	270 to 310
Mold Surface Temperature, °C	15 to 95
Injection Pressure, MPa	55 to 140
Holding Pressure, MPa	55 to 140
Injection Time, sec	< 1 to 2.5
Screw Back Pressure, MPa	0.2 to 1.0
Screw Speed, rpm	50 to 150
Cushion, mm	3.0 to 6.4
Clamp Pressure, tons/cm <sup>2</sup>	0.3 to 0.7

Virgin and regrind up to 50% by weight have the same basic material characteristics.

All numerical flame spread ratings appearing in this data sheet are not intended to reflect hazards presented by this or any other material under actual fire conditions. Each end user should determine whether potential fire hazards are associated with the finished product and whether Vydyne resin is suitable for the particular use. Products made from Vydyne resins should not be exposed to open flames. In the case of direct exposure to open fire, Vydyne resins and products made therefrom can ignite and burn. Always store and use finished products in locations well away from open flames and sources of ignition.

# vydyne 21SPF/21SPG data sheet

Natural and Black general purpose high productivity

## Suggested Guidelines for Molding

1. Your Vydyne nylon resins arrive packaged in moisture-protected containers. If you do not open the original package prior to use, then drying is not necessary. However, if drying is necessary, we recommend that you use a dehumidified air-type dryer (desiccant bed) with a maximum air temperature of 70°C or 1 to 3 hours.

2. The recommended melt temperatures for Vydyne general-purpose resins are 275 to 305°C. Measure the stock in an air shot with a hand-held pyrometer. In addition to the barrel heater bands, screw back pressure and rotation speed add heat to the melt.

3. Maintain mold surface temperatures in a range of 15 to 95°C. We recommend

temperatures on the high end, as the molding cycle allows, to aid in mold filling and to improve the appearance of the molded part.

4. Injection fill rates should be fast. Minimize the use of back pressure 0.2 to 1.0 MPa to yield a consistent melt and/or adequate mixing of color concentrates. Set the screw rotation speed at the minimum required to maintain the molding cycle (50 to 150 rpm).

5. Hold pressure should be set high enough to prevent screw bounce. Hold time should be set until the gate freezes.

6. Maintain your machine's shot-weight-to-barrel-size ratio at 40% to 80% of rated (polystyrene) capacity. A lower shot-to-barrel ratio results in excess residence

time and polymer degradation, which can permanently embrittle the molded part. At a shot-to-barrel ratio above the recommended ratio, molding machinery is often unable to deliver a uniform melt or the desirable fast mold fill.

7. Regrind must be dry when molded. The preferred procedure is to grind and reuse immediately after molding. Regrind-to-virgin ratios of 25% or less have shown no significant property loss when properly molded. However, to ensure adequate performance of your molded part, determine acceptable levels for each application through actual part testing.



### Disclaimer of Warranty and Liability

*NOTICE: Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials, LLC makes no representations or warranties as to the completeness or accuracy thereof.*

*Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials, LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the products to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment, or formulation in conflict with any patent, and Ascend Performance Materials, LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose, or of any other nature are made hereunder with respect to Information or the product to which Information refers.*

