# productinformation

# tesa® 4928

# Double-sided allround filmic tape

tesa® 4928 is a transparent double-sided self-adhesive tape consisting of a PET backing and a modified acrylic adhesive.

tesa® 4928 features especially:

- An excellent balance of good holding power and bonding performance
- Sufficient bonding even to critical surfaces such as diverse foams and rubber materials and at elevated temperatures
- High initial tack to immediately grab to the bonding surface

### Main Application

- Mounting of batteries to battery packs in electronic devices
- Mounting of ABS plastic parts in the automotive industry
- Mounting of decorative profiles and mouldings in the furniture industry

#### Technical Data

	Backing material	PET film		Type of adhesive	tackified acrylic
•	Color	transparent	•	Elongation at break	50 %
•	Total thickness	125 μm	•	Tensile strength	20 N/cm

#### Adhesion to

•	Steel (initial)	9.6 N/cm		Steel (after 14 days)	12.0 N/cm
•	ABS (initial)	8.2 N/cm	•	ABS (after 14 days)	9.7 N/cm
•	Aluminium (initial)	8.1 N/cm	•	Aluminium (after 14 days)	11.1 N/cm
•	PC (initial)	10.3 N/cm	•	PC (after 14 days)	11.5 N/cm
•	PE (initial)	4.9 N/cm	•	PE (after 14 days)	5.4 N/cm
	PET (initial)	7.4 N/cm	•	PET (after 14 days)	8.7 N/cm
	PP (initial)	4.8 N/cm	•	PP (after 14 days)	6.4 N/cm
	PS (initial)	8.8 N/cm	•	PS (after 14 days)	9.4 N/cm
	PVC (initial)	7.2 N/cm		PVC (after 14 days)	10.1 N/cm

# **Properties**

	Temperature resistance short term	200 °C		Resistance to chemicals	• • •
	Temperature resistance long term	100 °C		Softener resistance	•••
	Tack	•••	•	Static shear resistance at 23°C	•••
	Ageing resistance (UV)	•••	•	Static shear resistance at 40°C	•••
•	Humidity resistance	•••			
Ev	aluation across relevant tesa® assortmen	t: ••• very good	•	● good ● ● medium ● low	

For latest information on this product please visit http://l.tesa.com/?ip=04928



# tesa® 4928

Double-sided allround filmic tape

#### Additional Information

Liner variants: PV0 brown glassine paper (71 $\mu$ m; 82g/m²) PV6 red MOPP-film (80 $\mu$ m; 72g/m²)

Page 2 of 2 - as of 06/08/2019 -