multicomp PRO



Application

RoHS Compliant

Provides both commercial and military applications electrical insulation and protects inline components, disconnect terminals and splices with its high strength and excellent resilience. Bundles wires for very flexible light-duty harnesses. Identifies or colour-code wires, cables, terminals and components.

Specifications

Operating Temperature : -55°C to +135°C

Min. Shrink Temperature : 70°C
Min. Full Recovery Temperature : 120°C
Shrink Ratio : 2:1

Colours : Black and Natural

Resistant to common fluids and solvents Approvals: UL224, 125°C 600V VW-1 Meets the AMS- DTL-23053/5 class1&3

Technical Data

Property	Test Method	Typical Data
Tensile Strength	ASTM D 2671	≥10.4MPa
Ultimate Elongation	ASTM D 2671	≥200%
Longitudinal Shrinkage	UL 224	±5%
Heat Aging Tensile Strength Ultimate Elongation	158°C, 168 hour	≥7.3MPa ≥100%
Flammability	UL224 VW-1	Pass
Heat shock (250°C, 4hrs)	ASTM D 2671	No cracking
Cold bend tests (-55°C, 4hrs)	ASTM D 2671	No cracking
Dielectric Strength (kV/mm)	ASTM D 150	≥15kV/mm
Volume Resistivity	ASTM D 876	≥1×10 ¹⁴ Ω·cm
Copper Stability	UL224	Pass
Copper Corrosion	UL224	No corrosion

Product Dimensions

	Si	ze	As Supplied	After Recovery	
Part Number	Inch	mm	Internal Diameter (mm)	Internal Diameter Max. (mm)	Wall Thickness Nom. (mm)
PP001929					
PP001930	1/16	4.5	2 ±0.2	0.95	0.26 +0.4
PP001941	1/16	1.5	∠ ±0.∠	0.85	0.36 ±0.1
PP001942					

Newark.com/multicomp-pro Farnell.com/multicomp-pro sg.element14.com/b/multicomp-pro





	Si	ze	As Supplied	After Recovery	
Part Number	Inch	mm	Internal Diameter (mm)	Internal Diameter Max. (mm)	Wall Thickness Nom. (mm)
PP001931					
PP001932	3/32	2	2.5 ±0.2	1	0.45 ±0.1
PP001943	3/32	2	2.5 ±0.2		0.45 ±0.1
PP001944					
PP001933					
PP001934	1/8	3.5	4 ±0.2	1.8	0.45 ±0.1
PP001945	1/0	3.5	4 ±0.2	1.0	0.45 ±0.1
PP001946]				
PP001935					
PP001936	1/4	6	6.5 ±0.2	3	0.56 ±0.1
PP001947	1/4	0	0.5 ±0.2	3	0.50 ±0.1
PP001948					
PP001937					
PP001938	3/8	10	10.5 ±0.3	5	0.56 ±0.1
PP001949	3/0	10	10.5 ±0.5		0.30 ±0.1
PP001950]				
PP001939					
PP001940	3/4	18	19 ±0.5	9	0.7 ±0.1
PP001951	3/4	10	19 ±0.5	9	0.7 ±0.1
PP001952					

Part Number Table

Description	Part Number
Tubing, Heat Shrink, 2:1, MIL Spec., 1.5mm, Black, 100m	PP001929
Tubing, Heat Shrink, 2:1, MIL Spec., 1.5mm, Black, 10m	PP001930
Tubing, Heat Shrink, 2:1, MIL Spec., 2mm, Black, 100m	PP001931
Tubing, Heat Shrink, 2:1, MIL Spec., 2mm, Black, 10m	PP001932
Tubing, Heat Shrink, 2:1, MIL Spec., 3.5mm, Black, 100m	PP001933
Tubing, Heat Shrink, 2:1, MIL Spec., 3.5mm, Black, 10m	PP001934
Tubing, Heat Shrink, 2:1, MIL Spec., 6mm, Black, 100m	PP001935
Tubing, Heat Shrink, 2:1, MIL Spec., 6mm, Black, 10m	PP001936
Tubing, Heat Shrink, 2:1, MIL Spec., 10mm, Black, 50m	PP001937
Tubing, Heat Shrink, 2:1, MIL Spec., 10mm, Black, 10m	PP001938
Tubing, Heat Shrink, 2:1, MIL Spec., 18mm, Black, 25m	PP001939
Tubing, Heat Shrink, 2:1, MIL Spec., 18mm, Black, 5m	PP001940

Newark.com/multicomp-pro Farnell.com/multicomp-pro sg.element14.com/b/multicomp-pro



Normal Wall Tubing (2X)

Environment Friendly, Flexible, Highly Flame Retardant, Polyolefin, Heat Shrink



Description	Part Number
Tubing, Heat Shrink, 2:1, MIL Spec., 1.5mm, Natural, 100m	PP001941
Tubing, Heat Shrink, 2:1, MIL Spec., 1.5mm, Natural, 10m	PP001942
Tubing, Heat Shrink, 2:1, MIL Spec., 2mm, Natural, 100m	PP001943
Tubing, Heat Shrink, 2:1, MIL Spec., 2mm, Natural, 10m	PP001944
Tubing, Heat Shrink, 2:1, MIL Spec., 3.5mm, Natural, 100m	PP001945
Tubing, Heat Shrink, 2:1, MIL Spec., 3.5mm, Natural, 10m	PP001946
Tubing, Heat Shrink, 2:1, MIL Spec., 6mm, Natural, 100m	PP001947
Tubing, Heat Shrink, 2:1, MIL Spec., 6mm, Natural, 10m	PP001948
Tubing, Heat Shrink, 2:1, MIL Spec., 10mm, Natural, 50m	PP001949
Tubing, Heat Shrink, 2:1, MIL Spec., 10mm, Natural, 10m	PP001950
Tubing, Heat Shrink, 2:1, MIL Spec., 18mm, Natural, 25m	PP001951
Tubing, Heat Shrink, 2:1, MIL Spec., 18mm, Natural, 5m	PP001952

Important Notice: This data sheet and its contents (the "Information") belong to the members of the AVNET group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp Pro is the registered trademark of Premier Farnell Limited 2019.

Newark.com/multicomp-pro Farnell.com/multicomp-pro sg.element14.com/b/multicomp-pro

