

MG Chemicals UK Limited

Version No: A-2.01 Safety data sheet according to REACH Regulation (EC) No 1907/2006, as amended by UK REACH Regulations SI 2019/758

Issue Date: 16/02/2022 Revision Date: 21/06/2022 L.REACH.GB.EN

SECTION 1 Identification of the substance / mixture and of the company / undertaking

1.1. Product Identifier

Product name	400
Synonyms	SDS Code: 400NS-series, 424-NS, 424-NS-10, 425-NS, 425-NS-10, 426-NS, 426-NS-10, 453-NS, 454-NS, 424-NS-10FT, 426-NS-10FT UFI: EUQ0-H07R-Q00Q-CXFK
Other means of identification	Super Wick No Clean

1.2. Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	desoldering braid
Uses advised against	Not Applicable

1.3. Details of the supplier of the safety data sheet

Registered company name MG Chemicals UK Limited M		MG Chemicals (Head office)		
Address Heame House, 23 Bilston Street, Sedgely Dudley DY3 1JA United Kingdom 93		9347 - 193 Street Surrey V4N 4E7 British Columbia Canada		
Telephone	Telephone +(44) 1663 362888 +(1) 800-201-8822			
Fax	Fax Not Available +(1) 800-708-9888			
Website Not Available www.mgchemicals.com		www.mgchemicals.com		
Email	sales@mgchemicals.com	Info@mgchemicals.com		

1.4. Emergency telephone number

Association / Organisation	Verisk 3E (Access code: 335388)
Emergency telephone numbers	+(44) 20 35147487
Other emergency telephone numbers	+(0) 800 680 0425

SECTION 2 Hazards identification

2.1. Classification of the substance or mixture Classified according to GB-CLP Regulation, UK SI 2019/720 and UK SI 2020/1567 Legend: 1. Classified by Chemwatch; 2. Classification drawn from GB-CLP Regulation, UK SI 2019/720 and UK SI 2020/1567

2.2. Label elements				

Hazard pictogram(s)		
Signal word	Danger	
Hazard statement(s)		

H334	May cause allergy or asthma symptoms or breathing difficulties if inhaled.
H317	May cause an allergic skin reaction.

Supplementary statement(s)

Not Applicable

P261 Avoid breathing dust/fumes.			
P280	Wear protective gloves and protective clothing.		
P284	[In case of inadequate ventilation] wear respiratory protection.		
P272	Contaminated work clothing should not be allowed out of the workplace.		

Precautionary statement(s) Response

r reductionary statement(s) response			
P304+P340 IF INHALED: Remove person to fresh air and keep comfortable for breathing.			
P342+P311 If experiencing respiratory symptoms: Call a POISON CENTER/doctor/physician/first aider.			
P302+P352 IF ON SKIN: Wash with plenty of water. P333+P313 If skin irritation or rash occurs: Get medical advice/attention.			
		P362+P364	Take off contaminated clothing and wash it before reuse.

Precautionary statement(s) Storage

Not Applicable

Precautionary statement(s) Disposal

P501 Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

2.3. Other hazards

Rosin: Caution: exposure to this material may cause certain sensitive individuals to develop eczema and/or asthma. Sensitised persons may subsequently show asthmatic symptoms when exposed to atmospheric concentrations well below the OEL. Persons with a history of asthma, allergies or chronic or recurrent respiratory disease should not be employed in any process in which this product is used.

SECTION 3 Composition / information on ingredients

3.1.Substances

See 'Composition on ingredients' in Section 3.2

3.2.Mixtures

1.CAS No 2.EC No 3.Index No 4.REACH No	%[weight]	Name	Classified according to GB-CLP Regulation, UK SI 2019/720 and UK SI 2020/1567	SCL / M-Factor	Nanoform Particle Characteristics
1.7440-50-8 2.231-159-6 3.Not Available 4.Not Available	95	<u>copper</u>	Not Applicable	Not Available	Not Available
1.8050-09-7 2.232-475-7 3.650-015-00-7 4.Not Available	5	rosin- colophony	Sensitisation (Skin) Category 1; H317 ^[2]	Not Available	Not Available
Legend: 1. Classified by Chemwatch; 2. Classification drawn from GB-CLP Regulation, UK SI 2019/720 and UK SI 2020/1567; 3. Classification drawn from G&L * EU IOELVs available; [e] Substance identified as having endocrine disrupting properties		567; 3. Classification drawn			

SECTION 4 First aid measures

4.1. Description of first aid measures

Eye Contact	 If this product comes in contact with the eyes: Immediately hold eyelids apart and flush the eye continuously with running water. Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids. Continue flushing until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Transport to hospital or doctor without delay. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel. DO NOT attempt to remove particles attached to or embedded in eye . Lay victim down, on stretcher if available and pad BOTH eyes, make sure dressing does not press on the injured eye by placing thick pads under dressing, above and below the eye. Seek urgent medical assistance, or transport to hospital. PO NOT attempt to remove particles attached to or embedded in eye. Lay victim down, on stretcher if available and pad BOTH eyes, make sure dressing does not press on the injured eye by placing thick pads under dressing, above and below the eye. Seek urgent medical assistance, or transport to hospital. PO NOT attempt to remove particles attached to or embedded in eye. Lay victim down, on stretcher if available and pad BOTH eyes, make sure dressing does not press on the injured eye by placing thick pads under dressing, above and below the eye. Lay victim down, on stretcher if available and pad BOTH eyes, make sure dressing does not press on the injured eye by placing thick pads under dressing, above and below the eye. Lay victim down, on stretcher if available and pad BOTH eyes, make sure dressing does not press on the injured eye by placing thick pads under dressing, above and below the eye. Seek urgent medical assistance, or transport to hospital.
Skin Contact	 If skin or hair contact occurs: Quickly but gently, wipe material off skin with a dry, clean cloth. Immediately remove all contaminated clothing, including footwear. Wash skin and hair with running water. Continue flushing with water until advised to stop by the Poisons Information Centre. Transport to hospital, or doctor. In case of burns: Immediately apply cold water to burn either by immersion or wrapping with saturated clean cloth. DO NOT remove or cut away clothing over burnt areas. DO NOT pull away clothing which has adhered to the skin as this can cause further injury.

	 DO NOT break bilster or remove solidified material. Quickly cover wound with dressing or clean cloth to help prevent infection and to ease pain. For large burns, sheets, towels or pillow slips are ideal; leave holes for yees, nose and mouth. DO NOT apply ointments, oils, butler, etc. to a burn under any circumstances. Water may be given in small quantities if the person is conscious. Alcohol is not to be given under any circumstances. Reassure. Treat for shock by keeping the person warm and in a lying position. Seek medical aid and advise medical personnel in advance of the cause and extent of the injury and the estimated time of arrival of the patient. For thermal burns: Decontaminate area around burn. Consider the use of cold packs and topical antibiotics. For first-degree burns (affecting top layer of skin) Hold burned skin under coll (not cold) running water or immerse in cool water until pain subsides. Use compresses if running water is not available. Cover with sterile non-adhesive bandage or clean cloth. Oo NOT apply butter or ointmerst; this may cause infection. Give our-the counter pain relievers if pain increases or swelling, redness, fever occur. For second-degree burns (affecting top two layers of skin) Cool the burn by immerse in cold running water for 10-15 minutes. Use compresses if running water is not available. Do NOT apply loce as this may lower body temperature and cause further damage. Do NOT apply cover hosely with sterile, nonstick bandage and secure in place with gauze or tape. To prevent shock: (unless the person has a head, neck, or leg injury, or it would cause discomfort): L ay the person flat. Elevate feet abour 12 inches. Elevate feet abour 12 inches. Elevate feet abour 12 inches. Elevate levation to contendes. Seek
Inhalation	 If fumes or combustion products are inhaled remove from contaminated area. Lay patient down. Keep warm and rested. Prostheses such as false teeth, which may block airway, should be removed, where possible, prior to initiating first aid procedures. Apply artificial respiration if not breathing, preferably with a demand valve resuscitator, bag-valve mask device, or pocket mask as trained. Perform CPR if necessary. Transport to hospital, or doctor, without delay.
Ingestion	 IF SWALLOWED, REFER FOR MEDICAL ATTENTION, WHERE POSSIBLE, WITHOUT DELAY. For advice, contact a Poisons Information Centre or a doctor. Urgent hospital treatment is likely to be needed. In the mean time, qualified first-aid personnel should treat the patient following observation and employing supportive measures as indicated by the patient's condition. If the services of a medical officer or medical doctor are readily available, the patient should be placed in his/her care and a copy of the SDS should be provided. Further action will be the responsibility of the medical specialist. If medical attention is not available on the worksite or surroundings send the patient to a hospital together with a copy of the SDS. Where medical attention is not immediately available or where the patient is more than 15 minutes from a hospital or unless instructed otherwise: INDUCE vomiting with fingers down the back of the throat, ONLY IF CONSCIOUS. Lean patient forward or place on left side (head-down position, if possible) to maintain open airway and prevent aspiration. NOTE: Wear a protective glove when inducing vomiting by mechanical means.

4.2 Most important symptoms and effects, both acute and delayed

See Section 11

4.3. Indication of any immediate medical attention and special treatment needed

- for copper intoxication:
- Unless extensive vomiting has occurred empty the stomach by lavage with water, milk, sodium bicarbonate solution or a 0.1% solution of potassium ferrocyanide (the resulting copper ferrocyanide is insoluble).
- Administer egg white and other demulcents.
- Maintain electrolyte and fluid balances.
- Morphine or meperidine (Demerol) may be necessary for control of pain.
- If symptoms persist or intensify (especially circulatory collapse or cerebral disturbances, try BAL intramuscularly or penicillamine in accordance with the supplier's recommendations.
- Treat shock vigorously with blood transfusions and perhaps vasopressor amines.
- F If intravascular haemolysis becomes evident protect the kidneys by maintaining a diuresis with mannitol and perhaps by alkalinising the urine with sodium bicarbonate.
- It is unlikely that methylene blue would be effective against the occassional methaemoglobinemia and it might exacerbate the subsequent haemolytic episode.
- ▶ Institute measures for impending renal and hepatic failure.
- [GOSSELIN, SMITH & HODGE: Commercial Toxicology of Commercial Products]
- ▶ A role for activated charcoals for emesis is, as yet, unproven.
- In severe poisoning CaNa2EDTA has been proposed.

[ELLENHORN & BARCELOUX: Medical Toxicology]

Copper, magnesium, aluminium, antimony, iron, manganese, nickel, zinc (and their compounds) in welding, brazing, galvanising or smelting operations all give rise to thermally produced particulates of smaller dimension than may be produced if the metals are divided mechanically. Where insufficient ventilation or respiratory protection is available these particulates may produce 'metal fume fever' in workers from an acute or long term exposure.

- Onset occurs in 4-6 hours generally on the evening following exposure. Tolerance develops in workers but may be lost over the weekend. (Monday Morning Fever)
 Pulmonary function tests may indicate reduced lung volumes, small airway obstruction and decreased carbon monoxide diffusing capacity but these abnormalities resolve after
- several months.
- Although mildly elevated urinary levels of heavy metal may occur they do not correlate with clinical effects.
 The general approach to treatment is recognition of the disease, supportive care and prevention of exposure.
- Seriously symptomatic patients should receive chest x-rays, have arterial blood gases determined and be observed for the development of tracheobronchitis and pulmonary edema.

[Ellenhorn and Barceloux: Medical Toxicology]

SECTION 5 Firefighting measures

5.1. Extinguishing media

- Do NOT direct a solid stream of water or foam into burning molten material; this may cause spattering and spread the fire.
- **DO NOT** use halogenated fire extinguishing agents.
- Metal dust fires need to be smothered with sand, inert dry powders.

DO NOT USE WATER, CO2 or FOAM.

- ▶ Use DRY sand, graphite powder, dry sodium chloride based extinguishers, G-1 or Met L-X to smother fire.
- Confining or smothering material is preferable to applying water as chemical reaction may produce flammable and explosive hydrogen gas.
- Chemical reaction with CO2 may produce flammable and explosive methane.
- ▶ If impossible to extinguish, withdraw, protect surroundings and allow fire to burn itself out.

5.2. Special hazards arising from the substrate or mixture

Fire Incompatibility	 Reacts with acids producing flammable / explosive hydrogen (H2) gas Avoid contamination with oxidising agents i.e. nitrates, oxidising acids, chlorine bleaches, pool chlorine etc. as ignition may result
----------------------	---

5.3. Advice for firefighters	
Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. Wear breathing apparatus plus protective gloves. Prevent, by any means available, spillage from entering drains or water courses. Use water delivered as a fine spray to control fire and cool adjacent area. DO NOT approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. If safe to do so, remove containers from path of fire. Equipment should be thoroughly decontaminated after use.
Fire/Explosion Hazard	 bo Not disturb burning dust. Explosion may result if dust is stirred into a cloud, by providing oxygen to a large surface of hot metal. bo Not use water of toma as generation of explosive hydrogen may result. With the exception of the metals that burn in contact with air or water (for example, sodium), masses of combustible metals do not represent unusual fire risks because they have the ability to conduct heat away from hot spots so efficiently that the heat of combustion cannot be maintained - this means that it will require a to of heat to ignite a mass of combustible metal. Generally, metal fire risks exist when sawdust, machine shavings and other metal fines' are present. Metal powders, while generally regarded as non-combustible: May burn when metal is finely divided and energy input is high. May bue ignited by triction, heat, sparks or flame. May be lighted by triction, heat, sparks or flame. May be lighted by triction, heat, sparks or flame. Muse the fight of times any flow mixtures with air. Containers may explode on heating. Dusts or fumes may flow mexplosive mixtures with air. Gases generated in fire may be poisonous, corrosive or irritating. Hor to turning metals may react violently upon contact with other materials, such as oxidising agents and exinguishing agents used on fires involving ordinary combustibles or flammable liquids. Temperatures produced by burning metals may react violently upon contact with other materials, such as oxidising agents and exinguishing agents used on fires involving ordinary combustibles or flammable liquids. Temperatures produced by burning metals can be higher than temperatures generated by burning metalsmaps and exinguishing agents used on fires involving ordinary combustibles or flammable liquids. Temperatures produced by burning metalsmaps and exinguishing age

SECTION 6 Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures See section 8

6.2. Environmental precautions

See section 12

6.3. Methods and material for containment and cleaning up

Minor Spills	 Environmental hazard - contain spillage. Clean up all spills immediately. Avoid breathing dust and contact with skin and eyes. Wear protective clothing, gloves, safety glasses and dust respirator. Use dry clean up procedures and avoid generating dust. Sweep up, shovel up or Vacuum up (consider explosion-proof machines designed to be grounded during storage and use). Place spilled material in clean, dry, sealable, labelled container.
Major Spills	 Environmental hazard - contain spillage. Do not use compressed air to remove metal dusts from floors, beams or equipment Vacuum cleaners, of flame-proof design, should be used to minimise dust accumulation. Use non-sparking handling equipment, tools and natural bristle brushes. Provide grounding and bonding where necessary to prevent accumulation of static charges during metal dust handling and transfer operations Cover and reseal partially empty containers. Do not allow chips, fines or dusts to contact water, particularly in enclosed areas. If molten: Contain the flow using dry sand or salt flux as a dam. All tooling (e.g., shovels or hand tools) and containers which come in contact with molten metal must be preheated or specially coated, rust free and approved for such use. Allow the spill to cool before remelting scrap. Moderate hazard. Control personal contact by wearing protective clothing. Prevent, by any means available, spillage from entering drains or water courses. Recover product wherever possible. IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or other containers for disposal. ALWAYS: Wash area down with large amounts of water and prevent runoff into drains. If contamination of drains or waterways occurs, advise Emergency Services.

6.4. Reference to other sections

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 Handling and storage

7.1. Precautions for safe hand	ling
Safe handling	 Develop work practices and procedures that prevent particulate from coming in contact with worker skin, hair, or personal clothing. If work practices and/or procedures are ineffective in controlling airborne exposure or visual particulate from deposition on skin, hair, or clothing, provide appropriate cleaning/washing facilities. Procedures should be written that clearly communicate the facility's requirements for protective clothing and personal hygiene requirements help keep particulate from being spread to non-production areas or from being taken home by the worker. Never use compressed air to clean work clothing or other surfaces. Fabrication processes may leave a residue of particulate on the surface of parts, products or equipment that could result in employee exposure during subsequent material handling activities. As necessary, clean loose particulate from parts between processing steps. As a standard hygiene practice, wash hands before eating or smoking. To prevent exposure, remove surface scale or oxidation formed on cast or heat treated products in an adequately ventilated process prior to working the surface. Exposure to elements found in the metal, its alloys or recycled materials, may result as a result of inhalation, ingestion, and skin contact, when metting, casting, or otherwise heating or barafact of this material in a maner which generates particulates. Exposure may also occur during repair or maintenance activities on contaminated equipment such as: furnace rebuilding, maintenance or repair of air cleaning equipment, structural renovation, welding, etc. Particulate depositing on hands, gloves, and clothing, can be transferred to the breathing zone and inhaled during normal hand to face motions such as rubbing of the nose or eyes, sneezing, coughing, etc. For molten metals: Motten metal and water can be an explosive combination. The risk i

Page 6 of 18

400NS Super Wick No Clean

	 or other surface contamination resulting from weather exposure, shipment, or storage. Store materials in dry, heated areas with any cracks or cavities pointed downwards. Preheat and dry large objects adequately before charging in to a furnace containing molten metal. This is typically done by the use of a drying oven or homogenising furnace. The dry cycle should bring the metal temperature of the coldest item of the batch to 200 degree C (400 deg F) and then hold at that temperature for 6 hours. The greatest potential for injury caused by molten materials occurs during purging of machinery (moulders, extruders etc.) It is essential that workers in the immediate area of the machinery wear eye and skin protection (such as full face, safety glasses, heat resistant gloves, overalls and safety boots) as protection from thermal burns. Fumes or vapours emitted from hot melled materials, during converting operations, may condense on overhead metal surfaces or exhaust ducts. The condensate may contain substances which are irritating or toxic. Avoid contact of that material with the skin. Wear rubber or other impermeable gloves when cleaning contaminated areas. Avoid process temperatures above decomposition temperatures. Overheating may occur at excessively high cylinder heats, overworking of the melt by wrong screw configuration, reach hazardous concentrations in the converting area. Hot purgings should be collected only as thin flat strands to allow for rapid cooling. Hot purgings should be colled by quenching in water in a well-ventilated area. Organic powders when finely divided over a range of concentrations regardless of particulate size or shape and suspended in air or some other oxidizing medium may form explosive dust-air mixtures and result in a fire or dust explosion (including secondary explosions) Minimise airborne dust and eliminate all ignition sources. Keep away from heat, hot surfaces, sparks, and flame. Establish g
	 Minimise dry sweeping to avoid generation of dust clouds. Vacuum dust-accumulating surfaces and remove to a chemical disposal area. Vacuums with explosion-proof motors should be used. Control sources of static electricity. Dusts or their packages may accumulate static charges, and static discharge can be a source of ignition Solids handling systems must be designed in accordance with applicable standards (e.g. NFPA including 654 and 77) and other national guidance. Do not empty directly into flammable solvents or in the presence of flammable vapors. The operator, the packaging container and all equipment must be grounded with electrical bonding and grounding systems. Plastic bags and plastics cannot be grounded, and antistatic bags do not completely protect against development of static charges.
	 Empty containers may contain residual dust which has the potential to accumulate following settling. Such dusts may explode in the presence of an appropriate ignition source. Do NOT cut, drill, grind or weld such containers. In addition ensure such activity is not performed near full, partially empty or empty containers without appropriate workplace safety authorisation or permit.
Fire and explosion protection	See section 5
Other information	 Store in original containers. Keep containers securely sealed. Store in a cool, dry area protected from environmental extremes. Store away from incompatible materials and foodstuff containers. Protect containers against physical damage and check regularly for leaks. Observe manufacturer's storage and handling recommendations contained within this SDS. For major quantities: Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground wate lakes and streams). Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation wit local authorities.
2. Conditions for safe storag	e, including any incompatibilities
Suitable container	 Bulk bags: Reinforced bags required for dense materials. CARE: Packing of high density product in light weight metal or plastic packages may result in container collapse with product release

Suitable container	 CARE: Packing of high density product in light weight metal or plastic packages may result in container collapse with product release Heavy gauge metal packages / Heavy gauge metal drums
Storage incompatibility	 Inorganic derivative of Group 11 metal. Chips, fines and dust are considerably more reactive in the presence of: Water - slowly generates flammable/explosive hydrogen gas and heat (generation rate is greatly increased with smaller particles (e.g., fines and dusts). Heat - oxidise at a rate dependent upon temperature and particle size. Strong oxidisers - violent reaction with considerable heat generation; an react explosively with nitrates (e.g., ammonium nitrate and fertilizers containing nitrate) when heated or molten. Acids and alkalis - reacts to generate flammable/explosive hydrogen gas; generation rate is greatly increased with smaller particles (e.g., fines and dusts). Halogenated compounds including halogenated fire extinguishing agents, which may react violently with finely divided or molten metals Iron oxide (rust) and other metal oxides (e.g., copper and lead oxides) which may react violent thermit reaction, initiated by a weak ignition source, generating considerable heat Iron powder and water which may react explosively forming hydrogen gas when heated above 800 degrees C (1470 deg F). Finely divided metals (e.g., powders or wire) may have enough surface oxide to produce thermit reactions/explosions The material is described as an electropositive metal. The activity or electromotive series of metals is a listing of the metals in decreasing order of their reactivity with hydrogen-ion sources such as water and acids. In the reaction with a hydrogen-ion source, the metal is oxidised to a metal cation. The more positive the standard reduction potential of the activity series can be related to the standard reduction potential of a metal cation. The more positive the standard reduction potential of the activity series an be related to the standard reduction potential of a metal cation. The more positive the standard reduction potential of the activity series can be related to the standard reductio

Page 7 of 18 400NS Super Wick No Clean

oxygen forming a protective oxide coating. This coating protects the bulk of the metal against further oxidation (the metal is passivated).
Reaction is reduced in the massive form (sheet, rod, or drop), compared with finely divided forms. The less active metals will not burn in air bu
can react exothermically with oxidising acids to form noxious gases.
catalyse polymerisation and other reactions, particularly when finely divided
react with halogenated hydrocarbons (for example, copper dissolves when heated in carbon tetrachloride), sometimes forming explosive compounds.
Elemental metals may react with azo/diazo compounds to form explosive products
Finely divided metal powders develop pyrophoricity when a critical specific surface area is exceeded; this is ascribed to high heat of oxide formation on exposure to air.
Safe handling is possible in relatively low concentrations of oxygen in an inert gas
Several pyrophoric metals, stored in glass bottles have ignited when the container is broken on impact. Storage of these materials moist in metal containers is recommended.
The reaction residues from various metal syntheses (involving vacuum evaporation and co-deposition with a ligand) are often pyrophoric
If the surface of the metal is in contact with both oxygen and water, corrosion can occur. In corrosion, the metal acts as an anode and is oxidis
Many metals may incandesce, react violently, ignite or react explosively upon addition of concentrated nitric acid.
Some electropositive metals do not react with nitric acid because they are passivated.
http://www.wou.edu/las/physci/ch412/activity.htm
WARNING: Avoid or control reaction with peroxides. All transition metal peroxides should be considered as potentially explosive. For example transition metal complexes of alkyl hydroperoxides may decompose explosively.
The pi-complexes formed between chromium(0), vanadium(0) and other transition metals (haloarene-metal complexes) and mono-or poly-fluorobenzene show extreme sensitivity to heat and are explosive.
Avoid reaction with borohydrides or cyanoborohydrides
Many metals may incandesce, react violently, ignite or react explosively upon addition of concentrated nitric acid.

7.3. Specific end use(s)

See section 1.2

SECTION 8 Exposure controls / personal protection

8.1. Control parameters

Ingredient	DNELs Exposure Pattern Worker	PNECs Compartment		
copper	Dermal 137 mg/kg bw/day (Systemic, Chronic) Dermal 273 mg/kg bw/day (Systemic, Acute) Dermal 137 mg/kg bw/day (Systemic, Chronic) * Oral 0.041 mg/kg bw/day (Systemic, Chronic) * Inhalation 1 mg/m ³ (Local, Chronic) * Dermal 273 mg/kg bw/day (Systemic, Acute) * Inhalation 1 mg/m ³ (Local, Acute) *	 3.1 μg/L (Water (Fresh)) 1.2 μg/L (Water - Intermittent release) 0 μg/L (Water (Marine)) 87 mg/kg sediment dw (Sediment (Fresh Water)) 12 mg/kg sediment dw (Sediment (Marine)) 0.7 mg/kg soil dw (Soil) 0.33 mg/L (STP) 0.12 mg/kg food (Oral) 		
rosin-colophony	Dermal 2.131 mg/kg bw/day (Systemic, Chronic) Inhalation 10 mg/m³ (Local, Chronic) Dermal 1.065 mg/kg bw/day (Systemic, Chronic) * Oral 1.065 mg/kg bw/day (Systemic, Chronic) *	0.002 mg/L (Water (Fresh)) 0 mg/L (Water - Intermittent release) 0.016 mg/L (Water (Marine)) 0.007 mg/kg sediment dw (Sediment (Fresh Water)) 0.001 mg/kg sediment dw (Sediment (Marine)) 0 mg/kg soil dw (Soil) 1000 mg/L (STP)		

* Values for General Population

Occupational Exposure Limits (OEL)

INGREDIENT DATA

Source	Ingredient	Material name	TWA	STEL	Peak	Notes
UK Workplace Exposure Limits (WELs)	copper	Copper fume (as Cu)	0.2 mg/m3	Not Available	Not Available	Not Available
UK Workplace Exposure Limits (WELs)	rosin-colophony	Rosin-based solder flux fume	0.05 mg/m3	0.15 mg/m3	Not Available	Sen

Emergency Limits

Ingredient	TEEL-1	TEEL-2		TEEL-3
copper	3 mg/m3	33 mg/m3		200 mg/m3
rosin-colophony	72 mg/m3	790 mg/m3		1,500 mg/m3
Ingredient	Original IDLH		Revised IDLH	
copper	100 mg/m3		Not Available	
rosin-colophony	Not Available		Not Available	

MATERIAL DATA

IFRA Prohibited Fragrance Substance The International Fragrance Association (IFRA) Standards form the basis for the globally accepted and recognized risk management system for the safe use of fragrance ingredients and are part of the IFRA Code of Practice. This is the self-regulating system of the industry, based on risk assessments carried out by an independent Expert Panel

8.2. Exposure controls

8.2. Exposure controls						
8.2.1. Appropriate engineering controls	For molten materials: Provide mechanical ventilation; in general such ventilation should be provided at comstations where the material is heated. Local exhaust ventilation should be used over molten material. Keep dry!! Processing temperatures may be well above boiling point of water, so wet or damp munvented equipment. Metal dusts must be collected at the source of generation as they are potentially expl Avoid ignition sources. Good housekeeping practices must be maintained. Dust accumulation on the floor, ledges and beams can present a risk of ignition, Do not use compressed air to remove settled materials from floors, beams or eq Vacuum cleaners, of flame-proof design, should be used to minimise dust accum Use non-sparking handling equipment, tools and natural bristle brushes. Cover a bonding where necessary to prevent accumulation of static charges during metal Do not allow chips, fines or dusts to contact water, particularly in enclosed areas Metal spraying and blasting should, where possible, be conducted in separate ro form of metal oxides, to potentially reactive finely divided metals such as aluminin Work-shops designed for metal spraying should possess smooth walls and a mir accumulation is possible. Wet scrubbers are preferable to dry dust collectors. Bag of filter-type collectors should be side do utside the workrooms and be fitted 4 Cyclones should be protected against entry of moisture as reactive metal dusts a wetted states. Local ventilation and vacuum systems must be designed to handle explosive dust used, unless specifically approved for use with flammable/ explosive dusts. Air contaminants generated in the workplace		r and in the vicinity of machinery involved in handling the material may cause a serious steam explosion if used in closive. a fame propagation and secondary explosions. A puipment mulation. and reseal partially empty containers. Provide grounding and al dust handling and transfer operations. s. cooms. This minimises the risk of supplying oxygen, in the inum, zinc, magnesium or titanium. inimum of obstructions, such as ledges, on which dust with explosion relief doors. are capable of spontaneous combustion in humid or partially y at the fume source, away from the worker, of 0.5 metre/sec. ists. Dry vacuum and electrostatic precipitators must not be ich, in turn, determine the 'capture velocities' of fresh Air Speed: 0.5-1.0 m/s (100-200 f/min.) are troionly mg of a simple extraction pipe. Velocity generally decreases a is speed at the extraction point should be adjusted,			
8.2.2. Personal protection						
Eye and face protection	 Safety glasses with side shields. Chemical goggles. Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59], [AS/NZS 1336 or national equivalent] 					
Skin protection	See Hand protection below					
Hands/feet protection	The selection of suitable gloves does not only depend on the manufacturer. Where the chemical is a preparation of sever and has therefore to be checked prior to the application. The exact break through time for substances has to be obter making a final choice. Personal hygiene is a key element of effective hand care. Of washed and dried thoroughly. Application of a non-perfume Suitability and durability of glove type is dependent on usage frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe EN When prolonged or frequently repeated contact may occu	ral substances, the resist ained from the manufactu Gloves must only be worr ad moisturiser is recomme ge. Important factors in th a 374, US F739, AS/NZS	ance of the g urer of the pro- n on clean ha ended. ue selection c 2161.1 or na	glove material can otective gloves and inds. After using gl of gloves include: ational equivalent).	not be calculated in advance d has to be observed when oves, hands should be	

Pag	е	9	of	1	8

• When only brief contact is expected, a glove with a protection class of 3 or higher (preakthrough time greater than 60 minutes according to EN 374, ASNC2 2016; 101 or analonal equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. • Excellent when breakthrough time > 400 min • Good when breakthrough time > 400 min • For yenes Toglications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasized that glove thickness is not necessarily a good predictor glove resistance to a specific chemical, as the permeation efficiency of the glove multi-alt threading, the task regulations of glove thickness is not necessarily a good predictor glove resistance to a specific chemical, as the permeation efficiency of the glove multi-alt threading, the solution should also be based on consideration of the task regulations, gloves also vary dipending on the glove mundrature, the glove multi-alt. Therefore, glove selection should also be based on consideration of the task regulation and socurit to ensure selection of the mesia, apportate glove for the task. To example: • Thinter gloves (Glove 10.01 mm of tes) may be required where a here is a mechanical tasks. For example: • Thicker gloves (glove signed where there is a mochanical task. Therefore, glove set or signed social tasks. To example: • Thicker gloves (Glove 10.01 mm of tes) may be required where there is a acchanical (seek-there were there is a barsion or puncture potential • Thicker gloves (gloves 10, cleanter gloves		minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
Production Second glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 40 min Good when breakthrough time > 40 min Four when gloves material degradas For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasized that glove thickness is not necessarily a good predictor of glove model. Therefore, the manufacturers technical data should always be taken into account cent composition of the most appropriate glove for the task. Glove thickness may also vay depending on the glove manufacturer, the glove model. Therefore, the amufacturers technical data should always be taken into account census esection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required where the is a mechanical data should always be taken more account census esection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required where the is a mechanical data should be well be explained. Outy the bioty of the glove with a thickness typically greater than disperse of needule. Thinker gloves should normally be trause there is a mechanical data with is needule. However, these gloves are only takes to use applications, then dependent on the sate regulared and the mostake thata the reglowes and there is a mechanical data with a reg		
Image: Second		374, AS/NZS 2161.10.1 or national equivalent) is recommended.
As defined in ASTM F-739-96 in any application, gloves are rated as: - Excellent when breakthrough time > 20 min - Good when breakthrough time > 20 min - Fair when glove material degrades For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the gloves manufacturer, the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinker gloves (down to 1.01 mm or loss) may be required where a high degree of manual detextry is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves gloves gloves or gloves with Leather facing Biover gloves are not recommended. - Protective gloves are not recommended when handing hot objects, materials - Note repeaterial - Thicker gloves are not recommended when handing hot objects, materials - Thicker gloves are not recommended when handing hot objects, materials - Nobjective gloves are not recommended		• Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.
Image: Second		Contaminated gloves should be replaced.
• Good when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Por when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the east composition of the glove material. Therefore, glove selection should also be based on consideration of the task towned glove threakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove of the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinker gloves (but no 1.01 mm or loss) may be required where a high degree of manual detexter) is needed. Theoremer, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (but no 1.01 mm or loss) more may be required where hands a chanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed motistriker is recommended. • Noteber gloves are not recommended when handling hot objects, materials For protection gl		As defined in ASTM F-739-96 in any application, gloves are rated as:
 Fair when breakthrough time < 20 min Poor when glove material degrades For ownen glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness in a tot necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves or varying thickness may also the object of specific tasks. For example:		
Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required three the sis a mechanical (as well as a chemical) risk i.e. where there is a breastion or puncture gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves eq. Leather gloves or gloves with Leather facing When handling to materials wear heat resistant, albow length gloves. Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive partices are not present. Polychirorpene. hit in obber. buyly rubber. buyly rubber. fluorocaucthouc: buyly rubber. fluorocaucthouc: buyly rubber. fluorocaucthouc: buyly rubber. fluoro		
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may allow output the glove manufacture; the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where small be equired for specific tasks. For example: Thinner gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves equired when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particitates is an on treesent. Polychioroprene. Nother breaktion. Polychioroprene. Nother breaktion. Body induber. Huite rubber. Huite rubber. Huite rubber. Huite rubber. Huite rubber. Huite rubber.<th></th><th></th>		
It should be emphasised that glove thickness is not necessarily agod predictor of glove resistance to a specific chemical, as the permeation of the fask requirements and howledge of breakthrough times. Glove thickness may also vary depending on the glove mantarial. Therefore, glove selection should also be based on consideration of the task requirements and howledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove mantarial. Therefore, glove selections should also be based on consideration of the task requirements and howledge of breakthrough times. Glove thickness may bas vary depending on the glove manufacturer, the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinker gloves (down to 0.1 mor or less) may be required where a high depend denterity in seed gloves are only tikely to give short duration protection and would normally be just for single use applications; then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical). Therefore, gloves set, beatter gloves or gloves with Leather facing Protective gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials Protective gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials Protective gloves are not recommended and the durations are suitable as glove materinals for protection against undissolved, dry		
efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the glove way be pending on the glove manufacture; the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, glove sof varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) fisk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves equive the materials were near tesistant, elbow length gloves. Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychiloroprene. butyl rubber. floroceautchouc. polychiloroprene. butyl rubber. floroceautchouc. polychiloroprene. butyl rubber. butyl cubber. bu		
Glove thickness may also vary depending on the glove matching the glove and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves eg. Leather gloves or gloves with Leather facing When handling hot materials wear heat resistant, elbow length gloves. Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychioroprene. hittle nubber. buyl rubber. buyl		efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on
data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mor less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves eg. Leather gloves or gloves with Leather facing When handling hot materials wear heat resistant, elbow length gloves. Rubber gloves are not recommended when handling hot olgets, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. initife nubber. buily rubber. fluorecoutchouc. polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid splils entering boots. Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CAUTON: Vapours may be irritating. Voveralls. PivC agroon.		
- Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves are not recommended. When handling hot materials wear heat resistant, elbow length gloves. Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. buly inbber: fluorocaoutchouc. buly inbber: fluorocaoutchouc. buly indber: fluorocaoutchouc. buly induber: fluorocaoutchouc. buly induber: fluorocaoutchouc. buly induber: fluorocaoutchouc. buly induber: fluorocaoutchouc. buly induber: buly induce as molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. CAUTION: 'apours may be inflating. boveralls. p.V.C apron. Barrier cream. Skin cleansin		
likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves eq. Leather gloves or gloves with Leather facing When handling hot materials wear heat resistant, elbow length gloves. Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. Polychloroprene. hittile rubber. budy rubber. Isoda moder and/or degradation constantly. Body protection See Other protection below When handling hot or molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CALTION: Vapours may be irritating. When handling hot or molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CALTION: Vapours may be irritating. Overalls. Polycaling. budy irriter cream. Skin cleansing cream. Skin cleansing cream.		Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:
• Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. • Protective gloves eg. Leather gloves or gloves with Leather facing • When handling hot materials wear heat resistant, elbow length gloves. • Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • nitrile rubber. • buly rubber. • fluorocaoutchouc. • polychloroprene. • nitrile rubber. • fluorocaoutchouc. • polychloroprene. • nitrile rubber. • buly rubber. • buly rubber. • buly rubber. • thur rober protection below See Other protection below • Vhen handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquids, wear trousers or overal		• Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only
puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves eg. Leather gloves or gloves with Leather facing When handling hot materials wear heat resistant, elbow length gloves. Rubber gloves are not present. Polychloroprene. • hitrile rubber. • hitrile rubber. • buyly rubber. • hitrile rubber. • buyly rubber. • buyly rubber. • fluorcocoutchouc. • polychloroprene. • polychloroprene. • initile rubber. • buyly rubber. • Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalis. • PV.C apron. • Barrier cream. • Skin cleansing cream.		likely to give short duration protection and would normally be just for single use applications, then disposed of.
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Protective gloves eg. Leather gloves or gloves with Leather facing When handling hot materials wear heat resistant, elbow length gloves. Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. Polychloroprene. • nitrile rubber. • buly rubber. • stimulation of or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots.		
moisturiser is recommended. Protective gloves eg. Leather gloves or gloves with Leather facing When handling hot materials wear heat resistant, elbow length gloves. Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. Polychloroprene. • Dityloroprene. • hitrile rubber. • butyl rubber. • butyl rubber. • Intrile rubber. • butyl rubber. • Body protection See Other protection below Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Lauring harder as molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Yapours may be irritating. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
 Protective gloves eg. Leather gloves or gloves with Leather facing When handling hot materials wear hear tesistant, elbow length gloves. Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. hittir euber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. Gloves shuld be examined for wear and/ or degradation constantly. Body protection See Other protection below When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CAUTION: Vapours may be irritating. Overalls. P.V.C apron. Barrier cream. Skin cleansing cream.		
• When handling hot materials wear heat resistant, elbow length gloves. • Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • initrile rubber. • butyl rubber. • fluorocaoutchouc. • polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
 Rubber gloves are not recommended when handling hot objects, materials Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CAUTION: Vapours may be irritating. Overalls. P.V.C apron. Barrier cream. Skin cleansing cream. 		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. hitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CAUTION: Vapours may be irritating. Overalls. P.V.C apron. Barrier cream. Skin cleansing cream. 		
particles are not present. > polychloroprene. > nitrile rubber. > butyl rubber. > butyl rubber. > polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
• polychloroprene. • nitrile rubber. • butyl rubber. • butyl rubber. • fluorocaoutchouc. • polychloroprene. • Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
• nitrile rubber. • butyl rubber. • butyl rubber. • polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalls. • PV.C apron. Barrier cream. • Skin cleansing cream.		
• butyl rubber. • fluorocaoutchouc. • polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalls. • Overalls. • PV-C apron. • Barrier cream. • Skin cleansing cream.		
• fluorocaoutchouc. • polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalls. • PV.C apron. • Barrier cream. • Skin cleansing cream.		
• polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. • Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. • CAUTION: Vapours may be irritating. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
Other protection When handling hot or molten liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CAUTION: Vapours may be irritating. Overalls. P.V.C apron. Barrier cream. Skin cleansing cream. 		
Other protection Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CAUTION: Vapours may be irritating. Overalls. P.V.C apron. Barrier cream. Skin cleansing cream. 	Body protection	See Other protection below
 Usually handled as molten liquid which requires worker thermal protection and increases hazard of vapour exposure. CAUTION: Vapours may be irritating. Overalls. P.V.C apron. Barrier cream. Skin cleansing cream. 		Numer handling hat as malter liquide, upper traugers as querelle outside of heads to querid apille entering heads
Other protection CAUTION: Vapours may be irritating. Overalls. P.V.C apron. Barrier cream. Skin cleansing cream. 		
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 		
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 		
 Barrier cream. Skin cleansing cream. 	Other protection	
Skin cleansing cream.		
		• Eye wash unit.
		-,

Respiratory protection

Type A-P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator	
up to 10 x ES	A P1 Air-line*	-	A PAPR-P1 -	
up to 50 x ES	Air-line**	A P2	A PAPR-P2	
up to 100 x ES	-	A P3	-	
		Air-line*	-	
100+ x ES	-	Air-line**	A PAPR-P3	

* - Negative pressure demand ** - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.
 Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

Where significant concentrations of the material are likely to enter the breathing zone, a Class P3 respirator may be required.

Class P3 particulate filters are used for protection against highly toxic or highly irritant particulates.

Filtration rate: Filters at least 99.95% of airborne particles

Suitable for:

· Relatively small particles generated by mechanical processes eg. grinding, cutting, sanding, drilling, sawing.

· Sub-micron thermally generated particles e.g. welding fumes, fertilizer and bushfire smoke.

· Biologically active airborne particles under specified infection control applications e.g. viruses, bacteria, COVID-19, SARS

 \cdot Highly toxic particles e.g. Organophosphate Insecticides, Radionuclides, Asbestos

Note: P3 Rating can only be achieved when used with a Full Face Respirator or Powered Air-Purifying Respirator (PAPR). If used with any other respirator, it will only provide filtration protection up to a P2 rating.

See section 12

SECTION 9 Physical and chemical properties

9.1. Information on basic physical and chemical properties

Appearance	copper		
Physical state	Solid	Relative density (Water = 1)	8.8
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature	Not Available
Melting point / freezing point (°C)	1057	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available BuAC = 1	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Applicable	pH as a solution (Not Available%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available
Nanoform Solubility	Not Available	Nanoform Particle Characteristics	Not Available
Particle Size	Not Available		

9.2. Other information

Not Available

SECTION 10 Stability and reactivity

10.1.Reactivity	See section 7.2
10.2. Chemical stability	 Unstable in the presence of incompatible materials. Product is considered stable. Hazardous polymerisation will not occur.
10.3. Possibility of hazardous reactions	See section 7.2
10.4. Conditions to avoid	See section 7.2
10.5. Incompatible materials	See section 7.2
10.6. Hazardous decomposition products	See section 5.3

SECTION 11 Toxicological information

11.1. Information on toxicological effects

Inhaled	Evidence shows, or practical experience predicts, that the material produces irritation of the respiratory system, in a substantial number of individuals, following inhalation. In contrast to most organs, the lung is able to respond to a chemical insult by first removing or neutralising the irritant and then repairing the damage. The repair process, which initially evolved to protect mammalian lungs from foreign matter and antigens, may however, produce further lung damage resulting in the impairment of gas exchange, the primary function of the lungs. Respiratory tract irritation often results in an inflammatory response involving the recruitment and activation of many cell types, mainly derived from the vascular system.
	Strong evidence exists that exposure to the material may produce serious irreversible damage (other than carcinogenesis, mutagenesis and teratogenesis) following a single exposure by inhalation. Inhalation of dusts, generated by the material during the course of normal handling, may produce severe damage to the health of the individual. Relatively small amounts absorbed from the lungs may prove fatal.

	Metals which form part of massive metals and their alloys, are 'locked' into a metal lattice; as a result they are not readily bioavailable following inhalation. Mechanical processing of massive metals (e.g. cutting, grinding) may cause irritation of the upper respiratory tract. Additional health effects from elevated temperature processing (e.g., welding) can cause metal fume fever (nausea, fever, chills, shortness of breath and malaise), reduced ability of the blood to carry oxygen (methaemoglobin) and the accumulation of fluid in the lungs (pulmonary oedema). Inhalation hazard is increased at higher temperatures. Inhalation of freshly formed metal oxide particles sized below 1.5 microns and generally between 0.02 to 0.05 microns may result in 'metal fume fever'. Symptoms may be delayed for up to 12 hours and begin with the sudden onset of thirst, and a sweet, metallic or foul taste in the mouth. Other symptoms include upper respiratory tract irritation accompanied by coughing and a dryness of the mucous membranes, lassitude and a generalised feeling of malaise. Mild to severe headache, nausea, occasional vomiting, fever or chills, exaggerated mental activity, profuse sweating, diarrhoea, excessive urination and prostration may also occur. Tolerance to the fumes develops rapidly, but is quickly lost. All symptoms usually subside within 24-36 hours following removal from exposure. Inhalation of fume may aggravate a pre-existing respiratory condition such as asthma, bronchitis, emphysema Copper poisoning following exposure to copper dusts and fume may result in headache, cold sweat and weak pulse. Capillary, kidney, liver and brain damage are the longer term manifestations of such poisoning. Inhalation of freshly formed metal oxide particles sized below 1.5 microns and generaliy between 0.02 to 0.05 microns may result in 'metal fume fever'. Symptoms may be delayed for up to 12 hours and begin with the sudden onset of thirst, and a sweet, metallic or foul taste in the mouth. Other symptoms include upper re
Ingestion	Severely toxic effects may result from the accidental ingestion of the material; animal experiments indicate that ingestion of less than 5 gram may be fatal or may produce serious damage to the health of the individual. Strong evidence exists that exposure to the material may produce serious irreversible damage (other than carcinogenesis, mutagenesis and teratogenesis) following a single exposure by swallowing. Metals which form part of massive metals and their alloys, are 'locked' into a metal lattice; as a result they are not readily bioavailable following ingestion. Secondary processes (e.g. change in pH or intervention by gastrointestinal microorganisms) may allow certain substances to be released in low concentrations. Not normally a hazard due to the physical form of product. The material is a physical irritant to the gastro-intestinal tract Numerous cases of a single oral exposure to high levels of copper have been reported. Consumption of copper-contaminated drinking water has been associated with mainly gastrointestinal symptoms including nausea, abdominal pain, vomiting and diarrhoea. A metallic taste, nausea, vomiting and epigastrib touring often occur after ingestion of copper and its derivatives. The vomitus is usually greenblue and discolours contaminated skin. Acute poisonings from the ingestion of copper and its derivatives. The vomitions and to many the delayed if food is present in the stomach. Should vomiting not occur, or is delayed, gradual absorption from the bowel may result in systemic poisoning with death, possibly, following within several days. Apparent recovery may be followed by lethal relapse. Systemic effects of copper resemble other heavy metal poisonings and produce wide-spread capillary damage, kidney and liver damage and central nervous system excitain followed by depression. Haemolytic anaemia (a result of red-blocd cell damage) has been described in acute human poisoning. [GOSSELIN, SMITH HODGE: Clinical Toxicology of Commercial Products.] Other symptoms of copper poisoning
Skín Contact	Strong evidence exists that exposure to the material may produce serious irreversible damage (other than carcinogenesis, mutagenesis and teratogenesis) following a single exposure by skin contact. Skin contact is not thought to produce harmful health effects (as classified under EC Directives using animal models). Systemic harm, however, has been identified following exposure of animals by at least one other route and the material may still produce health damage following entry through wounds, lesions or abrasions. Good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting. Particles and foreign bodies produced by high speed processes may be penetrate the skin. Even after the wound heals persons with retained foreign bodies may experiencing sharp pain with movement or pressure over the site. Discolouration or a visible mass under the epidermis may be obvious. Numbness or tingling ('pins and needles'), with decreased sensation, may be the result of a foreign body pressing against nerves. Persons with diabetes or a history of vascular problems have a higher potential for acquiring an infection Irritation and skin reactions are possible with sensitive skin Exposure to copper, by skin, has come from its use in pigments, ointments, ornaments, jewellery, dental amalgams and IUDs and as an antifungal agent and an algicide. Although copper algicides are used in the treatment of water in swimming pools and reservoirs, there are no reports of toxicity from these applications. Reports of allergic contact dermatitis following contact with copper and its salts have appeared in the literature, however the exposure concentrations leading to any effect have been poorty characterised. In one study, patch testing of 1190 eczema patients found that only 13 (1.1%) cross-reacted with 2% copper sulfate in petrolatum. The investigators warned, however, that the possibility of contamination with nickel (an established contact allergen) might have been the cause of the
Eye	Evidence exists, or practical experience predicts, that the material may cause eye irritation in a substantial number of individuals and/or may produce significant ocular lesions which are present twenty-four hours or more after instillation into the eye(s) of experimental animals. Repeated or prolonged eye contact may cause inflammation characterised by temporary redness (similar to windburn) of the conjunctiva (conjunctivitis); temporary impairment of vision and/or other transient eye damage/ulceration may occur. Contact with the eye, by metal dusts, may produce mechanical abrasion or scratches on the cornea - these injuries usually are minor. However foreign body penetration of the eyeball may produce infection or result in permanent visual damage. High-speed machines (such as drills and saws) can produce white-hot particles of metal that resemble sparks. Any of these white-hot particles can enter the unprotected eye and become embedded deep within it. Foreign bodies that penetrate the inside of the eye can cause infection

Page 12 of 18

400NS Super Wick No Clean

	(endophthalmitis). During the first hours after injury, symptoms of intraocular foreign bodies may be similar to those of corneal abrasions and foreign bodies. However, people with intraocular foreign bodies may also have a noticeable loss of vision. Fluid may leak from the eye, but if the foreign body is small, the leak may be so small that the person is not aware of it. Also, pain may increase after the first several hours Corneal abrasions caused by particles and foreign bodies usually cause pain, tearing, and a feeling that there is something in the eye. They may also cause redness (due to inflamed blood vessels on the surface of the eye) or, occasionally, swelling of the eye and eyelid. Vision may become blurred. Light may be a source of irritation or may cause the muscle that constricts the pupil to undergo a painful spasm. Injuries that penetrate the eye may cause similar symptoms. If a foreign object penetrates the inside of the eye, fluid may leak out. Copper salts, in contact with the eye, may produce conjunctivitis or even ulceration and turbidity of the cornea.
Chronic	 Repeated or long-term occupational exposure is likely to produce cumulative health effects involving organs or biochemical systems. Long-term exposure to respiratory irritants may result in disease of the ainways involving difficult breathing and related systemic problems. There is sufficient evidence to provide a strong presumption that human exposure to the material may produce heritable genetic damage. There is sufficient evidence to provide a strong presumption that human exposure to the material may result in the development of heritable genetic damage, generally on the basis of appropriate animal studies, other relevant information Metallic dusts generated by the industrial process give rise to a number of potential health problems. The larger particles, above 5 micron, are nose and throat irritants. Smaller particle, may give rise to further serious health consequences. Metals are widely distributed in the environment and are not biodegradable. Biologically, mary metals are essential to living systems and are involved in a variety of cellular, physiological, and structural functions. They often are cofactors of enzymes, and play a role in transcriptional control, muscle contraction, nerve transmission, blood clotting, and oxygen transport and delivery. Although all metals are potentially toxic at some level, some are highly toxic at relatively low levels. Moreover, in some cases the same metal can be essential at low levels and toxic at higher levels, or may be toxic via one route of entry but not another. Toxic effects of some metals are. Furthermore, the half life of a given metal varies in different tissues. Lead has a half life of 14 days in soft issues and 20 years in bone. In considering how to evaluate the toxicity of metals of potential concentrates, and thus the observed toxic effects; Metal-metal interactivity of one metal based on the adverse effects of another; in trying to evaluate the toxicity of one particular sorti

400NS Super Wick No Clean			IRRITATION	
400NS Super Wick NO Clean	Not Available		Not Available	
	ΤΟΧΙCΙΤΥ	IRRITA	TION	
	dermal (rat) LD50: >2000 mg/kg ^[1]	Eye: no	adverse effect observed (not irritating) ^[1]	
copper	Inhalation(Rat) LC50; 0.733 mg/l4h ^[1] Skin: no		o adverse effect observed (not irritating) ^[1]	
	Oral (Mouse) LD50; 0.7 mg/kg ^[2]			
	TOXICITY	IRRITATION		
rosin-colophony	dermal (rat) LD50: >2000 mg/kg ^[1]	Eye: no ac	dverse effect observed (not irritating) ^[1]	
	Oral (Rat) LD50; >1000 mg/kg ^[1]	Skin: no a	dverse effect observed (not irritating) ^[1]	
Legend:	1. Value obtained from Europe ECHA Registered Subst specified data extracted from RTECS - Register of Toxic		xicity 2.* Value obtained from manufacturer's SDS. Unless otherwise cal Substances	

400NS Super Wick No Clean	Asthma-like symptoms may continue for months or even years after exposure to the material ceases. This may be due to a non-allergenic condition known as reactive airways dysfunction syndrome (RADS) which can occur following exposure to high levels of highly irritating compound. Key criteria for the diagnosis of RADS include the absence of preceding respiratory disease, in a non-atopic individual, with abrupt onset of persistent asthma-like symptoms within minutes to hours of a documented exposure to the irritant. A reversible airflow pattern, on spirometry, with the presence of moderate to severe bronchial hyperreactivity on methacholine challenge testing and the lack of minimal lymphocytic inflammation, without eosinophilia, have also been included in the criteria for diagnosis of RADS. RADS (or asthma) following an irritating inhalation is an infrequent disorder with rates related to the concentration of and duration of exposure to the irritating substance. Industrial bronchitis, on the other hand, is a disorder that occurs as result of exposure due to high concentrations of irritating substance (often particulate in nature) and is completely reversible after exposure ceases. The disorder is characterised by dyspnea, cough and mucus production.
COPPER	 WARNING: Inhalation of high concentrations of copper fume may cause 'metal fume fever', an acute industrial disease of short duration. Symptoms are tiredness, influenza like respiratory tract irritation with fever. for copper and its compounds (typically copper chloride): Acute toxicity: There are no reliable acute oral toxicity results available. In an acute dermal toxicity study (OECD TG 402), one group of 5 male rats and 5 groups of 5 female rats received doses of 1000, 1500 and 2000 mg/kg bw via dermal application for 24 hours. The LD50 values of copper monochloride were 2,000 mg/kg bw or greater for male (no deaths observed) and 1,224 mg/kg bw for female. Four females died at both 1500 and 2000 mg/kg bw, and one at 1,000 mg/kg bw. Symptom of the hardness of skin, an exudation of hardness site, the formation of scar and

Т

	I					
	reddish changes were observed on application sites in a black urine was observed in females at 2,000, 1,500 and mortality and clinical signs.					
	No reliable skin/eye irritation studies were available. The acute dermal study with copper monochloride suggests that it has a potential to cause skin irritation.					
	Repeat dose toxicity: In repeated dose toxicity study pr Sprague-Dawley rats for 30 days to males and for 39 - 5 value was 5 and 1.3 mg/kg bw/day for male and female was observed in female rats in the high dose group. Ery frequency of squamous cell hyperplasia of the forestoma groups, and was statistically significant in males at dose effects are considered to be local, non-systemic effect on Genotoxicity : An in vitro genotoxicity study with copper Salmonella typhimurium strains (TA 98, TA 100, TA 1533 vitro test for chromosome aberration in Chinese hamstei aberrations at the concentration of 50, 70 and 100 ug/ml of structural aberrations were observed at 50 and 70 ug in vivo mammalian erythrocyte micronucleus assay, all a PCE/(PCE+NCE) ratios and MNPCE frequencies comper vivo mutagen. Carcinogenicity: there was insufficient information to er Reproductive and developmental toxicity: In the combine test (OECD TG 422), copper monochloride was given or at concentrations of 0, 1.3, 5.0, 20, and 80 mg/kg bw/day parental animals. No treatment-related effects were obser developmental toxicity the NOAEL was 20 mg/kg bw/day the highest dose tested (80 mg/kg bw/day).	51 days to females at concentrations rats, respectively. No deaths were ob thropoietic toxicity (anaemia) was se ach was increased in a dose-depend is of =20 mg/kg bw/day and in female n the forestomach which result from monochloride showed negative results 5, and TA 1537) with and without S9 r lung (CHL) cells showed that coppe L without S9 mix. In the presence of mL and significant increases of num animals dosed (15 - 60 mg/kg bw) with ared to those of the negative control a valuate the carcinogenic activity of cc ed repeated dose toxicity study with t rally (gavage) to Sprague-Dawley rat y. The NOAEL of copper monochloric erved on the reproductive organs and	of 0, 1.3, 5.0, 20, and 80 mg/kg bw/day. The NOAEL served in male rats. One treatment-related death en in both sexes at the 80 mg/kg bw/day. The ent manner in male and female rats at all treatment is at doses of =5 mg/kg bw/day doses. The observed oral (gavage) administration of copper monochloride. Its in a bacterial reverse mutation test with mix at concentrations of up to 1,000 ug/plate. An in er monochloride induced structural and numerical the metabolic activation system, significant increases erical aberrations were observed at 70 ug/mL. In an h copper monochloride exhibited similar animals. Therefore copper monochloride is not an in opper monochloride. he reproduction/developmental toxicity screening s for 30 days to males and for 39-51 days to females de for fertility toxicity was 80 mg/kg bw/day for the d the fertility parameters assessed. For			
ROSIN-COLOPHONY	The following information refers to contact allergens as a Contact allergies quickly manifest themselves as contact eczema involves a cell-mediated (T lymphocytes) immur involve antibody-mediated immune reactions. The signift distribution of the substance and the opportunities for cord distributed can be a more important allergen than one we clinical point of view, substances are noteworthy if they provide the substances are noteworthy if they provide the substances are noteworthy if they they different rosin types are used interchangeably and are conterned to the substances are noteworthy if they they as a major allergen of colophony . A variety of other oxic colophony) were isolated and identified, some of which we that patch testing with the hydroperoxide detects about the converted into a highly reactive hydroperoxide by contact Unmodified colophony is a complex mixture of diterpeno cause sensitization, a chemical must bind to macromole Hydroperoxy resin acids are dermal sensitizers, with hat predicted, with a Schiff base (or imine) linkage formed by the plasma membrane, a non-aqueous environment app membrane proteins, through covalent binding. Such bind haptenation mechanism may be involved in allergic cont aerosols. For a better understanding of the mechanisms of contact products were studied. The 13,14(alpha)-epoxide and th were shown in experimental sensitization studies to be contact products were studied. The 13,14(alpha)-epoxide and th were shown in experimental sensitization studies to be and also between the epoxides and the previously identif form an epoxide which then reacts with skin protein to green explained by the formation of similar alkoxy radicals from the resin acid oxidation products indicate that 15-HPA m antigens. The presence in rosin of the epoxides of abieti epoxides elicited reactions in rosin-allergic individuals. T allergen.	At eczema, more rarely as urticaria or ne reaction of the delayed type. Othe icance of the contact allergen is not a pontact with it are equally important. A tith stronger sensitising potential with produce an allergic test reaction in m often chemically modified Colophony acid. Abietic acid has been describe en investigations regarding the allergy enic but rapidly autooxidises forming dation products from abietic acid and were shown to be sensitizers in guine 50% of the patients with contact aller t with air. bid acids (i.e., resin acids, ca. 90%), c cueles (proteins) in the skin (producin ptenation thought to occur via radical etween the C-7 of the resin and the f parently conducive to conjugation of f ding might lead to interaction with imit tact dermatitis and occupational asth et allergic reactions, the patterns of cr ine 13,14(beta)-epoxide of abietic acid contact allergens. Cross-reactivity wa ified rosin allergen 15-hydroperoxyad enerate the complete antigen. 15-HP in both hydroperoxides which further i nay react with skin proteins either as ic acid was also studied. The beta-ep	Quincke's oedema. The pathogenesis of contact r allergic skin reactions, e.g. contact urticaria, simply determined by its sensitisation potential: the weakly sensitising substance which is widely which few individuals come into contact. From a ore than 1% of the persons tested. y (rosin) is the nonvolatile fraction of the exudates d as the allergenic constituent. Because it is not an enic properties of colophony started many years ago. a hydroperoxide which subsequently was identified dehydroabietic acid (the other major resin acid in ea pig studies. Clinical investigations have shown gy to colophony. Abietic acid, a rosin acid, is diterpene alcohols, aldehydes, and hydrocarbons To g so-called haptenation). mechanisms. Conjugation of L-lysine to the resin is ree amino group of lysine. Resin acids accumulate in hydroperoxy resin acids with lysine side chains of mune cells having resin acid specificity. The ma observed from exposure to resin acid oxidation I and 15-hydroperoxydehydroabietic acid (15-HPDA) is observed between the alpha- and beta-epoxides pietic acid (15-HPA). This indicates that 15-HPA may A and 15-HPDA cross-reactivity patterns of a radical or as an epoxide, thus generating different toxide was detected in gum rosin. Moreover, the			
400NS Super Wick No Clean & ROSIN-COLOPHONY	No evidence of a sensitization response was observed in ten supporting studies conducted in guinea pigs accordi according to the UN Globally Harmonized System of Cla Sensitization according to Annex I to Directive 67/548/EI according to EU Classification, Labelling and Packaging harmonized translation between Directive 67/548/EEC a 1272/2008 classifies Gum Rosin as "Skin Sensitizer Cate Table 3.2 of EU CLP Regulation (EC) No. 1272/2008 con Annex I to Directive 67/548/EEC. Gum Rosin is assigner Subsequent evaluation determined that the single positi Several esters of Rosin have been tested using similar p protocol, the oxidized material caused a positive sensitiz did not cause oxidation, all sensitization responses were the recommendation is made to declassify non-oxidized	ng to the GPMT or Buehler methods. assification and Labelling of Chemica EC as R43: May cause sensitization of Substances and Mixtures (CLP) F and EU CLP Regulation (EC) No. 127 egory 1" and assigns the hazard state ntains a list of harmonized classificat d the risk phrase R43: May cause se ve study for Gum Rosin was actually protocols with similar results. When the tation response. When those same e	Gum Rosin is not classified for dermal sensitization Is (GHS). Gum Rosin is currently classified for Skin by skin contact. Gum Rosin is also classified Regulation (EC) No. 1272/2008. As part of the 2/2008, Table 3.1 of EU CLP Regulation (EC) No. ement H317: May cause an allergic skin reaction. ions and labelling of hazardous substances from nsitization by skin contact in Table 3.2. conducted with an oxidized form of the test material. Re Rosin esters were heated beyond the specified sters were retested using a different protocol which			
Acute Toxicity	×	Carcinogenicity	×			
Skin Irritation/Corrosion	×	Reproductivity	×			
Serious Eye Damage/Irritation	×	STOT - Single Exposure	×			
Respiratory or Skin sensitisation	 ✓ 	STOT - Repeated Exposure	×			
Mutagenicity	×	Aspiration Hazard	×			
·····;	1		1			

Legend:

X – Data either not available or does not fill the criteria for classification \checkmark – Data available to make classification

Not Available

SECTION 12 Ecological information

12.1. Toxicity

400NS Super Wick No Clean	Endpoint	Test Duration (hr)		Species	Value		Source
	Not Available	Not Available		Not Available	Not Avai	ilable Not Available	
	Endpoint	Test Duration (hr)	Species			Value	Source
	EC50(ECx)	24h	Algae or	other aquatic plants		<0.001mg/L	4
	LC50	96h	Fish			~0.005mg/L	4
copper	EC50	72h	Algae or	other aquatic plants		0.011-0.017mg/L	4
	EC50	48h	Crustace	rustacea		<0.001mg/L	4
	EC50	96h Algae or o		ther aquatic plants 0.03-0.058mg/l		4	
	Endpoint	Test Duration (hr)	Specie	Species		Value	Source
	EC0(ECx)	48h	Crusta	Crustacea 2.15mg/l		2.15mg/l	1
and a selection	LC50	96h	Fish 1.5mg/l		2		
rosin-colophony	EC50	72h	Algae	Algae or other aquatic plants >10<20mg/l		2	
	EC50	48h	Crusta	Crustacea 4.5mg/l		1	
	EC50	96h	Algae	Algae or other aquatic plants 0.031mg/l		2	
						nformation - Aquati	

Very toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.

Do NOT allow product to come in contact with surface waters or to intertidal areas below the mean high water mark. Do not contaminate water when cleaning equipment or disposing of equipment wash-waters.

Wastes resulting from use of the product must be disposed of on site or at approved waste sites.

Metal-containing inorganic substances generally have negligible vapour pressure and are not expected to partition to air. Once released to surface waters and moist soils their fate depends on solubility and dissociation in water. Environmental processes (such as oxidation and the presence of acids or bases) may transform insoluble metals to more soluble ionic forms. Microbiological processes may also transform insoluble metals to more soluble forms. Such ionic species may bind to dissolved ligands or sorb to solid particles in aquatic or aqueous media. A significant proportion of dissolved/ sorbed metals will end up in sediments through the settling of suspended particles. The remaining metal ions can then be taken up by aquatic organisms.

When released to dry soil most metals will exhibit limited mobility and remain in the upper layer, some will leach locally into ground water and/ or surface water ecosystems when soaked by rain or melt ice. Environmental processes may also be important in changing solubilities.

Even though many metals show few toxic effects at physiological pHs, transformation may introduce new or magnified effects.

A metal ion is considered infinitely persistent because it cannot degrade further.

The current state of science does not allow for an unambiguous interpretation of various measures of bioaccumulation.

The counter-ion may also create health and environmental concerns once isolated from the metal. Under normal physiological conditions the counter-ion may be essentially insoluble and may not be bioavailable.

Environmental processes may enhance bioavailability.

Copper is unlikely to accumulate in the atmosphere due to a short residence time for airborne copper aerosols. Airborne coppers, however, may be transported over large distances. Copper accumulates significantly in the food chain.

Drinking Water Standards:

3000 ug/l (UK max)

2000 ug/I (WHO provisional Guideline)

1000 ug/l (WHO level where individuals complain)

Soil Guidelines: Dutch Criteria

36 mg/kg (target)

190 mg/kg (intervention) Air Quality Standards: no data available

The toxic effect of copper in the aquatic biota depends on the bio-availability of copper in water which, in turn, depends on its physico-chemical form (ie.speciation). Bioavailability is decreased by complexation and adsorption of copper by natural organic matter, iron and manganese hydrated oxides, and chelating agents excreted by algae and other aquatic organisms. Toxicity is also affected by pH and hardness. Total copper is rarely useful as a predictor of toxicity. In natural sea water, more than 98% of copper is organically bound and in river waters a high percentage is often organically bound, but the actual percentage depends on the river water and its pH.

Copper exhibits significant toxicity in some aquatic organisms. Some algal species are very sensitive to copper with EC50 (96 hour) values as low as 47 ug/litre dissolved copper whilst for other algal species EC50 values of up to 481 ug/litre have been reported. However many of the reportedly high EC50 values may arise in experiments conducted with a culture media containing copper-complexing agents such as silicate, iron, manganese and EDTA which reduce bioavailability.

Toxic effects arising following exposure by aquatic species to copper are typically:						
Algae EC50 (96 h)	Daphnia magna LC50 (48-96 h)	Amphipods LC50 (48-96 h)	Gastropods LC50 (48-96 h)	Crab larvae LC50 (48-96 h)		
47-481 *	7-54 *	37-183 *	58-112 *	50-100 *		

* ua/litre

Exposure to concentrations ranging from one to a few hundred micrograms per litre has led to sublethal effects and effects on long-term survival. For high bioavailability waters, effect concentrations for several sensitive species may be below 10 ug Cu/litre.

In fish, the acute lethal concentration of copper ranges from a few ug/litre to several mg/litre, depending both on test species and exposure conditions. Where the value is less than 50 ug Cu/litre, test waters generally have a low dissolved organic carbon (DOC) level, low hardness and neutral to slightly acidic pH. Exposure to concentrations ranging from one to a few hundred micrograms per litre has led to sublethal effects and effects on long-term survival. Lower effect concentrations are generally associated with test waters of high bioavailability

Responses expected for high concentration ranges of copper *

1-10 Significant effects are expected for diatoms and sensitive invertebrates, notably cladocerans. 1-10 Effects on fish could be significant in freshwaters with low pH and hardness. 10-100 Significant effects are expected on various species of microalgae, some species of macroalgae, and a range of invertebrates, including crustaceans, gastropods and sea urchins. Survival of sensitive fish will be affected and a variety of fish show sublethal effects. 100-1000 Most taxonomic groups of macroalgae and invertebrates will be severely affected. Lethal levels for most fish species will be reached. >1000 Lethal concentrations for most tolerant organisms are reached.		lotal dissolved Cu concentration range (ug/litre)	Effects of high availability in water
10-100 Effects on fish could be significant in freshwaters with low pH and hardness. 10-100 Significant effects are expected on various species of microalgae, some species of macroalgae, and a range of invertebrates, including crustaceans, gastropods and sea urchins. Survival of sensitive fish will be affected and a variety of fish show sublethal effects. 100-1000 Most taxonomic groups of macroalgae and invertebrates will be severely affected. Lethal levels for most fish species will be reached.		1 10	Significant effects are expected for diatoms and sensitive invertebrates, notably cladocerans.
10-100 gastropods and sea urchins. Survival of sensitive fish will be affected and a variety of fish show sublethal effects. 100-1000 Most taxonomic groups of macroalgae and invertebrates will be severely affected. Lethal levels for most fish species will be reached.		1-10	Effects on fish could be significant in freshwaters with low pH and hardness.
		10-100	
>1000 Lethal concentrations for most tolerant organisms are reached.		100-1000	Most taxonomic groups of macroalgae and invertebrates will be severely affected. Lethal levels for most fish species will be reached.
		>1000	Lethal concentrations for most tolerant organisms are reached.

* Sites chosen have moderate to high bioavailability similar to water used in most toxicity tests.

In soil, copper levels are raised by application of fertiliser, fungicides, from deposition of highway dusts and from urban, mining and industrial sources. Generally, vegetation rooted in soils reflects the soil copper levels in its foliage. This is dependent upon the bioavailability of copper and the physiological requirements of species concerned.

Typical foliar levels of copper are:		
Uncontaminated soils (0.3-250 mg/kg)	Contaminated soils (150-450 mg/kg)	Mining/smelting soils
6.1-25 mg/kg	80 mg/kg	300 mg/kg

Plants rarely show symptoms of toxicity or of adverse growth effects at normal soil concentrations of copper. Crops are often more sensitive to copper than the native flora, so protection levels for agricultural crops range from 25 mg Cu/kg to several hundred mg/kg, depending on country. Chronic and or acute effects on sensitive species occur at copper levels occurring in some soils as a result of human activities such as copper fertiliser addition, and addition of sludge.

When soil levels exceed 150 mg Cu/kg, native and agricultural species show chronic effects. Soils in the range 500-1000 mg Cu/kg act in a strongly selective fashion allowing the survival of only copper-tolerant species and strains. At 2000 Cu mg/kg most species cannot survive. By 3500 mg Cu/kg areas are largely devoid of vegetation cover. The organic content of the soil appears to be a key factor affecting the bioavailability of copper.

On normal forest soils, non-rooted plants such as mosses and lichens show higher copper concentrations. The fruiting bodies and mycorrhizal sheaths of soil fungi associated with higher plants in forests often accumulate copper to much higher levels than plants at the same site. International Programme on Chemical Safety (IPCS): Environmental Health Criteria 200

DO NOT discharge into sewer or waterways.

12.2. Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
rosin-colophony	HIGH	HIGH

12.3. Bioaccumulative potential

Ingredient	Bioaccumulation
rosin-colophony	HIGH (LogKOW = 6.4607)

12.4. Mobility in soil

Ingredient	Mobility
rosin-colophony	LOW (KOC = 21990)

12.5. Results of PBT and vPvB assessment

	Р	В	т
Relevant available data	Not Available	Not Available	Not Available
PBT	×	×	×
vPvB	×	×	×
PBT Criteria fulfilled?			No
vPvB			No

12.6. Endocrine Disruption Properties

Not Available

12.7. Other adverse effects

Not Available

SECTION 13 Disposal considerations

13.1. Waste treatment methods

Product / Packaging disposal	 Recycle wherever possible or consult manufacturer for recycling options. Consult State Land Waste Management Authority for disposal. Metal scrap recycling operations present a wide variety of hazards, including health hazards associated with chemical exposures and safety hazards associated with material processing operations and the equipment used in these tasks. Many of these metals do not pose any hazard to people who handle objects containing the metal in everyday use. In cases where employees could be exposed to multiple hazardous metals or other hazardous substances at the same time or during the same workday, employers must consider the combined effects of the exposure in determining safe exposure levels. The recycling of scrap metals is associated with illness and injury The most common causes of illness were poisoning (e.g., lead or cadmium poisoning), disorders associated with repeated trauma, skin diseases or disorders, and respiratory conditions due to inhalation of, or other contact with, toxic agents. The most common events or exposures leading to these cases were contact with an object or piece of equipment; overextension; and exposure to a harmful substance. The most common types of these injuries were sprains and strains; heat burns; and cuts, lacerations, and punctures. Any combustible material can burn rapidly when in a finely divided form. If such a dust is suspended in air in the right concentration, under certain
------------------------------	---

Page 16 of 18

400NS Super Wick No Clean

	conditions, it can become explosible. Even materials that do not burn in larger pieces (such as aluminum or iron), given the proper conditions, can be explosible in dust form. The force from such an explosion can cause employee deaths, injuries, and destruction of entire buildings. Breaking apart large metal pieces may involve the use of gas cutting torch. Classic cutting torches use gas, while other torches use plasma or powder, or vero water. Thermal (gas) torches expose employees to syrays of sparks and metal dust particles, to high temperatures, to bright ligh that could damage eyes (light both inside and outside of the visible spectrum), and to various gases. Materials that require higher temperatures to cut, such as pig iron and heat-resistant alloyed scrap, or materials that conduct heat too well to be cut with thermal torches, such as copper and broze, may be cut with non-thermal methods such as plasma torches or powder cutting torches. Plasma torches generate a large amount of smoke and noise, as well as ultraviolet (UV) and infrared(IR) light. Depending on the metal, this smoke could contain toxic fumes or dusts. Other hazards common to cutting operations (as well as to welding and brazing) include burns, fires, explosions, electric shock, and heat stress. Even chemicals that are generally not flammable may burn readily when vapourised. Larger scrap metal objects are often token apart using stationary shears, such as alligator shears used to cut apart short steel for foundries or to cut nonferrous metals. These machines can send small pieces of metal flying. Many scrap metal cores, the use fuel or electrical heating sources. Furances generate smoke, dust, and metal fumes, depending on temperature and content. Combustion by-products may include sulfur and nitrogen oxides, and carbon monoxide and carbon dioxide. Organic compounds may be emitted as heating vapourises oil and grease on scraps. In addition, heating or burning of certain plastics (such as plastic form a back of scrap notals or other hazardo
	Where in doubt contact the responsible authority.
Waste treatment options	Not Available
Sewage disposal options	Not Available

SECTION 14 Transport information

Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable	
14.2. UN proper shipping name	Not Applicable	
14.3. Transport hazard class(es)	ClassNot ApplicableSubriskNot Applicable	
14.4. Packing group	Not Applicable	
14.5. Environmental hazard	Not Applicable	
14.6. Special precautions for user	Hazard identification (Kemler) Classification code	Not Applicable Not Applicable
	Hazard Label Special provisions	Not Applicable Not Applicable
	Limited quantity	Not Applicable
	Tunnel Restriction Code	Not Applicable

Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable Image: Work Applicable			
14.2. UN proper shipping name				
14.3. Transport hazard class(es)	ICAO/IATA Class ICAO / IATA Subrisk ERG Code	Not Applicable Not Applicable Not Applicable		
14.4. Packing group	Not Applicable			
14.5. Environmental hazard	rironmental hazard Not Applicable			
14.6. Special precautions for user	Special provisions Cargo Only Packing Instructions Cargo Only Maximum Qty / Pack		Not Applicable Not Applicable Not Applicable	

Passenger and Cargo Packing Instructions	Not Applicable
Passenger and Cargo Maximum Qty / Pack	Not Applicable
Passenger and Cargo Limited Quantity Packing Instructions	Not Applicable
Passenger and Cargo Limited Maximum Qty / Pack	Not Applicable

Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable	
14.2. UN proper shipping name	Not Applicable	
14.3. Transport hazard class(es)	IMDG Class Not Applicable IMDG Subrisk Not Applicable	
14.4. Packing group	Not Applicable	
14.5. Environmental hazard	Not Applicable	
14.6. Special precautions for user	EMS NumberNot ApplicableSpecial provisionsNot ApplicableLimited QuantitiesNot Applicable	

Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable	
14.2. UN proper shipping name	Not Applicable	
14.3. Transport hazard class(es)	Not Applicable Not Applicable	
14.4. Packing group	Not Applicable	
14.5. Environmental hazard	Not Applicable	
14.6. Special precautions for user	Classification codeNot ApplicableSpecial provisionsNot ApplicableLimited quantityNot ApplicableEquipment requiredNot ApplicableFire cones numberNot Applicable	

14.7. Transport in bulk according to Annex II of MARPOL and the IBC code Not Applicable

14.8. Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
copper	Not Available
rosin-colophony	Not Available

14.9. Transport in bulk in accordance with the ICG Code

Product name	Ship Type
copper	Not Available
rosin-colophony	Not Available

SECTION 15 Regulatory information

15.1. Safety, health and environmental regulations / legislation specific for the substance or mixture

copper is found on the following regulatory lists	
Europe EC Inventory	European Union - European Inventory of Existing Commercial Chemical Substances (EINECS)
rosin-colophony is found on the following regulatory lists	
Europe EC Inventory	European Union (EU) Regulation (EC) No 1272/2008 on Classification, Labelling and
European Union - European Inventory of Existing Commercial Chemical Substances	Packaging of Substances and Mixtures - Annex VI
(EINECS)	

This safety data sheet is in compliance with the following EU legislation and its adaptations - as far as applicable - : Directives 98/24/EC, - 92/85/EEC, - 94/33/EC, - 2008/98/EC, - 2010/75/EU; Commission Regulation (EU) 2020/878; Regulation (EC) No 1272/2008 as updated through ATPs.

15.2. Chemical safety assessment

No Chemical Safety Assessment has been carried out for this substance/mixture by the supplier.

Status

National Inventory Status

National Inventory

National Inventory	Status
Australia - AIIC / Australia Non-Industrial Use	Yes
Canada - DSL	Yes
Canada - NDSL	No (copper; rosin-colophony)
China - IECSC	Yes
Europe - EINEC / ELINCS / NLP	Yes
Japan - ENCS	No (copper; rosin-colophony)
Korea - KECI	Yes
New Zealand - NZIoC	Yes
Philippines - PICCS	Yes
USA - TSCA	Yes
Taiwan - TCSI	Yes
Mexico - INSQ	Yes
Vietnam - NCI	Yes
Russia - FBEPH	Yes
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.

SECTION 16 Other information

Revision Date 21	21/06/2022
Initial Date 21	21/02/2018

Full text Risk and Hazard codes

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered. For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

Definitions and abbreviations

PC-TWA: Permissible Concentration-Time Weighted Average

PC-STEL: Permissible Concentration-Short Term Exposure Limit

IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists

STEL: Short Term Exposure Limit

TEEL: Temporary Emergency Exposure Limit。 IDLH: Immediately Dangerous to Life or Health Concentrations

ES: Exposure Standard

OSF: Odour Safety Factor

NOAEL :No Observed Adverse Effect Level

LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value

BCF: BioConcentration Factors BEI: Biological Exposure Index

AIIC: Australian Inventory of Industrial Chemicals

DSL: Domestic Substances List

NDSL: Non-Domestic Substances List

IECSC: Inventory of Existing Chemical Substance in China EINECS: European INventory of Existing Commercial chemical Substances

ELINCS: European List of Notified Chemical Substances

NLP: No-Longer Polymers

ENCS: Existing and New Chemical Substances Inventory

KECI: Korea Existing Chemicals Inventory

NZIoC: New Zealand Inventory of Chemicals

PICCS: Philippine Inventory of Chemicals and Chemical Substances TSCA: Toxic Substances Control Act

TCSI: Taiwan Chemical Substance Inventory

INSQ: Inventario Nacional de Sustancias Químicas

NCI: National Chemical Inventory

FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

Reason For Change

A-2.01 - Added new part numbers