



Polymer Processing



360° Spray System for all angle use



High Temperature Resistant

## FORMULA 12

### NON-SILICONE SEMI-PERMANENT RELEASE AGENT

Formula 12 is a specially formulated release coating for use in a wide variety of rubber and rotational moulding applications. The coating once applied to a pre-heated mould surface forms a thin, inert and thermally stable release film. Multiple releases of many grades of polyethylene, polypropylene and all natural and synthetic rubbers (except silicone elastomers) can be expected. Formula 12 is fast curing, offering easier release and reduced reject rates. It is effective up to 250°C and has lower mould build-up.

### PRODUCT CODES / FILL SIZES



31544 / 400ml

### DIRECTIONS

#### Mould Preparation

- **New Moulds:** All moulds must be thoroughly cleaned and dried and any traces of previous release agents must be removed, using one of Ambersils mould cleaners or Amberklene FE10, ME20 or LO30.
- **Old Moulds:** All traces of previous release agents and moulding residues must be cleaned away, taking care to ensure that any deep cavities, corners or undercuts are free of residues and signs of oxidation.
- **Application:** Mould should be clean and dry. Apply a thin, even film from 15 – 25cm at temperatures between ambient room temperature and 60OC. Allow 5 – 10 minutes for film to cure before commencing moulding. Performance will be enhanced by re-coating once the first few releases have been made.

With respect to curing times and baking on of the release agent film, this will depend greatly on the grade of material being moulded, mould construction and mould condition.

- Only a thin film is required, apply 8-10” from the mould surface. To obtain the best results, coat small areas at a time working progressively from one side of the mould to the other. Avoid spraying over the same area that was just coated until the solvent has fully evaporated
- On new moulds apply 2-3 base coats prior to commencing moulding, allowing up to 5-10 minutes after each application for complete solvent evaporation. The film should be dry and not feel tacky. A further two coats should be applied after the second release from the tool paying special attention to any deep cavities and undercuts and leaving 5-10 mins after the final coat for the film to cure properly.
- Performance will be enhanced by re-coating once the first few releases have been made. As the mould becomes conditioned to Formula Twelve, release will become more uniform and multiple releases will be obtained.
- When any slight variances in the quality of release are noted, a light touch up coat may be applied. This may be done to the affected area or to the whole mould surface following the guidelines above.

## TECHNICAL DATA (WITHOUT PROPELLANT)

Appearance	Finely atomised spray
Odour	Hydrocarbon
Solvents	Aliphatic Naptha
Pressure @ 25°C	40 psi
Flammability	Classified as extremely flammable under current EU regulations

## MATERIALS COMPATIBILITY

OK	-
CAUTION	-
NOT OK	-

## STORAGE & SHELF LIFE

The product may be stored at normal ambient temperatures and has a shelf life of not less than 1 year with correct storage.

## HEALTH AND SAFETY

A separate Safety Data Sheet (SDS) according to EC Regulation 73/404/EEC and 648/2004/EC is available from Ambersil.com or via [info.uk@crcind.com](mailto:info.uk@crcind.com)

## MISREPRESENTATION ACT 1967

## TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

Version 3.1  
Created: July 2019  
Updated: October 2020

CRC Industries UK Ltd.  
Wylds Road, Bridgwater  
Somerset, TA6 4DD  
United Kingdom

t +44 (0)1278 727200  
f +44 (0)1278 425644  
e [sales.uk@crcind.com](mailto:sales.uk@crcind.com)  
w [www.ambersil.com](http://www.ambersil.com)

Company Registered No. 04910479

VAT No. GB 821 5195 42

