

# Statguard® Conductive Acrylic Paint Application Instructions




Figure 1, Item No. 71016, 3.8 litres

# **Description**

Charleswater Europe's Statguard<sup>®</sup>
Conductive Acrylic Paint is a one part floor coating formulated to produce controlled dissipation of static electrical charges.
Conductive Acrylic Paint is very effective as a static control floor coating for electronics manufacturing, assembly, and storage. It is available in grey in a 3.8 litre container as item no. 71016 and in 19 litre container as item no. 71017.

# **General Guidelines**

#### **GROUNDING:**

Conventional grounding practices like connecting painted surfaces to ground or internal building grounds are only required for applications of Statguard<sup>®</sup> Conductive Acrylic Paint that are not in excess of 1.8 square metres. For applications that are greater than 1.8 square metres, grounding should not be required. The electrical properties of conductive paint enable the surface to dissipate 5000 volts to zero in less than 0.01 seconds per FTMS 101C, Method 4046 without conventional grounds. The conductive paint becomes a capacitance reservoir that effectively drains static charges.

Foot grounders should be used in conjunction with flooring painted with Statguard<sup>®</sup> Conductive Acrylic Paint to properly ground personnel. For more information, please contact the Charleswater Europe factory.

# **Surface Preparation**

The two most important characteristics for successful application of Statguard<sup>®</sup> Conductive Acrylic Paint applications are:

1. The surface must be clean, dry, dull, and smooth. Heavy dirt or grease build-up should be removed with a stripper or

degreaser. Cleaning methods range from: sweeping, vacuuming, wire brush, air-blasting, water jet, steam cleaning, or stripping.

2. If the surface is concrete, it must be in good condition.

#### CONCRETE:

New concrete should cure for a minimum of 28 days before coating with Statguard<sup>®</sup> Conductive Acrylic Paint. Not all concrete is created equal -- concrete surfaces vary widely in physical and chemical qualities due to the way the concrete was originally formulated, poured, or finished.

There are several methods to prepare problem concrete. Each method depends on the condition of the concrete. Adhesion properties can be increased by profiling or roughing the surface through acid etching, rotary drum sanding, scarifying, or mechanically scratching the surface.

#### PRIMING

Statguard<sup>®</sup> Conductive Acrylic Paint bonds well to clean, dry concrete. However, a standard industrial primer can be used on certain difficult to bond substrates and enhance the adhesion of Statguard<sup>®</sup> Conductive Acrylic Paint.

# PREVIOUSLY PAINTED SURFACES:

The surface should be clean and free of dust, grease, wax, and soap residue. Wash with ordinary detergent and water. Rinse thoroughly with clean water and let dry. Glossy surfaces can be dulled by lightly sanding and then vacuuming, and cleaning. Cracks and holes should be repaired before applying the Statguard<sup>®</sup> Conductive Acrylic Paint. Adhesion can be improved by using a standard industrial type primer.

#### **UNPAINTED SURFACES:**

Adhesion can be improved by using a standard industrial type primer. Metal should be primed with red oxide primer. Concrete, wood, plastics, and most other surfaces should be properly cleaned. Let dry and then apply Statguard<sup>®</sup> Conductive Acrylic Paint.

#### **COVERAGE:**

Statguard® Conductive Acrylic Paint will cover 28 to 37 square metres at a 1 to 1.5 mm thick dry film per 3.8 litre on a smooth surface. Coverage is less on coarse or textured surfaces. Two coats are recommended to achieve maximum performance from the paint.

# **Application**

Always use in a well ventilated area or wear a suitable respirator. Wear appropriate eye protection such as splash goggles and impervious type protection gloves to protect hands.

#### **APPLICATION BY ROLLER**

- 1. Stir paint thoroughly to mix any settled solids to produce uniform grey colour.
- 2. Combine separate cans of paint into one container to ensure uniform colour distribution. It is recommended that a test area be coated to ensure that the adhesion and electrical performance of the paint is acceptable. (See Adhesion Testing, Figure 5.) If the test areas show inadequate adhesion, use an industrial floor primer/sealer.
- 3. Saturate a 6.35 mm fine nap roller or an industrial brush with paint. Remove excess paint and trapped air from the applicator by moving applicator several times in the paint tray.
- 4. A minimum number of strokes from the applicator on the substrate is recommended to minimise air bubbles.



Figure 2. Paint application with roller.

#### **APPLICATION BY SPRAY**

**Conventional Spray Gun:** "E" fluid tip and needle and #704, 765 or 78 air gap.

**Airless Spray:** Spray gun and spray cap or suitable orifice diameter 0.508-0.635 mm.

Mix paint thoroughly before using and stir occasionally when applying. No thinning necessary. Room temperature must be above 10°C.

A minimum of two coats of Statguard<sup>®</sup> Conductive Acrylic Paint is recommended for appropriate static protection.



Figure 3. Spray paint application

# Clean Up

Wash applicators with water immediately after painting. Remove paint spills promptly with a wet cloth. Close container after each use. Keep container from freezing.

## **Drying**

It is recommended that Conductive Acrylic Paint be allowed to dry at a temperature in excess of 7°C. A minimum of 1 to 2 hours drying time should be allowed before applying the second coat. Wait a minimum of 12 hours drying time after the last coat before allowing light traffic on the coated area. At high humidity levels, a longer drying time may be necessary. Do not force dry.

#### **Maintenance**

Use sweeper, vacuum, or broom to remove dirt. Allow two weeks drying time before using a damp mop to clean the coated area. Do not use abrasive cleaners, floor rinse, or scrubbing machine to clean the floor.

# **Optional Finish/Sealer**

Charleswater Europe's Statguard<sup>®</sup>
Conductive Acrylic Paint can be over-coated or sealed with Statguard<sup>®</sup> Floor Finish static dissipative coating to increase durability, enhance shine, improve ease of maintenance, and seal out dirt and debris. Statguard<sup>®</sup> is a polymer base floor finish/sealer that can be used as a top coat on the Conductive Acrylic Paint. Surface resistivity will then be in the 10<sup>6</sup>-10<sup>7</sup> ohms range. Two coats are recommended. Three coats will increase electrical properties, durability and reduce frequency of maintenance. Ask for Technical Bulletin PPE-5023E for more information on Statguard<sup>®</sup> Floor Finish.

# **Physical Properties**

#### Type

Water base acrylic coating

#### Colour:

Grey

# Vehicle Type:

Pure acrylic resin waterborne

## **Pigment Type:**

Lead free, iron oxide, titanium dioxide and extenders

#### Viscosity:

50 Krebs units

#### Solids:

21% by volume

#### **Coating Density:**

1.0 kilograms per litre

#### Gloss:

30 @ 60°

## Max. Temperature:

Dry - 149°C Wet - 93°C

# **Electrical Properties**

# **Surface Resistivity:**

10<sup>5</sup> ohms/sq. per ASTM D257

## Static Charge Decay:

<0.01 sec. per FTMS 101B, Method 4046

#### **Charge Generation:**

Zero per AATCC Step Test, Method 134-197

#### RTT:

10<sup>5</sup> ohms per ANSI ESD-S7.1

#### RTG:

 $10^5$  ohms per ANSI ESD-S7.1

# **Testing**

Representative areas should be tested for adhesion and electrical performance of the paint before applying paint to the entire floor. To best ensure consistent results, the test should be done at various locations.

# **ELECTRICAL PROPERTIES:**

Test the surface resistivity, point-to-point resistance, and resistance-to-ground properties of coated area per ANSI ESD-S7.1 test method. For quick and easy verification of the paint's electrical properties, Charleswater Europe recommends the use of our 99100 Surface Resistance Test Kit (Figure 4). For more information request Technical Bulletin PPE-5032E.



Figure 4. Electrical testing on the painted floor using Surface Resistance Test Kit, Item

#### ADHESION:

Allow newly applied paint to dry a minimum of 48 hours before proceeding with the test. At humidity levels over 55% RH, allow 72 hours of drying time before testing. Use a razor to cut a cross or a few perpendicular lines over a 75 mm by 75 mm area on several spots of the thoroughly dried area. Use a piece of masking tape to cover the marked area. Make sure the tape is thoroughly adhered to the test area. Pull the tape off the surface and examine the amount of paint which has peeled off during the test. If any significant portion is transfered to the tape, better surface preparation (acid etching, cleaning or sanding) should be done on the substrate to enhance the adhesion.




Figure 5. Adhesion test on the painted floor.

#### **Limited Warranty**

Charleswater Europe expressly warrants that for a period of one (1) year from the date of purchase, Charleswater Europe's Statguard<sup>®</sup> Conductive Paint will be free of defects in material (parts). Within the warranty period, the material will be tested, repaired or replaced at our option free of charge. Call customer service at 00 44 (0) 1892-665313 for a Return Material Authorisation (RMA) and proper shipping instructions and address. You should include a copy of your original packing slip, invoice, or other proof of purchase date. Any material under warranty should be shipped prepaid to the Charleswater Europe factory in Crowborough, UK. Warranty replacements will take approximately two weeks.

#### **Warranty Exclusions**

THE FOREGOING EXPRESS WARRANTY IS MADE IN LIEU OF ALL OTHER PRODUCT WARRANTIES, EXPRESSED AND IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE WHICH ARE SPECIFICALLY DISCLAIMED. The express warranty will not apply to defects or damage due to accidents, neglect, misuse, alterations, operator error, or failure to properly maintain, clean or repair products.

#### **Limit of Liability**

In no event will Charleswater Europe or any seller be responsible or liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and users assume all risk and liability whatsoever in connection therewith.

EC-Material Safety Data Sheet, according to 91/155EC

Date: September 1, 1998

Conductive Acrylic Paint

#### 1. IDENTIFICATION OF THE PRODUCT AND OF THE ENTERPRISE

Chemical name: Paint, Conductive

Manufacturer Desco Industries, Inc. Charleswater Europe

Hudson Road Unit 17. Millbrook Business Park

Canton, MA 02021 Sybron Way

U.S.A. Crowborough, East Sussex TN 3JZ

United Kingdom

**Emergency** Phone: (781) 821-8370 Phone: 00 44 (0) 1892-665313 Fax: (781) 575-0172 Fax: 00 44 (0) 1892-668838

#### 2. INFORMATION ON INGREDIENTS/COMPOSITION

Ingredients	Weight	CAS-No.	TLV-value	R-Phrases
Ethylene Glycol Monobutyl Ether*	5-25%	111-76-2	25 ppm	R20/R21/R22, R37
Mineral Spirits	1-5%	8032-32-4	100 ppm	Carc, Cat 2, R22, R45
Butonal*	1-5%	71-36-3	50 ppm	R10, R20
Ammonium, Hydroxide	1-5%	1336-21-6	50 ppm	R34, R37
Aromatic Acid	0-1%	65-85-0		
Ektasolve EP	1-5%	2807-30-9	25 ppm	R10, R21, R36
DE Glycol*	1-5%	111-90-0		

#### \* Listed Chemical Subject To Reporting Requirement of SARA Section 313 of Title III

HMIS Rating	Health	1	Reactivity	0
_	Flammability	0	Personal Protection	В

#### 3. HAZARDS IDENTIFICATION

Eyes May cause irritation, possible corneal injury, eye damage, and/or blindness.

Skin Repeated or continuous contact may cause irritation of the skin. No evidence of adverse effects. May cause nausea,

dizziness & weakness.

Ingestion May cause nausea, vomiting, and diarrhea. May cause headache, dizziness & stupor. May cause abdominal discomfort.

Contains a carcinogen, may cause cancer.

Inhalation May cause headache & dizziness, & possible unconsciousness. May cause nausea & vomiting. Vapours may irritate the

eyes, nose, throat, & respiratory tract.

# 4. FIRST AID MEASURES

Eye Contact Flush with water for at least 15 minutes. Contact a physician immediately.

Skin contact Wash with soap and water. Remove contaminated clothing. Consult a physician if irritation persists.

Induce vomiting, drink 2 glasses of water. Contact a physician.

Inhalation Move subject to fresh air. If breathing has stopped, give artificial respiration. If breathing is difficult, give oxygen.

Contact a physician.

#### 5. EXTINGUISHING MEASURES

Proper Extinguishing Media The National Fire Protection (NFPA) classifies ingredient liquids to be Class B fires. Therefore, any approved Fire

Extinguisher or extinguishing agent may be used for fire fighting purpose, e.g. CO<sub>2</sub>, dry chemical and foam. Wearing of appropriate protective equipment including self-contained breathing apparatus should be used.

Special Procedures Water spray may be ineffective. If water is used, fog nozzles are preferable. Water may be used to cool closed containers

to prevent pressure build-up, and possible auto ignition or explosion when exposed to extreme heat.

## 6. MEASURES TO EXPOSURE OF PRODUCT

Personal Precautions Wearing protective clothing. Inhalation protection. Extinguish all ignition sources.

Environmental Precautions Cleaning Procedures

Protective Clothing

N/A

Dike and collect material into plastic container. Water rinse and drain, flush small amounts. Use sanitary landfill disposal.

Follow state and local regulations (RCRA; Subtitle D).

# 7. HANDLING AND STORAGE

Handling Use in well-ventilated areas; avoid breathing vapours. Keep containers closed when not in use. Avoid from freezing.

Storage Temperature: Max. 49°C/120°F - 1°C/34°F. Keep from freezing.

## 8. EXPOSURE CONTROL/PERSONAL EXPOSURE

Control Parameters TLV-value 50 ppm maximum for Ethylene Glycol Monobutyl Ether

Other Regulations Nor

Measures For Technical Control Preferences of technical measure to prevent or control contact with the product. Isolating process and personnel,

mechanical ventilation (dilution and local exhaust) and the regulation of process conditions. In case of non-prevention

or non-control, proper protective wearing should be used.

Respiratory Protection Wear MSHA/NIOSH approved respirator where exposure limits are exceeded.

Hand Protection Impervious/Neoprene Gloves

Eye Protection Chemical Splash Goggles (ANSI-87.1)

Work/Hygienic Practices Wash hands before eating, smoking, or using washroom facilities.

#### 9. PHYSICAL AND CHEMICAL PROPERTIES

Form Liquid Colour Grey, Opaque Smell Mild pН 8.5 Boiling Point at °C 100-101°C Freezing Point at °C  $0^{\circ}C$ Flash Point at °C -17.7 °C

**Explosive Limits** LEL: 0.8 UEL: 25.0 Inflammability Limits (vol % in air) N/A

Solubility in water Complete 92.43 mm @ 20°C Vapour Pressure (mmHg) Vapour Density (air = 1) Heavier than air Density at 20°C 979 grams/litre

Specific Gravity (H20 = 1) 1.21

Inflammability Classification according to OSHA and EC-regulations "non-flammable"

Ignition Temperature N/A

Evaporation Rate Slower than n-butyl acetate

13.299% % Volatile by Volume

#### 10. STABILITY AND REACTIVITY

Stability/Reactivity Stable at normal conditions.

Temperatures above 49°C/120°F and below 1°C/34°F, open flames and sparks. Conditions to avoid

Materials to avoid Strong Oxidizing agents and alkalies.

Oxides of carbon and nitrogen. If involved in fire (from other sources) could conceivably result in release of Carbon Hazardous Decomposition

Dioxide and Carbon Monoxide fumes

#### 11 TOVICOLOCICAL INFORMATION

II. IUXICULUGICAL INFURMA	ATION					
Ingredient-Material Description	PEL	TLV (twa) mg/m3 ppm		LD50 (r (rat) oral	ng/kg) (rbt) dermal	LC50 (ppm) (rat) Inhal
EB Glycol*	50.0	0.0	25.0	470.0	220.0	0.0
Butanol*	50.0	0.0	50.0	0.0	0.0	0.0
Mineral Spirits	100.00	0.0	100.00	0.0	0.0	0.0
Ammonium Hydroxide	0.0	35.0	50.0	350.00	0.0	0.0
Aromatic Acid	0.0	0.0	0.0	2530.0	2000.0	0.0
Ektasolve EP	0.0	0.0	25.0	3089.0	1337.0	2131.0
Butyl Carbitol	0.0	0.0	0.0	6560.0	4120.0	0.0
DE Glycol*	0.0	0.0	0.0	0.0	0.0	0.0

<sup>\*</sup>Listed Chemical Subject To Reporting Requirement of SARA Section 313 of Title III

#### 12. ECOLOGICAL INFORMATION

No environmental hazards have been reported or known.

Mobility The product is aqueous and will be separated in aqueous conditions.

Degradability N/A Bioaccumulation Not likely Ecotoxicity None known References to BimSch V N/A Hazard Classification Non-hazardous

13. DISPOSAL CONSIDERATIONS

Dike and collect material into plastic container. Water rinse and drain, flush small amounts. Use sanitary landfill disposal. Product

Follow state and local regulations (RCRA; Subtitle D).

Hazardous Waste Number Nonregulated

#### 14. TRANSPORT INFORMATION

This product is not classified for transport under ADR/IMDG regulations.

#### 15. REGULATORY INFORMATION

Physical/Chemical Indication Non-flammable

(R20/R21/R22): harmful by inhalation, in contact with skin, and if swallowed (R36/R37/R38): irritates eyes, respiratory Risk-phrase

systems, and skin (R45): may cause cancer.

Safety Phrase (S2): keep away from children, (S7): keep containers well closed, (S24/25): avoid contact with skin and eyes, (S45): in case of

accident or if you feel unwell, seek medical advice immediately, show label where possible, (S53): avoid exposure, obtain special instruction before use, (S62): if swallowed, do not induce vomiting; seek medical advice immediately and show this container or label.

**EU Classification** This product does not have to be classified according to the EU Regulations.

(67/548/EEC-88/379/EEC)

All components are included in the EINECS Inventories **EINECS Status** 

#### 16. OTHER INFORMATION

Further Information None

Disclaimer

The information given in this publication has been worked up to the best of the knowledge of Charleswater Europe, as well as taking into consideration the applicable laws and regulations. We cannot anticipate all conditions under which this information and our products or the products of the manufacturers in combination with our products may be used. We accept no responsibility for the results obtained by the application information or the safety and suitability of our product or combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and end users assume responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.