



PILLOWPACKS

- Perfect for fragile, sensitive and expensive components
- ESD safe foam forms around the parts
- No tooling required
- Provides great physical protection
- Fits multiple sized components

PN	L X W X H (D)	QTY/CASE
PP2020	2 X 2 X 1/4"	100
PP2525	2-9/16 x 2-9/16 x 1/2"	150
PP2535	3-1/2 x 2-9/16 x 1/2"	100
PP3545	4-5/8 x 3-1/2 x 1/2"	50
PP7035	7 x 3-1/2 x 1/2"	50



SPECIFICATIONS

These products meet and/or exceed ANSI/ESD S20.20-2021 and ANSI/ESD S541-2019.

INJECTION MOLDED HINGED BOXES		
PROPERTY	VALUE (U.S.)	TEST METHOD
Surface Resistivity	<1 ⁶ Ohms/sq	D257
Volume Resistivity	<1 ³ Ohms/sq	D257
Electrostatic Decay Rate	<2 sec	FTMS101C 4046.1
Impact Strength, IZOD		
Notched 1/8" Section	5.0 ft-lb/in	D256
Unnotched 1/8" Section	No Break	D4812
Tensile Strength	3200 psi	D638
Tensile Elongation	>10.0%	D638
Tensile Module	.15x10 ⁶ psi	D638
Flexural Strength	4700 psi	D790
Flexural Modulus	.17x10 ⁶ psi	D790

PILLOWSTAT FOAM		
PROPERTY	VALUE (U.S.)	TEST METHOD
Color	Black	Visual
Volume Resistance	103-105 Ohms/sq	ANSI/ESD STM11.12-2021
Surface Resistance	103-105 Ohms/sq	ANSI/ESD STM11.11-2022
Static Decay Rate	0.01 Sec	ASTM D-257
Density	4.8 - 5.2 lbs/ft ³	ASTM D-3574-01
Indent Force Deflection @ 25%	7-17 psi	ASTM D-3574-01
Shelf Life	Long Term	

All values are for pre-formed materials. Electrical values will vary with each individual design. All information, recommendations and suggestions appearing in this bulletin concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Conductive Containers, Inc. as to the effects of such use or the results to be obtained, nor does Conductive Containers, Inc. assume any liability arising out of use, by others, of the products referred to herein. Nor is the information herein to be construed as absolutely complete since additional information may be necessary or desirable, when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.

