

LS 9 V

Primary lithium battery

Primary lithium-thionyl chloride (Li-SOCl2) high energy density battery pack.

A prismatic battery pack for a wide range of applications requesting low base currents combined with superimposed pulses. The LS 9 V version yields good voltage readings in a wide T range (- 60°C to + 85°C).



- · Memory back-up
- · Alarm and security devices
- · Smoke detectors
- · Alarm equipment
- · Industrial electronics
- · Medical equipment



- Pack assembled from three ½ AA-sized (and UL-recognized) cells connected in series
- · Component cells with stainless steel container and hermetic glass-to-metal sealing
- · Plastic sleeve for battery housing
- Miniature snap-on terminals
- · Non-flammable electrolyte
- Non-restricted for transport
- · Manufactured in China
- · CE: P/N: C10-0576

Benefits

- High voltage, stable during most of the application's lifetime
- Wide operating temperature range
- · Low self-discharge rate (less than 1% per year of storage at + 20°C)
- · Easy integration into compact systems




Pack construction	3 LS 14250 in series
Pack designation	LS 9 V
Part number	C10-0576
Electrical characteristics*	
Nominal capacity (at 1 mA, +20°C, 6.0V cut-off. The capacity restored by the battery pack varies according to current drai, temperature and cut-off	1.2 Ah y (1.0 mA)
Open circuit voltage (at +20°C)	11.0 V
Nominal voltage (at +20°C and 0.1mA)	10.8 V
Pulse capability: typically up to (0.1 second pulses, drained every 2 mn at +20°C from undischarged cells with 10 μ A base current, yield voltage readings above 9.0 V. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult Saft	/. e a
Maximum recommended continuous current (Higher currents possible, consult Saft)	35 mA
Storage (recommended) (For more severe conditions, consult Saft)	+30°C (+86°F) max
Operating temperature range (Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult Saft)	- 60°C / +85°C (- 76°F / +185°F)
Typical weight	31 g (1.09 oz)
Lithium metal content	approx. 0.9 g
* Typical values relative to cells stored for one year or less at + 30°C max.	





LS 9 V

Primary lithium battery




Dimensions in mm


Storage


 The storage area should be clean, cool (preferably not exceeding + 30°C), dry and ventilated.

Warning

- · Fire, explosion and burn hazard
- Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water
- Do not solder directly to the battery pack







Block 8, 201 Lianfeng Road, Xiangzhou District, Zhuhai, Guangdong Province 519030, China Tel: +86 756 6290 288 Saft(Zhuhai FTZ) Batteries Co,Ltd

Saft, a subsidiary of TotalEnergies S.A.S. au capital de 26 724 876 € R.C.S. Nanterre 481 480 465 www.saft.com Document N° 700027-EN-2501

Edition: Jan 2025

Data in this document is subject to change without notice and becomes contractual only after written confirmation.

Photo credits: © Saft

