


1-800-383-7323 USA/CAN www.energizer.com

# **EVEREADY 732**





## **Industry Standard Dimensions**



Chemical System: Zinc-Manganese Dioxide (Zn/MnO<sub>2</sub>)

(No Added Mercury or Cadmium)

**Designation:** ANSI-926 **Battery Voltage:** 12 Volts

Operating Temp: -18°C to 55°C (0°F to 130°F)
Average Weight: 1,200 grams (42.5 oz.)

Volume: 1,182 cubic centimeters (72 cubic inch)

Average Capacity: 7.5 Ah to 0.6 volts / cell

(Rated at 25k ohms continuous at 21°C)

Cell: Eight No. 60 (size "F") in series

Terminals: Screw Post Jacket: Plastic


#### INTERNAL RESISTANCE VS. TEMPERATURE


The measurement is an approximation of the battery's actual internal resistance. It is sensitive to the loads and operator technique.

Schedule: Background Load 600 ohms

Pulse Load 10 ohms
Pulse Duration 1 second

| Temperature  | Typical Ri (ohms) |
|--------------|-------------------|
| 45°C (113°F) | 2                 |
| 21°C (70°F)  | 2.1               |
| 0°C (32°F)   | 2.4               |
| -21°C (-4°F) | 24.0              |





### **Important Notice**

This data sheet contains information specific to batteries manufactured at the time of its publication.

Contents herein do not constitute a warranty.

Copyright © Eveready Battery Co. Inc. - All Rights Reserved


Form No. EBC - 3232G Page 1 of 2





1-800-383-7323 USA/CAN www.energizer.com


# **EVEREADY 732**

## **Typical Applications**









#### **Important Notice**

This data sheet contains information specific to batteries manufactured at the time of its publication.

Contents herein do not constitute a warranty.

Copyright © Eveready Battery Co. Inc. - All Rights Reserved

Form No. EBC - 3232G Page 2 of 2