

ANCHORSET GREEN 300

Colour	Product Code	Pack Size	Box Qty
Grey	ANCHGREEN	300ML	10

Product Description

ANCHORSET GREEN is a styrene free rapid curing chemical anchoring system designed for high strength fixing of railings, satellite dishes, signs, brackets and other fixtures which carry heavy loads. The unique EASY-FLOW technology of ANCHORSET GREEN means the twin bag system within the cartridge enables the product to be applied using a standard cartridge gun.

Benefits

- Easy mix twin bag system.
- Styrene free low odour.
- Apply using a standard sealant gun.
- Rapid curing system.

Areas For Use

- Fixing wall ties.
- Bolts and screws into a wide range of building substrates.
- Securing machinery into floors.
- Fixing studs and starter bars.

Limitations

- Do not use in non porous substrates i.e. metal, PVC.
- Do not use on wet surfaces.
- As the manufacturer cannot know all the uses its products may be put to, it is the users responsibility to determine suitability for use. If in doubt, contact technical services department for advice.

Surface Preparation

Drill hole to the correct diameter and depth (see chart for guide), ideally using a rotary percussion machine. For optimum results the hole must be coarse sided. If the holes are produced by diamond drilling the surfaces should be thoroughly roughened. Remove all dust and debris from the hole using a hand air pump or a stiff rotary brush. All bars should be clean and free from oil or grease and all flaking rust should be removed. Threaded rod or studs should be chisel-ended to prevent them being unscrewed from the cured resin.

Application

Unscrew the lid and cut off the top of the bag under the metal clamp. Attach the mixing nozzle to the cartridge (*screw down hand tight*). Place cartridge into the dispensing gun. Gradually pressurise the Cartridge by activating the hand trigger a few times until material passes through the mixing nozzle and an even colour is obtained (approximately 5-6 inches of extruded material should be adequate). Once the desired fill is achieved release the pressure by pressing the slide release arm and pulling back the slide rail, wipe off excess material and insert the fixing slowly, with a rotating action, to the desired depth.

Specific Data

Compressive Strength (ASTM 695)		58 N/mm ²	
Tensile Strength (ASTM 638)		< 10 N/mm ²	
Flexural Strength (ASTM 790)		19 N/mm ²	
Elastic Modulus		6700 N/mm ²	
Flexural Modulus		4205 N/mm ²	
Mixed Density		1.65 g/cm ³	
Mixing Ratio		10:1 by volume as supplied in cartridge	
Temperature		Gel Time	Minimum Loading Time
(°C)	(°F)	(Minutes)	(Minutes)
5	41	12	50
10	50	9	45
15	59	6	35
20	68	5	30
25	77	3	30

ANCHOR SIZE (mm)	HOLE DIAMETER (mm)	HOLE DEPTH (mm)	TENSION (kN) (Ultimate pull out)	FIXINGS PER UNIT (Holes filled 2/3 full) 300ml
8	10	80	21.5	68
10	12	90	28.0	42
12	14	110	30.0	25
16	18	125	69.0	13
20	22	170	75.0	5
24	26	210	101.0	4
30	32	280	171.0	2

Tension Figures quoted are tested in accordance with B.S. 5080 PART 1 in approximately 30 N/mm² concrete

Health & Safety

Consult MSDS for full list of hazards.

Storage

Store in cool dry conditions between + 5°C and 25°C.

Shelf Life

Use within 12 months.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.