

# 8406 Wicking Grade

## Technical Data Sheet

### 8406 Wicking Grade Cyanoacrylate Adhesive

**Chemtools 8406** is low viscosity combined with fast cure speed, surface insensitive cyanoacrylate adhesive (CA). It is specifically formulated to bond difficult surfaces with high industrial strength.

#### APPLICATIONS:

- Ideal for bonding rough, porous and acidic surfaces including Wood, Cardboard, Balsa Wood, Rubbers, Plastics, Metals, Leather, etc.
- Wide variety of industrial manufacturing and repairing applications

#### BONDING TIMES:

Plastics	2-5 seconds	Rubbers	< 3 seconds
Wood	1-5 seconds	Leather	5-15 seconds
Metals	8-10 seconds	Ceramics	12-18 seconds

#### PHYSICAL PROPERTIES:

Composition	Ethyl Cyanoacrylate
Appearance	Colourless liquid
Viscosity@ 25°C	20 cps
Brookfield LVT Spindle 1 @ 30 rpm	

#### Cured Adhesive

Gap Filling	0.05mm
Tensile Shear Strength	18-28 N/mm <sup>2</sup>
Service Temperature Range	-60 to +80°C
Full Cure	24 hours
Melting Point Temperature	160 to 170°C

#### **Shear Strength** ASTM D 1002/DIN 53283

Grit Blasted Steel	>20 N/mm <sup>2</sup>
Etched Aluminum	>18 N/mm <sup>2</sup>
Rubbers	>22 N/mm <sup>2</sup>
Wood	>25 N/mm <sup>2</sup>
Polycarbonate	>12 N/mm <sup>2</sup>
ABS	>10 N/mm <sup>2</sup>

#### Mechanical Properties:

Coefficient of thermal conductivity, ASTM C177, W.m <sup>-1</sup> k <sup>-1</sup>	0.1
Glass Transition Temperature, ASTM E228,	122°C
Coefficient of thermal expansion, ASTM D696, K <sup>-1</sup>	75 x 10 <sup>-6</sup>
Dielectric strength, ASTM D149, kV/mm	27
Volume resistivity, ASTM D257, Ohm.cm	1 x 10 <sup>16</sup>
Dielectric constant, 25 °C, ASTM D150	2.7



**Chemtools P/L**

Unit 4, 3 Pullman Place  
Emu Plains, NSW 2750

Phone: 02 4735 3126

Fax: 02 4735 3746

[info@chemtools.com.au](mailto:info@chemtools.com.au)

[www.chemtools.com.au](http://www.chemtools.com.au)

# 8406 Wicking Grade

## Technical Data Sheet

### APPLICATION INSTRUCTIONS:

- All surfaces must be clean, dry, dust and grease free. Best result will be achieved with surfaces that have been lightly abraded immediately prior to bonding.
- If using accelerator apply to one component surface only. Apply thin film of adhesive to the other surface and bring the pieces together immediately. Hold for few seconds without disturbing the joints.
- When bonding "O" rings, cut a fresh surface onto each end of the rubber to gain the best possible strength.

### PACKAGING:

Available Size	Part Number
20g	8406-20
50g	8406-50
500g	8406-500

**PRECAUTIONS:** This product capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

**Warranty:** All products purchased from or supplied by ChemTools are subject to terms and conditions set out in the contract. ChemTools warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by ChemTools is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. ChemTools makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

**Date of issue: July 2009**



**Chemtools P/L**

Unit 4, 3 Pullman Place  
Emu Plains, NSW 2750

**Phone:** 02 4735 3126

**Fax:** 02 4735 3746

[info@chemtools.com.au](mailto:info@chemtools.com.au)

[www.chemtools.com.au](http://www.chemtools.com.au)