

MBP

Matt Black Paint

MBP is a quick drying, high quality, universal spray paint based on alkyd resins. It exhibits excellent coverage and hardness characteristics and is ideally suited for use in manufacturing, repair and for home/workshop use.

- Excellent adhesion to bare metal; suitable for a variety of applications
- Fast drying with high opacity; excellent coverage and good final hardness
- Very good resistance to water & external conditions
- Very good resistance to petrol and other solvents

Typical Properties

Net Volume:	400ml
Net Weight:	300g
Gloss:	Angle of 25 to 60°
Coverage:	1.25-1.75 m ² (layer 25-30μ)
Drying time:	3-5 minutes (dust free) 10-15 mins (touch dry) 2 hrs (fully dry)
Maximum Operating Temperature:	110°C

<u>Description</u>	<u>Packaging</u>	<u>Order Code</u>	<u>Shelf Life</u>
Matt Black Paint	400ml aerosol	MBP400	24 Months

Directions for Use

- Ensure that surface is dry, smooth and free from dust and grease
- To test, paint a sample panel in advance. Check synthetic and plastic substrates for adhesion and compatibility. For plastics such as PP and EPDM, a primer coat should be applied first
- Shake the spray-can well for at least 2 minutes and at intervals during use
- Spray (holding the aerosol vertical) at a distance of 25-30 cm from the object to be painted. Best results are obtained by applying several thin coats rather than one single thick coat
- Wait a few minutes, with a maximum of 30 minutes, between the application of each layer
- After use, clear the valve by spraying with the can inverted
- If repainting is necessary, this should be after 24 hours
- Drying of the synthetic paint depends on the thickness of the layer and the ambient temperature

Revision 1: Apr 2014

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,
Ashby de la Zouch,
Leicestershire LE65 1JR
T +44 (0)1530 419 600
F +44 (0)1530 416 640
BS EN ISO 9001:2008
Certificate No. FM 32082