



Loctite UK Limited, Watchmead,
Welwyn Garden City, Herts, AL7 1JB
Technical Services Tel: (01707) 358888
Customer Services Tel: (01707) 358844

Technical Data Sheet Product 243

Worldwide Version, October 1995

PRODUCT DESCRIPTION

LOCTITE® Product 243 is a single component anaerobic threadlocking material, which is thixotropic and develops medium strength. The product cures when confined in the absence of air between close fitting metal surfaces and is particularly suitable for less active substrates such as stainless steel and plated surfaces.

TYPICAL APPLICATIONS

Prevents loosening and leakage of threaded fasteners. Particularly suitable for applications such as pump or motor mounting bolts, engine rocker nuts or equipment housing screws, where disassembly with hand tools is required for servicing.


PROPERTIES OF UNCURED MATERIAL

| | Value | Typical Range |
|---|-----------------------------------|-----------------|
| Chemical Type | Dimethacrylate Ester | |
| Appearance | Opaque Blue Fluorescent Liquid | |
| Specific Gravity @ 25°C | 1.08 | |
| Viscosity @ 25°C, mPa.s (cP) | | |
| Brookfield RVT | | |
| Spindle 3 @ 2.5 rpm | 12,000 | 6,000 to 18,000 |
| @ 20 rpm | 2,250 | 1,500 to 3,000 |
| DIN 54453, MV | | |
| D = 129 s ⁻¹ after t=180secs | 350 | 250 to 500 |
| Flash Point (TCC), °C | >93 | |

TYPICAL CURING PERFORMANCE


Cure speed vs. substrate

The rate of cure will depend on substrate used. The graph below shows the breakaway strength developed with time on M10 steel nuts and bolts compared to different materials and tested according to ISO 10964.




Cure speed vs. bond gap

The rate of cure will depend on the bondline gap. Gaps in threaded fasteners depend on thread type, quality and size. The following graph shows shear strength developed with time on steel pins and collars at different controlled gaps and tested according to ISO 10123.




Cure speed vs. temperature

The rate of cure will depend on the ambient temperature. Graph below shows the breakaway strength developed with time at different temperatures on M10 steel nuts and bolts and tested according to ISO 10964.



Cure speed vs. activator

Where cure speed is unacceptably long, or large gaps are present, applying activator to the surface will improve cure speed. The graph below shows breakaway strength developed with time using ACTIVATOR N and T on M10 Zinc Dichromate steel nuts & bolts and tested according to ISO 10964.



TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

| | |
|---|-----------------------|
| Coefficient of thermal expansion, ASTM D696, K ⁻¹ | 80 x 10 ⁻⁶ |
| Coefficient of thermal conductivity, ASTM C177, W.m ⁻¹ K ⁻¹ | 0.1 |
| Specific Heat, kJ.kg ⁻¹ K ⁻¹ | 0.3 |

NOT FOR PRODUCT SPECIFICATIONS.

THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.

PLEASE CONTACT LOCTITE CORPORATION QUALITY DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT.

ROCKY HILL, CT FAX: +1 (860)-571-5473

DUBLIN, IRELAND FAX: +353-(1)-451-9959

PERFORMANCE OF CURED MATERIAL

(After 24 hr at 22°C on M10 steel nuts & bolts)


| | Typical | |
|---|-------------|--------------------------|
| | Value | Range |
| Breakaway Torque, ISO 10964 (4.3), N.m (lb.in) | 20 (180) | 15 to 25 (130 to 220) |
| Prevail Torque, ISO 10964 (4.5), N.m (lb.in) | 7 (62) | 4 to 10 (35 to 88) |
| Breakloose Torque, DIN 54454, N.m (lb.in) | 24 (210) | 14 to 34 (120 to 300) |
| Max. Prevail Torque, DIN 54454, N.m (lb.in) | 24 (210) | 14 to 34 (120 to 300) |

TYPICAL ENVIRONMENTAL RESISTANCE

Test Procedure : Breakloose Torque, DIN 54454
 Substrate: M10 Zinc Phosphate Nuts&Bolts
 Cure procedure: 1 week at 22°C


Hot Strength

Tested at temperature.



Heat Ageing

Aged at temperature indicated and tested at 22°C.



Chemical / Solvent Resistance

Aged under conditions indicated and tested at 22°C.

| Solvent | Temp. | % Initial Strength retained at | | | |
|------------------------|-------|--------------------------------|--------|---------|---------|
| | | 100 hr | 500 hr | 1000 hr | 5000 hr |
| Motor Oil | 125°C | 95 | 95 | 95 | 95 |
| Leaded Petrol | 22°C | 100 | 100 | 95 | 95 |
| Brake Fluid | 22°C | 100 | 100 | 100 | 100 |
| Water/Glycol (50%/50%) | 87°C | 95 | 80 | 80 | 80 |
| Ethanol | 22°C | 100 | 85 | 85 | 85 |
| Acetone | 22°C | 100 | 100 | 85 | 85 |

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidising materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

Directions for use

For best performance surfaces should be clean and free of grease. Product should be applied to the bolt in sufficient quantity to fill all engaged threads. This product performs best in thin bond gaps, (0.05mm). Very large thread sizes may create large gaps which will affect cure speed and strength. This product is designed to give controlled friction, (torque/tension ratio), during assembly. In critical tightening applications this ratio should be confirmed.

Storage

Product shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C to 28°C (46°F to 82°F) unless otherwise labelled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container. For further specific shelf life information, contact your local Technical Service Centre.

Data Ranges

The data contained herein may be reported as a typical value and/or range (based on the mean value ±2 standard deviations). Values are based on actual test data and are verified on a periodic basis.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Loctite Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loctite Corporation's products. Loctite Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a licence under any Loctite Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.