

STP Foam 2-in-1

Technical Data Sheet

Technical Data Sheet

Product name:	STP Foam 2-in-1	Creation date: 28 Aug 2015	Version:	1.2
Sales code:	32477 -32478		Replaces:	1.0

Section 1: General description

Mono component foam which expands and hardens with ambient humidity. This foam does not contain isocyanate has a low post expansion and high elasticity. Professional quality, convenient for all common used substrates in constructions.

The aerosol has a remarkable valve system that allows manual application as well as the use of an application gun.

Section 2: Features

- 0 % isocyanantes.(well below the target stipulated by directive EU 67/548/CE).
- Excellent insulation due to the high density.
- Appropriate for sealing, insulating, filling and fixing.
- The cured foam can be either covered with a filler-primer or straight painted.
- Excellent adhesion to all common construction materials.
- Exercises limited pressure and does not deform the supports.
- Manual application for the filling of cavities.
- The aerosol fits on an application gun for precise dosing application.
- Excellent thermal and acoustic insulation properties.

Section 3: Applications

Filling of all kind of cavities in a building construction. Insulation of conduits. Thermal and acoustic insulations Fixation of building components. Modeling.

Section 4: Directions

Manual use:

- Shake well.
- Click/turn the manual dispensing tube with trigger, on the valve.
- Humidify the surfaces to be treated slightly.

www.crcind.com



STP Foam 2-in-1

Technical Data Sheet

• Hold the can upside down. Place a finger on the trigger on each side of the dispensing tube and activate by pressing the trigger straight down(do not tilt).

Use with the application gun:

- Shake well.
- Screw the aerosol on the gun.
- Humidify the surfaces to be treated slightly.
- Regulate the flow rate with the throttling nut on the gun.
- After removal of an empty aerosol, clean the gun with CRC PU Foam Cleaner.

Note: Clean spoilage of non cured product immediately with CRC PU Foam Cleaner. Cured product only allows mechanical removal.

A safety data sheet (MSDS) according to EU directive 91/155/EEC and amendments is available for all CRC products.

Section 5: Typical product data (without propellant)

Color	: White		
Fire reaction class	: B3	DIN 4102-1	
Ambit application temperature	$: 0^{\circ}C \text{ to } +35^{\circ}C$		
Maximal gap filling	: 50%		
Drying time	: to touch 15 min	FEICA TM 1014	
	to be cut 60 min	FEICA TM 1005	
	full curing : 24 hours		
Expanded volume	: a 500 ml aerosol produces	FEICA TM 1003	
•	10 liters when applied manual		
	15 liters when applied with a gun		
:	a 750 ml aerosol produces	FEICA TM 1003	
	15 liters when applied	5 liters when applied manual	
	22 liters when applied	22 liters when applied with a gun	
Thermal conductivity	: 0,036 W/m.K	EN 12667	
Tensile strength	: applied manual : 87 kPa	ISO 527	
e e e e e e e e e e e e e e e e e e e	applied by gun : 38 kPa		
Elongation at break	: applied manual : 13 %	ISO 527	
-	applied by gun : 12 %		
Temperature resistance	: permanent -20° C to $+90^{\circ}$ C		
•	temporarily -20°C to 130°C		



STP Foam 2-in-1

Technical Data Sheet

Conservation and storage

: At a temperature between 5°C and 25°C Straight up, 9 months in the original closed packaging in a fresh and dry environment.

Section 6: Packaging

Aerosol	12x500 ML	ref	32477
Aerosol	12x750 ML	ref	32478

All statements in this publication are based on service experience and/or laboratory testing. Because of the wide variety of equipment and conditions and the unpredictable human factors involved, we recommend that our products be tested on-the-job prior to use. All information is given in good faith but without warranty neither expressed nor implied. This Technical Data Sheet may already have been revised at this moment for reason such as legislation, availability of components and newly acquired experiences. The latest and only valid version of this Technical Data Sheet will be sent to you upon simple request or can be found on our website: www.crcind.com. We recommend you to register on this website for this product so you will be able to receive any future updated version automatically.