

MG Chemicals UK Limited

Version No: A-2.02

Safety Data Sheet (Conforms to Regulation (EU) No 2015/830)

Issue Date:13/05/2019 Revision Date: 18/03/2020 L.REACH.GBR.EN

SECTION 1 IDENTIFICATION OF THE SUBSTANCE / MIXTURE AND OF THE COMPANY / UNDERTAKING

1.1. Product Identifier

Product name	9200FR-A
Synonyms	SDS Code: 9200FR-Part A, 9200FR-25ML, 9200FR-50ML
Other means of identification	Flame Retardant Structural Epoxy Adhesive (Part A)

1.2. Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	epoxy resine for use with hardeners
Uses advised against	Not Applicable

1.3. Details of the supplier of the safety data sheet

Registered company name	MG Chemicals UK Limited	MG Chemicals (Head office)
Address	Hearne House, 23 Bilston Street, Sedgely Dudley DY3 1JA United Kingdom	9347 - 193 Street Surrey V4N 4E7 British Columbia Canada
Telephone	+(44) 1663 362888	+(1) 800-201-8822
Fax	Not Available	+(1) 800-708-9888
Website	Not Available	www.mgchemicals.com
Email	sales@mgchemicals.com	Info@mgchemicals.com

1.4. Emergency telephone number

Association / Organisation	Verisk 3E (Access code: 335388)	Not Available
Emergency telephone numbers	+(44) 20 35147487	Not Available
Other emergency telephone numbers	+(0) 800 680 0425	Not Available

SECTION 2 HAZARDS IDENTIFICATION

2.1. Classification of the substance or mixture

on according to () No 1272/2008 [CLP] ^[1]	H411 - Chronic Aquatic Hazard Category 2, H302 - Acute Toxicity (Oral) Category 4, H315 - Skin Corrosion/Irritation Category 2, H319 - Eye Irritation Category 2, H361 - Reproductive Toxicity Category 2, H317 - Skin Sensitizer Category 1
Legend:	1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

2.2. Label elements

Hazard pictogram(s)	
---------------------	--

SIGNAL WORD WARNING

Hazard statement(s)

H411	Toxic to aquatic life with long lasting effects.
H302	Harmful if swallowed.
H315	Causes skin irritation.
H319	Causes serious eye irritation.
H361	Suspected of damaging fertility or the unborn child.
H317	May cause an allergic skin reaction.

EUH205	Conta

Contains epoxy constituents. May produce an allergic reaction.

Precautionary statement(s) Prevention

······································		
P201	Obtain special instructions before use.	
P280	Wear protective gloves/protective clothing/eye protection/face protection.	
P261	Avoid breathing mist/vapours/spray.	
P270	Do not eat, drink or smoke when using this product.	
P273	Avoid release to the environment.	
P272	Contaminated work clothing should not be allowed out of the workplace.	

Precautionary statement(s) Response

P308+P313	IF exposed or concerned: Get medical advice/ attention.
P302+P352	IF ON SKIN: Wash with plenty of water and soap.
P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
P333+P313	If skin irritation or rash occurs: Get medical advice/attention.
P337+P313	If eye irritation persists: Get medical advice/attention.
P362+P364	Take off contaminated clothing and wash it before reuse.
P391	Collect spillage.
P301+P312	IF SWALLOWED: Call a POISON CENTER/doctor/physician/first aider/if you feel unwell.
P330	Rinse mouth.

Precautionary statement(s) Storage

P405 Store locked up.

Precautionary statement(s) Disposal

P501 Di

Dispose of contents/container in accordance with local regulations.

2.3. Other hazards

REACh - Art.57-59: The mixture does not contain Substances of Very High Concern (SVHC) at the SDS print date.

SECTION 3 COMPOSITION / INFORMATION ON INGREDIENTS

3.1.Substances

See 'Composition on ingredients' in Section 3.2

3.2.Mixtures

1.CAS No 2.EC No 3.Index No 4.REACH No	%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP]
1.28064-14-4 2.Not Available 3.Not Available 4.Not Available	33	bisphenol F glycidyl ether/ formaldehyde copolymer	Skin Corrosion/Irritation Category 2, Eye Irritation Category 2, Chronic Aquatic Hazard Category 2, Skin Sensitizer Category 1; H315, H319, H411, H317, EUH205, EUH019 ^[1]
1.21645-51-2 2.244-492-7 3.Not Available 4.01-2119529246-39-XXXX	20	aluminium hydroxide	Eye Irritation Category 2; H319, EUH066 ^[1]
1.68333-79-9 2.269-789-9 3.Not Available 4.01-2120090300-70-XXXX	19	ammonium polyphosphate	Chronic Aquatic Hazard Category 4; H413 ^[1]
1.1675-54-3 2.216-823-5 3.603-073-00-2 603-074-00-8 4.01-2119456619-26-XXXX	19	bisphenol A diglycidyl ether	Eye Irritation Category 2, Skin Sensitizer Category 1, Skin Corrosion/Irritation Category 2; H319, H317, H315 ^[2]
1.12767-90-7 2.215-566-6 3.Not Available 4.01-0000016699-53- XXXX 01-2119691658-19- XXXX 01-2120773328-46-XXXX	6	zinc borate	Eye Irritation Category 2, Chronic Aquatic Hazard Category 1, Acute Aquatic Hazard Category 1, Reproductive Toxicity Category 1B; H319, H410, H400, H360 ^[1]
1.60506-81-2 2.262-270-8 3.Not Available 4.01-2119980666-22-XXXX	2	dipentaerythritol pentaacrylate	Eye Irritation Category 2, Chronic Aquatic Hazard Category 3, Skin Sensitizer Category 1; H319, H412, H317 ^[1]
Legend:	1. Classified available	by Chemwatch; 2. Classification drawn	n from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L * EU IOELVs

SECTION 4 FIRST AID MEASURES

4.1. Description of first aid measures

Eye Contact	 If this product comes in contact with the eyes: Wash out immediately with fresh running water. Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids. Seek medical attention without delay; if pain persists or recurs seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.
Skin Contact	 If skin contact occurs: Immediately remove all contaminated clothing, including footwear. Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation.
Inhalation	 If fumes, aerosols or combustion products are inhaled remove from contaminated area. Other measures are usually unnecessary.
Ingestion	 IF SWALLOWED, REFER FOR MEDICAL ATTENTION, WHERE POSSIBLE, WITHOUT DELAY. For advice, contact a Poisons Information Centre or a doctor. Urgent hospital treatment is likely to be needed. In the mean time, qualified first-aid personnel should treat the patient following observation and employing supportive measures as indicated by the patient's condition. If the services of a medical officer or medical doctor are readily available, the patient should be placed in his/her care and a copy of the SDS should be provided. Further action will be the responsibility of the medical specialist. If medical attention is not available on the worksite or surroundings send the patient to a hospital together with a copy of the SDS. Where medical attention is not immediately available or where the patient is more than 15 minutes from a hospital or unless instructed otherwise: INDUCE vomiting with fingers down the back of the throat, ONLY IF CONSCIOUS. Lean patient forward or place on left side (head-down position, if possible) to maintain open airway and prevent aspiration. NOTE: Wear a protective glove when inducing vomiting by mechanical means.

4.2 Most important symptoms and effects, both acute and delayed

See Section 11

4.3. Indication of any immediate medical attention and special treatment needed

As in all cases of suspected poisoning, follow the ABCDEs of emergency medicine (airway, breathing, circulation, disability, exposure), then the ABCDEs of toxicology (antidotes, basics, change absorption, change distribution, change elimination).

For poisons (where specific treatment regime is absent):

BASIC TREATMENT

- Establish a patent airway with suction where necessary.
- Watch for signs of respiratory insufficiency and assist ventilation as necessary.
- Administer oxygen by non-rebreather mask at 10 to 15 L/min.
- Monitor and treat, where necessary, for pulmonary oedema.
- Monitor and treat, where necessary, for shock.
- Anticipate seizures.
- DO NOT use emetics. Where ingestion is suspected rinse mouth and give up to 200 ml water (5 ml/kg recommended) for dilution where patient is able to swallow, has a strong gag reflex and does not drool.

ADVANCED TREATMENT

- + Consider orotracheal or nasotracheal intubation for airway control in unconscious patient or where respiratory arrest has occurred.
- Positive-pressure ventilation using a bag-valve mask might be of use.
- Monitor and treat, where necessary, for arrhythmias.
- Start an IV D5W TKO. If signs of hypovolaemia are present use lactated Ringers solution. Fluid overload might create complications.
- Drug therapy should be considered for pulmonary oedema.
- + Hypotension with signs of hypovolaemia requires the cautious administration of fluids. Fluid overload might create complications.
- Treat seizures with diazepam.
- Proparacaine hydrochloride should be used to assist eye irrigation.
- BRONSTEIN, A.C. and CURRANCE, P.L.

EMERGENCY CARE FOR HAZARDOUS MATERIALS EXPOSURE: 2nd Ed. 1994

for phosphate salts intoxication:

- All treatments should be based on observed signs and symptoms of distress in the patient. Consideration should be given to the possibility that overexposure to materials other than this product may have occurred.
- Ingestion of large quantities of phosphate salts (over 1.0 grams for an adult) may cause an osmotic catharsis resulting in diarrhoea and probable abdominal cramps. Larger doses such as 4-8 grams will almost certainly cause these effects in everyone. In healthy individuals most of the ingested salt will be excreted in the faeces with the diarrhoea and, thus, not cause any systemic toxicity. Doses greater than 10 grams hypothetically may cause systemic toxicity.
- Treatment should take into consideration both anionic and cation portion of the molecule.
- + All phosphate salts, except calcium salts, have a hypothetical risk of hypocalcaemia, so calcium levels should be monitored.

Treat symptomatically

SECTION 5 FIREFIGHTING MEASURES

5.1. Extinguishing media

Page 4 of 20

9200FR-A Flame Retardant Structural Epoxy Adhesive (Part A)

- Foam.
- Dry chemical powder.
- BCF (where regulations permit). Carbon dioxide.
- Water spray or fog Large fires only.

5.2. Special hazards arising from the substrate or mixture

Fire Incompatibility	Avoid contamination with oxidising agents i.e. nitrates, oxidising acids, chlorine bleaches, pool chlorine etc. as ignition may result

5.3. Advice for firefighters

Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. May be violently or explosively reactive. Wear full body protective clothing with breathing apparatus. Prevent, by any means available, spillage from entering drains or water course. Fight fire from a safe distance, with adequate cover. If safe, switch off electrical equipment until vapour fire hazard removed. Use water delivered as a fine spray to control the fire and cool adjacent area. Avoid spraying water onto liquid pools. Do not approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. If safe to do so, remove containers from path of fire.
Fire/Explosion Hazard	 Combustible. Slight fire hazard when exposed to heat or flame. Heating may cause expansion or decomposition leading to violent rupture of containers. On combustion, may emit toxic fumes of carbon monoxide (CO). May emit acrid smoke. Mists containing combustible materials may be explosive. Combustion products include: carbon dioxide (CO2) aldehydes nitrogen oxides (NOx) phosphorus oxides (POx) other pyrolysis products typical of burning organic material.

SECTION 6 ACCIDENTAL RELEASE MEASURES

6.1. Personal precautions, protective equipment and emergency procedures

See section 8

6.2. Environmental precautions

See section 12

6.3. Methods and material for containment and cleaning up

Major Spills Environmental hazard - contain spillage. Chemical Class: phenols and cresols For release onto land: recommended sorbents listed in order of priority. COLLECTION SORBENT TYPE RANK APPLICATION COLLECTION LAND SPILL - SMALL cross-linked polymer - particulate 1 shovel cross-linked polymer - pillow 1 throw wood fiber - pillow 1 throw gamed glass - pillow 2 shovel		
cross-linked polymer - pillow 2 throw 2 sorbent clay - particulate 3 blower 2	ION Shovel Shiploader Skiploader Skiploader	LIMITATIONSR, W, SSR, DGC, RTR, P, DGC, RTR, W, P, DGCR, I, PR, W, P, DGCR, W, SSR, DGC, RTR, I, PR, SS, DGCR, W, P, DGC

Page 5 of 20

9200FR-A Flame Retardant Structural Epoxy Adhesive (Part A)

expanded moneral - particulate	4	blower	skiploader	R, I, W, P, DGC	
Legend					
DGC: Not effective where ground cover is dense					
R; Not reusable					
I: Not incinerable					
P: Effectiveness reduced when rainy					
RT:Not effective where terrain is rugged					
SS: Not for use within environmentally sensitive sites					
W: Effectiveness reduced when windy					
Reference: Sorbents for Liquid Hazardous Substance Clea	up and Control	;			
R.W Melvold et al: Pollution Technology Review No. 150: No.	•				
Industrial spills or releases of reactive diluents are infrequer	and generally	contained. If a la	rge spill does occur, t	he material should be captured,	
collected, and reprocessed or disposed of according to appl	cable governm	ental requiremen	its.		
An approved air-purifying respirator with organic-vapor canis	ter is recomme	nded for emerge	ncy work.		
Moderate hazard.		-			
 Clear area of personnel and move upwind. 					
Alert Fire Brigade and tell them location and nature of hazard.					
Wear breathing apparatus plus protective gloves.					
 Prevent, by any means available, spillage from entering 	Prevent, by any means available, spillage from entering drains or water course.				
No smoking, naked lights or ignition sources.					
 Increase ventilation. 					
 Stop leak if safe to do so. 					
 Contain spill with sand, earth or vermiculite. 					
 Collect recoverable product into labelled containers for 	recycling.				
 Absorb remaining product with sand, earth or vermiculit 	э.				
 Collect solid residues and seal in labelled drums for dis 	oosal.				
 Wash area and prevent runoff into drains. 					
If contamination of drains or waterways occurs, advise e	mergency servi	ces.			

6.4. Reference to other sections

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 HANDLING AND STORAGE

7.1. Precautions for safe handling

 Most acrylic monomers have low viscasity therefore pouring, material transfer and processing of these materials do not necessitate heading. Viscous monomers may require heading to facilitate handling. To facilitate product transfer from original containers, product must be heated to no more than 60 deg. C. (140 F), for not more than 24 hours. Do NOT use localised heat sources such as band heaters to heat 'melt product. Do NOT use steam. Hot boxes or hot rooms are recommended for heating/ melting material. The hot box or hot room should be set a maximum temperature of 60 deg. C. (140 F). Do NOT overheat - this may compromise product quality and /or result in product degradation. If product freezes, heat as indicated above and mix gently to redistribute the inhibitor. Product should be consumed in its entirety after heating/ melting; avoid multiple reheats' which may affect product quality or result in product degradation. Product should be packaged with inhibitor(s). Unless inhibited, product may polymerise, raising temperature and pressure, possibly rupturing container. Check inhibitor level periodically, adding to bulk material if needod. In addition, the products inhibitor(s) require the presence of dissolved oxygen. Maintain, at a minimum, the original headspace in the product solution greater than 0 deg. C. (32 F), if no freezing point available and below 38 deg. C (100 F). Store product indoors at temperatures greater than the product's final biots', sparks, open flame, strong oxidisers, radiation and other initiators. Prevent contamination by foreign materials. Prevent containers in a property vented storage area away from heat, sparks, open flame, strong oxidisers, radiation and other initiators. Prevent containiation by divergin materials. Prevent containing holics and limit storage time. Unless specified elsewhere, shelf-life is 6 months from receipt. Avoid all personal contact,
See section 5
 Store in original containers. Keep containers securely sealed. Store in a cool, dry, well-ventilated area. Store away from incompatible materials and foodstuff containers. Protect containers against physical damage and check regularly for leaks. Observe manufacturer's storage and handling recommendations contained within this SDS.

Suitable container	Metal can or drum Deducing a programmended by many factures
Suitable container	 Packaging as recommended by manufacturer. Check all containers are clearly labelled and free from leaks.
Storage incompatibility	 Check all containers are clearly labelled and the from leaks. Epoxides: are highly reactive with acids, bases, and oxidising and reducing agents. react, possibly violently, with anhydrous metal chlorides, ammonia, amines and group 1 metals. may polymerise in the presence of peroxides or heat - polymerisation may be violent may react, possibly violently, with water in the presence of acids and other catalysts. Phenols are incompatible with strong reducing substances such as hydrides, nitrides, alkali metals, and sulfides. Avoid use of aluminium, copper and brass alloys in storage and process equipment. Heat is generated by the acid-base reaction between phenols and bases. Phenols are sufforated very readity (for example, by concentrated sulfuric acid at room temperature), these reactions generate heat. Phenols are nitrated very rapidly, even by dilute nitric acid. Nitrated phenols often explode when heated. Many of them form metal salts that tend toward detonation by rather mild shock. for multifunctional acrylates: Avoid exposure to free radical initiators (peroxides, persulfates), iron, rust, oxidisers, and strong acids and strong bases. Avoid heat, flame, sunlight, X-rays or ultra-violet radiation. Storage beyond expiration date, may initiate polymerisation. Polymerisation of large quantities may be violent (even explosive) Glycidyl ethers: may polymerise in contact with heat, organic and inorganic free radical producing initiators may polymerise with evolution of heat in contact with noxidisers, strong acids, bases and amines react violently with strong oxidisers, permanganates, peroxides, acyl halides, alkalis, ammonium persulfate, bromine dioxide attack some forms of plastics, coatings, and rubber Reactive diluents are stable under recommended storage conditions, but can decompose at elevated tempera

7.3. Specific end use(s)

See section 1.2

SECTION 8 EXPOSURE CONTROLS / PERSONAL PROTECTION

8.1. Control parameters

DERIVED NO EFFECT LEVEL (DNEL) Not Available

PREDICTED NO EFFECT LEVEL (PNEC)

Not Available

OCCUPATIONAL EXPOSURE LIMITS (OEL)

INGREDIENT DATA

Source	Ingredient	Material name	TWA	STEL	Peak	Notes
Not Available						

EMERGENCY LIMITS

EMERGENCI EIMITS					
Ingredient	Material name	TEEL-1	TEEL-2	TEEL-3	
bisphenol F glycidyl ether/ formaldehyde copolymer	Phenol, polymer with formaldehyde, oxiranylmethyl ether	30 mg/m3	330 mg/m3	2,000 mg/m3	
aluminium hydroxide	Aluminum hydroxide		8.7 mg/m3	73 mg/m3	440 mg/m3
bisphenol A diglycidyl ether	Bisphenol A diglycidyl ether		39 mg/m3	430 mg/m3	2,600 mg/m3
bisphenol A diglycidyl ether	Epoxy resin includes EPON 1001, 1007, 820, ERL-2795	Epoxy resin includes EPON 1001, 1007, 820, ERL-2795			5,900 mg/m3
Ingredient	redient Original IDLH Revised IDLH				
bisphenol F glycidyl ether/ formaldehyde copolymer	Not Available				
aluminium hydroxide	Not Available	Not Available			
ammonium polyphosphate	Not Available	Not Available			
bisphenol A diglycidyl ether	Not Available	Not Available			
zinc borate	Not Available	Not Available			
dipentaerythritol pentaacrylate	Not Available Not Available				

MATERIAL DATA

CEL TWA: 1 mg/m3 [compare WEEL-TWA* for multifunctional acrylates (MFAs)]

(CEL = Chemwatch Exposure Limit)

Exposure to MFAs has been reported to cause contact dermatitis in humans and serious eye injury in laboratory animals. Exposure to some MFA-resin containing aerosols has also been reported to cause dermatitis. As no assessment of the possible effects of long-term exposure to aerosols was found, a conservative Workplace Environmental Exposure Level (WEEL) was suggested by the American Industrial Hygiene Association (AIHA).

For epichlorohydrin

Odour Threshold Value: 0.08 ppm

Odour Threshold Value: 0.08 ppm NOTE: Detector tubes for epichlorohydrin, measuring in excess of 5 ppm, are commercially available. Exposure at or below the recommended TLV-TWA is thought to minimise the potential for adverse respiratory, liver, kidney effects. Epichlorohydrin has been implicated as a human skin sensitiser, hence individuals who are hypersusceptible or otherwise unusually responsive to certain chemicals may NOT be adequately protected from adverse health effects. Odour Safety Factor (OSF) OSF=0.54 (EPICHLOROHYDRIN)

8.2. Exposure controls

0.2. Exposure controls					
	Engineering controls are used to remove a hazard or place a barrier between the worker and the hazard. Well-designed engineering controls can be highly effective in protecting workers and will typically be independent of worker interactions to provide this high level of protection. The basic types of engineering controls are: Process controls which involve changing the way a job activity or process is done to reduce the risk. Enclosure and/or isolation of emission source which keeps a selected hazard 'physically' away from the worker and ventilation that strategically 'adds' an 'removes' air in the work environment. Ventilation can remove or dilute an air contaminant if designed properly. The design of a ventilation system must match the particular process and chemical or contaminant in use. Employers may need to use multiple types of controls to prevent employee overexposure. General exhaust is adequate under normal operating conditions. Local exhaust ventilation may be required in specific circumstances. If risk of overexposure exists, wear approved respirator. Correct fit is essential to obtain adequate protection. Provide adequate ventilation in warehouse or close storage areas. Air contaminants generated in the workplace possess varying 'escape' velocities which, in turn, determine the 'capture velocities' of fres circulating air required to effectively remove the contaminant. Type of Contaminant: Air Speed:				
	solvent, vapours, degreasing etc., evaporating from tank (in still air).				
	aerosols, fumes from pouring operations, intermittent container filling, low speed conveyer trans acid fumes, pickling (released at low velocity into zone of active generation)	fers, welding, spray drift, plating	f/min) 0.5-1 m/s (100-200 f/min.)		
8.2.1. Appropriate engineering controls	direct spray, spray painting in shallow booths, drum filling, conveyer loading, crusher dusts, gas into zone of rapid air motion)	discharge (active generation	1-2.5 m/s (200-500 f/min.)		
	grinding, abrasive blasting, tumbling, high speed wheel generated dusts (released at high initial rapid air motion).	velocity into zone of very high	2.5-10 m/s (500-2000 f/min.)		
	Within each range the appropriate value depends on:				
	Lower end of the range	Upper end of the range			
	1: Room air currents minimal or favourable to capture	1: Disturbing room air currents			
	2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity			
	3: Intermittent, low production.	3: High production, heavy use			
	4: Large hood or large air mass in motion	4: Small hood-local control only			
	square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for example, should be a minimum of 1-2 m/s (200-400 f/min) extraction of solvents generated in a tank 2 meters distant from the extraction point. Other mechanical considerations, producing performance deficits the extraction apparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction systems are installed or used.				
8.2.2. Personal protection					
Eye and face protection	 Safety glasses with side shields. Chemical goggles. Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59], [AS/NZS 1336 or national equivalent] 				
Skin protection	See Hand protection below				
Hands/feet protection	See Hand protection below NOTE: The material may produce skin sensitisation in predisposed individuals. Care must be taken, when removing gloves and other protective equipment, to avoid all possible skin contact. Contaminated leather items, such as shoes, belts and watch-bands should be removed and destroyed. The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be observed when making a final choice. Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 				

	240 minutes according to EN 374, AS/N	ZS 2161.10.1 or national equivalent) is recommended.			
	-	ed, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according			
	to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.				
	 Some glove polymer types are less 	s affected by movement and this should be taken into account when considering gloves for long-term			
	use.				
	Contaminated gloves should be re				
	As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 480 min				
	Good when breakthrough time > 20 min				
	Fair when breakthrough time < 20				
	Poor when glove material degrade				
	For general applications, gloves with a thickness typ	pically greater than 0.35 mm, are recommended.			
	It should be emphasised that glove thickness is not	necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of			
		n of the glove material. Therefore, glove selection should also be based on consideration of the task			
	requirements and knowledge of breakthrough times				
		ve manufacturer, the glove type and the glove model. Therefore, the manufacturers' technical data			
	should always be taken into account to ensure select	loves of varying thickness may be required for specific tasks. For example:			
		r less) may be required where a high degree of manual dexterity is needed. However, these gloves are			
		n and would normally be just for single use applications, then disposed of.			
	 Thicker gloves (up to 3 mm or mo 	re) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is			
	abrasion or puncture potential				
	-	ng gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is			
	recommended.				
	When handling liquid-grade epoxy resins wear cher The performance, based on breakthrough times ,of:				
	Ethyl Vinyl Alcohol (EVAL laminate				
	Butyl Rubber ranges from exceller				
	Nitrile Butyl Rubber (NBR) from e				
	Neoprene from excellent to fair				
	 Polyvinyl (PVC) from excellent to p 	nood			
	As defined in ASTM F-739-96				
	Excellent breakthrough time > 480	i min			
	Good breakthrough time > 20 min Eair breakthrough time > 20 min				
	Fair breakthrough time < 20 min Poor glove material degradation				
		prior to making a selection of the most suitable type. Systems include both the resin and any hardener,			
	individually and collectively)				
	 DO NOT use cotton or leather (while the second secon	nich absorb and concentrate the resin), natural rubber (latex), medical or polyethylene gloves (which			
	absorb the resin).				
		aining emulsified fats and oils as these may absorb the resin; silicone-based barrier creams should be			
	reviewed prior to use.	ating the most appropriate along. It may be more effective to called a along with lower elemical			
		cting the most appropriate glove. It may be more effective to select a glove with lower chemical			
	resistance but which is replaced frequently than to s	select a more resistant alove which is reused many times			
		select a more resistant glove which is reused many times			
		select a more resistant glove which is reused many times ily recommended gloves - using the wrong gloves may increase the risk:			
	General warning: Do NOT use latex gloves! Use or	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm)			
	General warning: Do NOT use latex gloves! Use or Exposure condition	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free			
	General warning: Do NOT use latex gloves! Use or	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour)	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour)	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour)	Iv recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour)	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools,	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools,	Ily recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools,	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools,	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.)	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; <0.56 mm low tactibility ('feel'), powder free			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; <0.56 mm low tactibility ('feel'), powder free High price			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Not give adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Avoid use of ketones and acetates in wash-up solutions.			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility ('feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations Where none of this gloves ensure safe handling (for	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility (feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Avoid use of ketones and acetates in wash-up solutions.			
Body protection	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations Where none of this gloves ensure safe handling (for laminated multilayer gloves. Guide to the Classification and Labelling of UV/EB	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility (feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Avoid use of ketones and acetates in wash-up solutions.			
Body protection	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations Where none of this gloves ensure safe handling (for laminated multilayer gloves. Guide to the Classification and Labelling of UV/EB See Other protection below	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility (feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Avoid use of ketones and acetates in wash-up solutions.			
Body protection	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations Where none of this gloves ensure safe handling (for laminated multilayer gloves. Guide to the Classification and Labelling of UV/EB See Other protection below ▶ Overalls.	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility (feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Avoid use of ketones and acetates in wash-up solutions.			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations Where none of this gloves ensure safe handling (for laminated multilayer gloves. Guide to the Classification and Labelling of UV/EB See Other protection below Overalls. P.V.C. apron. 	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility (feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Avoid use of ketones and acetates in wash-up solutions.			
Body protection Other protection	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations Where none of this gloves ensure safe handling (for laminated multilayer gloves. Guide to the Classification and Labelling of UV/EB See Other protection below ▶ Overalls.	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility (feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Avoid use of ketones and acetates in wash-up solutions.			
	General warning: Do NOT use latex gloves! Use or Exposure condition Short time use; (few minutes less than 0.5 hour) Little physical stress Exposure condition Medium time use; less than 4 hours Physical stress (opening drums, using tools, etc.) Exposure condition Long time Cleaning operations Where none of this gloves ensure safe handling (for laminated multilayer gloves. Guide to the Classification and Labelling of UV/EB See Other protection below Overalls. P.V.C. apron. Barrier cream. 	Ny recommended gloves - using the wrong gloves may increase the risk: Use of thin nitrile rubber gloves: Nitrile rubber (0.1 mm) Excellent tactibility ('feel'), powder-free Disposable Inexpensive Give adequate protection to low molecular weigh acrylic monomers Use of medium thick nitrile rubber gloves Nitrile rubber, NRL (latex) free; <0.45 mm Moderate tactibility (feel'), powder-free Disposable Moderate price Gives adequate protection for most acrylates up to 4 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Nitrile rubber, NRL (latex) free; >0.56 mm low tactibility ('feel'), powder free High price Gives adequate protection for most acrylates in combination with commonly used solvents up to 8 hours Do NOT give adequate protection to low molecular weight monomers at exposures longer than 1 hour Avoid use of ketones and acetates in wash-up solutions.			

Respiratory protection

Type A Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Selection of the Class and Type of respirator will depend upon the level of breathing zone contaminant and the chemical nature of the contaminant. Protection Factors (defined as the ratio of contaminant outside and inside the mask) may also be important.

Required minimum protection factor up to 10 up to 50 up to 50 up to 100 up to 100 100+	Maximum gas/vapour concentration present in air p.p.m. (by volume) 1000 1000 5000 5000 10000	Half-face Respirator A-AUS / Class1 - Airline * - -	Full-Face Respirator - A-AUS / Class 1 - A-2 A-3 Airline**
--	---	--	--

* - Continuous Flow ** - Continuous-flow or positive pressure demand

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

Cartridge respirators should never be used for emergency ingress or in areas of unknown vapour concentrations or oxygen content.

- The wearer must be warned to leave the contaminated area immediately on detecting any odours through the respirator. The odour may indicate that the mask is not functioning properly, that the vapour concentration is too high, or that the mask is not properly fitted. Because of these limitations, only restricted use of cartridge respirators is considered appropriate.
- Cartridge performance is affected by humidity. Cartridges should be changed after 2 hr of continuous use unless it is determined that the humidity is less than 75%, in which case, cartridges can be used for 4 hr. Used cartridges should be discarded daily, regardless of the length of time used

8.2.3. Environmental exposure controls

See section 12

SECTION 9 PHYSICAL AND CHEMICAL PROPERTIES

9.1. Information on basic physical and chemical properties

Appearance	Off White		
Physical state	Liquid	Relative density (Water = 1)	1.30
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature	Not Available
Melting point / freezing point (°C)	Not Available	Viscosity (cSt)	>20.5
Initial boiling point and boiling range (°C)	>150	Molecular weight (g/mol)	Not Available
Flash point (°C)	113	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Applicable	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Available
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Partly miscible	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

9.2. Other information

Not Available

SECTION 10 STABILITY AND REACTIVITY

10.1.Reactivity	See section 7.2
10.2. Chemical stability	 Unstable in the presence of incompatible materials. Product is considered stable. Hazardous polymerisation will not occur.
10.3. Possibility of hazardous reactions	See section 7.2
10.4. Conditions to avoid	See section 7.2
10.5. Incompatible materials	See section 7.2
10.6. Hazardous decomposition products	See section 5.3

SECTION 11 TOXICOLOGICAL INFORMATION

11.1. Information on toxicological effects

Inhaled The material is not thought to produce either adverse health effects or irritation of the respiratory tract following inhalation (as classified by EC Directives using animal models). Nevertheless, adverse systemic effects have been produced following exposure of animals by at least one other route and good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting. No report of respiratory illness in humans as a result of exposure to multifunctional acrylates has been found. Similarly evidence of systemic damage does not appear to exist. In animal testing, exposure to aerosols of some reactive diluents (notably o-cresol glycidyl ether, CAS RN: 2210-79-9) has been reported to affect the adrenal gland, central nervous system, kidney, liver, ovaries, spleen, testes, thymus, and respiratory tract.

	Inhalation hazard is increased at higher temperatures. Accidental ingestion of the material may be harmful; animal experiments indicate that ingestion of less than 150 gram may be fatal or may produce serious
	damage to the health of the individual. Reactive diluents exhibit a range of ingestion hazards. Small amounts swallowed incidental to normal handling operations are not likely to cause injury. However, swallowing larger amounts may cause injury. Male rats exposed to a single oral dose of bisphenol A diglycidyl ether (BADGE) at 750, 1000, and 2000 mg/kg/day showed a significantly increase in the number of immature and maturing sperm on the testis. There were no significant differences with respect to sperm head count, sperm motility, and sperm abnormality in the BADGE treatment groups
Ingestion	Inorganic polyphosphates are used extensively in domestic and industrial products. Rats fed 10% sodium trimetaphosphate for a month exhibited transient tubular necrosis; those given 10% sodium metaphosphate exhibited growth retardation; 10% sodium hexametaphosphate produced pale and swollen kidneys. Salts of this type appear to be hydrolysed in the bowel to produce phosphoric acid and systemic acidosis may result following absorption. Higher molecular weight species, absorbed from the alimentary canal, may produce hypocalcaemic tetany due to binding of ionised calcium by the absorbed phosphate. This is reported in at least one case following ingestion of sodium tripolyphosphate. Symptoms of borate poisoning include nausea, vomiting, diarrhoea, epigastric pain. These may be accompanied headache, weakness and a distinctive red skin rash. In severe cases there may be shock, increased heart rate and the skin may appear blue. Vomiting (which may be violent) is often persistent and vomitus and faeces may contain blood. Weakness, lethargy, headache, restlessness, tremors and intermittent convulsions may also occur. Poisoning produces central nervous system stimulation followed by depression, gastrointestinal disturbance (haemorrhagic gastro-enteritis), erythematous skin eruptions (giving rise to a boiled lobster appearance) and may also involve kidneys (producing oliguria, albuminuria, anuria) and, rarely, liver (hepatomegaly, jaundice). Toxic symptoms may be delayed for several hours. Ingested borates are readily absorbed and do not appear to be metabolised via the liver. Excretion occurs mainly through the kidneys in the urine with about half excreted in the first 12 hours and the remainder over 5-12 days. Borates are exceted primarily in the urine regardless of the route of administration. The borates (tetra-, di-, meta, or ortho- salts, in contrast to perborates) once solubilised in the acid of gastric juices, cannot be distinguished from each other on chemical or toxicological grounds. In humans acute gastroenter
Skin Contact	Evidence exists, or practical experience predicts, that the material either produces inflammation of the skin in a substantial number of individuals following direct contact, and/or produces significant inflammation when applied to the healthy intact skin of animals, for up to four hours, such inflammation being present twenty-four hours or more after the end of the exposure period. Skin irritation may also be present after prolonged or repeated exposure; this may result in a form of contact dermatitis (nonallergic). The dermatitis is often characterised by skin redness (erythema) and swelling (oedema) which may progress to blistering (vesiculation), scaling and thickening of the epidermis. At the microscopic level there may be intercellular oedema of the spongy layer of the skin (spongiosis) and intracellular oedema of the epidermis. The material may accentuate any pre-existing dermatitis condition All multifunctional acrylates (MFA) produce skin discomfort and are known or suspected skin sensitisers. Aerosols generated in the industrial process are reported to produce dermatitis - vapours generated by the heat of milling may also occur in sufficient concentration to produce dermatitis. Because exposure to industrial aerosols of MFA may also include exposure to various resin systems, photo-initiators, solvents, hydrogen-transfer agents, stabilisers, surfactants, fillers and polymerisation inhibitors, toxic effects may arise due to a range of chemical actions. Bisphenol A diglycidyl ether (BADGE) may produce contact dermatitis characterised by erythema and oedema, with weeping followed by crusting and scaling. A liquid resin with a molecular weight of 350 produced severe skin irritation in rabbits when applied daily for 4 hours over 20 days. Following the initial contact there may be a discrete erythematous lesion, confined to the point of contact, which may persist for 48 hours to 10 days; the erythema may give way to a papular, vesicular rash with scaling. In animals uncured resin produces moderate ante-morte
Eye	Evidence exists, or practical experience predicts, that the material may cause eye irritation in a substantial number of individuals and/or may produce significant ocular lesions which are present twenty-four hours or more after instillation into the eye(s) of experimental animals. Repeated or prolonged eye contact may cause inflammation characterised by temporary redness (similar to windburn) of the conjunctiva (conjunctivitis); temporary impairment of vision and/or other transient eye damage/ulceration may occur. Eye contact with reactive diluents may cause slight to severe irritation with the possibility of chemical burns or moderate to severe corneal injury.
Chronic	 The contract will reactive dubelies inspire to servere initiation will the possibility of circleniate to servere contract input. Practical experience shows that skin contact with the material is capable either of inducing a sensitisation reaction in a substantial number of individuals, and/or of producing a positive response in experimental animals. Exposure to the material may cause concerns for human fertility, generally on the basis that results in animal studies provide sufficient evidence to cause a storing suspicion of impaired fertility in the absence of toxic effects, evidence of impaired fertility occurring at around the same dose levels as other toxic effects, but which are not a secondary non-specific consequence of other toxic effects. Exposure to the material may cause concerns for humans owing to possible developmental toxic effects, generally on the basis that results in appropriate other toxic effects but which are not a secondary non-specific consequence of other toxic effects. Bisphenol A diglycicly tethers (BADGEE) produce sensitisation dematitis characterised by a papular, vesicular eczerna with considerable itching of the exposure but is unlikely to become more intense. Lesions may develop a trowine tocic affects but which are not a secondary non-specific consequence of a small number of fibrosacromas in radius. Babde of the hand, the forearm and face and neck. This besion may persist for 10-14 days after withrhawal from exposure and recur immediately on re-exposure. This dermatitis may persist for longer periods following each exposure but is unlikely to buccome nore intense. Lesions may develop a torwink inclusion and acting and contact in the material is hord assifiable as to its carcinogenicity to humans'. Concern has been raised over this possible carcinogenicity because BADGE is used in epoxy resins in the lining of some tin cans for foodstuffs, and unreacted BADGE may englise. Integration shows and a stall

but not oral administration. Phenyl glycidyl ether did not induce micronuclei or chromosomal aberrations <i>in vivo</i> or chromosomal aberrations in animal cells <i>in vitro</i> . Alkyl C12 or C14 glycidyl ether did not induce DNA damage in cultured human cells or mutation in cultured animal cells. Allyl glycidyl ether
induced mutation in <i>Drosophila</i> . The glycidyl ethers were generally mutagenic to bacteria There are reports of lung damage due to excessive inhalation of alumina dust. Ingestion of large amounts of aluminium hydroxide for prolonged periods may cause phosphate depletion, especially if phosphate intake is low. This may cause loss of appetite, muscle weakness, muscular disease and even softening of the bones. These effects have not been reported in people occupationally exposed to aluminium hydroxide. On the basis, primarily, of animal experiments, concern has been expressed by at least one classification body that the material may produce carcinogenic or mutagenic effects; in respect of the available information, however, there presently exists inadequate data for making a satisfactory assessment. Bisphenol F, bisphenol A, fluorine-containing bisphenol A (bisphenol AF), and other diphenylalkanes were found to be oestrogenic in a bioassay with MCF7 human breast cancer cells in culture. Bisphenol F (4,4-dihydroxydiphenylmethane) has been reported to exhibit oestrogen agonistic properties in the uterotrophic assay. Bisphenol F (BPF) is present in the environment and as a contaminant of food. Humans may, therefore, be exposed to BP. BPF has been shown to have genotoxic and endocrine-disruptor properties in a human hepatoma cell line (HepG2), which is a model system for studies of xenobiotic toxicity. BPF was largely metabolised into the corresponding sulfate by the HepG2 cell line. BPF was metabolised into both sulfate and glucuronide by human hepatocytes, but with differences between individuals. The metabolism of BPF in both HepG2 cells and human hepatocytes suggests the existence of a detoxification pathway Bisphenol F was orally administered at doses 0, 20, 100 and 500 mg/kg per day for at least 28 days, but no clear endocrine-mediated changes were detected, and it was concluded to have no endocrine-mediated effects in young adult rats. On the other hand, the main effect of bisphenol F was concluded to be liver
albumin values were observed in the female rats given 20 mg/kg per day or higher doses of bisphenol F. Bisphenol A exhibits hormone-like properties that raise concern about its suitability in consumer products and food containers. Bisphenol A is thought to be an endocrine disruptor which can mimic oestrogen and may lead to negative health effects. More specifically, bisphenol A closely mimics the structure and function of the hormone oestradiol with the ability to bind to and activate the same oestrogen receptor as the natural hormone. Early developmental stages appear to be the period of greatest sensitivity to its effects and some studies have linked prenatal exposure to later physical and neurological difficulties. Regulatory bodies have determined safety levels for humans, but those safety levels are being questioned or are under review. A 2009 study on Chinese workers in bisphenol A factories found that workers were four times more likely to report erectile dysfunction, reduced sexual desire and overall dissatisfaction with their sex life than workers with no heightened bisphenol A exposure. Bisphenol A workers were also seven times more likely to have ejaculation difficulties. They were also more likely to report reduced sexual function within one year of beginning employment at the factory, and the higher the exposure, the more likely they were to have sexual difficulties. Bisphenol A in weak concentrations is sufficient to produce a negative reaction on the human testicle. The researchers found that a concentration equal to 2 ug/ litre of bisphenol A in the culture medium, a concentration equal to the average concentration generally found in the blood, urine and amniotic fluid of the population, was sufficient to produce the effects. The researchers believe that exposure of pregnant women to bisphenol A may be one of the causes of congenital masculinisation defects of the hypospadia and cryptorchidism types the frequency of which has doubled overall since the 70's. They also suggested that' it is also p
cancer in adults that have been observed in recent decades' One review has concluded that obesity may be increased as a function of bisphenol A exposure, which 'merits concern among scientists and public health
officials' One study demonstrated that adverse neurological effects occur in non-human primates regularly exposed to bisphenol A at levels equal to the United States Environmental Protection Agency's (EPA) maximum safe dose of 50 ug/kg/day This research found a connection between bisphenol A and interference with brain cell connections vital to memory, learning, and mood.
A further review concluded that bisphenol-A has been shown to bind to thyroid hormone receptor and perhaps have selective effects on its functions. Carcinogenicity studies have shown increases in leukaemia and testicular interstitial cell tumours in male rats. However, 'these studies have not been considered as convincing evidence of a potential cancer risk because of the doubtful statistical significance of the small differences in incidences from controls'. Another in vitro study has concluded that bisphenol A is able to induce neoplastic transformation in human breast epithelial cells.[whilst a further study concluded that maternal oral exposure to low concentrations of bisphenol A, during lactation, increases mammary carcinogenesis in a rodent model. In vitro studies have suggested that bisphenol A can promote the growth of neuroblastoma cells and potently promotes invasion and metastasis of neuroblastoma cells. Newborn rats exposed to a low-dose of bisphenol A (10 ug/kg) showed increased prostate cancer susceptibility when adults. At least one study has suggested that bisphenol A suppresses DNA methylation which is involved in epigenetic changes. Bisphenol A is the isopropyl adduct of 4,4'-dihydroxydiphenyl oxide (DHDPO). A series of DHDPO analogues have been investigated as potential oestrogen receptor/anti-tumour drug carriers in the development of a class of therapeutic drugs called 'cytostatic hormones'. Oestrogenic activity is induced with 1 to 100 mg/kg body weight in animal models. Bisphenol A sealants are frequently used in dentistry for treatment of dental pits and fissures. Samples of saliva collected from dental patients during a 1-hour period following application contain the monomer. A bisphenol-A sealant has been shown
to be oestrogenic in vitro; such sealants may represent an additional source of xenoestrogens in humans and may be the cause of additional concerns in children. Concerns have been raised about the possible developmental effects on the foetus/embryo or neonate resulting from the leaching of bisphenol A from epoxy

9200FR Flame Retardant Structural Epoxy Adhesive			IRRITATION		
(Part A)			Not Av	Not Available	
	TOXICITY			IRRITATION	
bisphenol F glycidyl ether/ formaldehyde copolymer	dermal (rat) LD50: 4000 mg/kg ^[2]			Eyes * (-) (-) Slight irritant	
	Oral (rat) LD50: 4000 mg/kg ^[2]			Skin * (-) (-) Slight irritant	
aluminium hydroxide	TOXICITY IRRITATION Oral (rat) LD50: >2000 mg/kg ^[1] Eye: no adverse effect observed (not irritating) ^[1] Skin: no adverse effect observed (not irritating) ^[1]				
ammonium polyphosphate	TOXICITY Dermal (rabbit) LD50: >3160 mg/kg ^[2]				IRRITATION Not Available
	Oral (rat) LD50: >=300-2000 mg/kg ^[1]				

1

	TOXICITY	IRRITATION	
	dermal (rat) LD50: >2000 mg/kg ^[1]	Eye (rabbit): 2 mg/24h - SEVERE	
bisphenol A diglycidyl ether	Oral (rat) LD50: >2000 mg/kg ^[1]	Eye: adverse effect observed (irritating) ^[1]	
		Skin (rabbit): 500 mg - mild	
		Skin: adverse effect observed (irritating) $^{[1]}$	
	TOXICITY	IRRITATION	
	Dermal (rabbit) LD50: >2000 mg/kg ^[1]	Eye (rabbit): mild *	
zinc borate	Oral (rat) LD50: >5000 mg/kg ^[1]	Eye: adverse effect observed (irritating) ^[1]	
		Skin: no adverse effect observed (not irritating) ^[1]	
		Skin: non-irritant *	
	TOXICITY	IRRITATION	
dipentaerythritol pentaacrylate	Oral (rat) LD50: >2000 mg/kg ^[1]	Not Available	
Legend:	Value obtained from Europe ECHA Registered Subs data extracted from RTECS - Register of Toxic Effect o	ances - Acute toxicity 2.* Value obtained from manufacturer's SDS. Unless otherwise	specified

9200FR Flame Retardant Structural Epoxy Adhesive (Part A)	Bisphenol A diglycidyl ethers (BADGEs) produce sensitisation dermatitis characterised by a papular, vesicular eczema with considerable itching of the back of the hand, the forearm and face and neck. This lesion may persist for 10-14 days after withdrawal from exposure and recur immediately on re-exposure. This dermatitis may persist for longer periods following each exposure but is unlikely to become more intense. Lesions may develop a brownish colour and scaling occurs frequently. Lower molecular weight species produce sensitisation more readily. In mice technical grades of bisphenol A diglycidyl ether produced epidermal tumours and a small increase in the incidence kidney tumours in males and of lymphoreticular/ haematopoietic tumours in females. Subcutaneous injection produced a small number of fibrosarcomas in rats. BADGE is listed as an IARC Group 3 carcinogen, meaning it is 'not classifiable as to its carcinogenicity to humans'. Concern has been raised over this possible carcinogenicity because BADGE is used in epoxy resins in the lining of some tin cans for foodstuffs, and unreacted BADGE may end up in the contents of those cans.
BISPHENOL F GLYCIDYL ETHER/ FORMALDEHYDE COPOLYMER	The chemical structure of hydroxylated diphenylalkanes or bisphenols consists of two phenolic rings joined together through a bridging carbon. This class of endocrine disruptors that mimic oestrogens is widely used in industry, particularly in plastics Bisphenol A (BPA) and some related compounds exhibit oestrogenic activity in human breast cancer cell line MCF-7, but there were remarkable differences in activity. Several derivatives of BPA exhibited significant thyroid hormonal activity towards rat pituitary cell line GH3, which releases growth hormone in a thyroid hormone-dependent manner. However, BPA and several other derivatives did not show such activity. Results suggest that the 4-hydroxyl group of the A-phenyl ring and the B-phenyl ring of BPA derivatives are required for these hormonal activities, and substituents at the 3,5-positions of the phenyl rings and the bridging alkyl moiety markedly influence the activities. Bisphenols promoted cell proliferation and increased the synthesis and secretion of cell type-specific proteins. When ranked by proliferative potency, the longer the alkyl substituent at the bridging carbon, the lower the concentration needed for maximal cell yield; the most active compound contained two propyl chains at the bridging carbon. Bisphenols with two hydroxyl groups in the para position and an angular configuration are suitable for appropriate hydrogen bonding to the acceptor site of the oestrogen receptor.
BISPHENOL A DIGLYCIDYL ETHER	55badger The substance is classified by IARC as Group 3: NOT classifiable as to its carcinogenicity to humans. Evidence of carcinogenicity may be inadequate or limited in animal testing.
DIPENTAERYTHRITOL PENTAACRYLATE	Asthma-like symptoms may continue for months or even years after exposure to the material ceases. This may be due to a non-allergenic condition known as reactive airways dysfunction syndrome (RADS) which can occur following exposure to high levels of highly irritating compound. Key criteria for the diagnosis of RADS include the absence of preceding respiratory disease, in a non-atopic individual, with abrupt onset of persistent asthma-like symptoms within minutes to hours of a documented exposure to the irritant. A reversible airflow pattern, on spirometry, with the presence of moderate to severe bronchial hyperreactivity on methacholine challenge testing and the lack of minimal lymphocytic inflammation, without eosinophilia, have also been included in the criteria for diagnosis of RADS. RADS (or asthma) following an irritating inhalation is an infrequent disorder with rates related to the concentration of and duration of exposure to the irritature. Industrial bronchitis, on the other hand, is a disorder that occurs as result of exposure due to high concentrations of irritating substance. (often particulate in nature) and is completely reversible after exposure ceases. The disorder is characterised by dyspnea, cough and mucus production.
9200FR Flame Retardant Structural Epoxy Adhesive (Part A) & BISPHENOL F GLYCIDYL ETHER/ FORMALDEHYDE COPOLYMER & BISPHENOL A DIGLYCIDYL ETHER & DIPENTAERYTHRITOL PENTAACRYLATE	The following information refers to contact allergens as a group and may not be specific to this product. Contact allergies quickly manifest themselves as contact eczema, more rarely as urticaria or Quincke's oedema. The pathogenesis of contact eczema involves a cell-mediated (T lymphocytes) immune reaction of the delayed type. Other allergic skin reactions, e.g. contact urticaria, involve antibody-mediated immune reactions. The significance of the contact allergen is not simply determined by its sensitisation potential: the distribution of the substance and the opportunities for contact with it are equally important. A weakly sensitising substance which is widely distributed can be a more important allergen than one with stronger sensitising potential with which few individuals come into contact. From a clinical point of view, substances are noteworthy if they produce an allergic test reaction in more than 1% of the persons tested.
9200FR Flame Retardant Structural Epoxy Adhesive (Part A) & BISPHENOL A DIGLYCIDYL ETHER	In mice, dermal application of bisphenol A diglycidyl ether (BADGE) (1, 10, or 100 mg/kg) for 13 weeks produced mild to moderate chronic active dermatitis. At the high dose, spongiosis and epidermal micro abscess formation were observed. In rats, dermal application of BADGE (10, 100, or 1000 mg/kg) for 13 weeks resulted in a decrease in body weight at the high dose. The no-observable effect level (NOEL) for dermal exposure was 100 mg/kg for both sexes. In a separate study, application of BADGE (same doses) five times per week for ~13 weeks not only caused a decrease in body weight but also produced chronic dermatitis at all dose levels in males and at >100 mg/kg in females (as well as in a satellite group of females given 1000 mg/kg). Reproductive and Developmental Toxicity : BADGE (50, 540, or 750 mg/kg) administered to rats via gavage for 14 weeks (P1) or 12 weeks (P2) produced decreased body weight in all males at the mid dose and in both males and females at the high dose, but had no reproductive effects. The NOEL for reproductive effects was 750 mg/kg. Carcinogenicity : IARC concluded that 'there is limited evidence for the carcinogenicity of bisphenol A diglycidyl ether is not classifiable as to its carcinogenicity to humans (Group 3). In a lifetime tumourigenicity study in which 90-day-old C3H mice received three dermal applications per week of BADGE (undiluted dose) for 23 months, only one out of 32 animals developed a papilloma after 16 months. A retest, in which skin paintings were done for 27 months, however, produced no tumours

(Weil et al., 1963). In another lifetime skin-painting study, BADGE (dose n.p.) was also reported to be noncarcinogenic to the skin of C3H mice; it was, however, weakly carcinogenic to the skin of C57BL/6 mice (Holland et al., 1979; cited by Canter et al., 1986). In a two-year bioassay, female Fisher 344 rats dermally exposed to BADGE (1, 100, or 1000 mg/kg) showed no evidence of dermal carcinogenicity but did have low incidences of tumours in the oral cavity (U.S. EPA, 1997).

Genotoxicity: In S. typhimurium strains TA100 and TA1535, BADGE (10-10,000 ug/plate) was mutagenic with and without S9; negative results were obtained in TA98 and TA1537 (Canter et al., 1986; Pullin, 1977). In a spot test, BADGE (0.05 or 10.00 mg) failed to show mutagenicity in strains TA98 and TA100 (Wade et al., 1979). Negative results were also obtained in the body fluid test using urine of female BDF and ICR mice (1000 mg/kg) micronucleus test (1000 mg/kg), and dominant lethal assay (~3000 mg/kg). Immunotoxicity: Intracutaneous injection of diluted BADGE (0.1 mL) three times per week on alternate days (total of 8 injections) followed by a three-week incubation period and a challenge dose produced sensitisation in 19 of 20 guinea pigs

Consumer exposure to BADGE is almost exclusively from migration of BADGE from can coatings into food. Using a worst-case scenario that assumes BADGE migrates at the same level into all types of food, the estimated per capita daily intake for a 60-kg individual is approximately 0.16 ug/kg body weight/day. A review of one- and two-generation reproduction studies and developmental investigations found no evidence of reproductive or endocrine toxicity, the upper ranges of dosing being determined by maternal toxicity. The lack of endocrine toxicity in the reproductive and developmental toxicological tests is supported by negative results from both in vivo and in vitro assays designed specifically to detect oestrogenic and androgenic properties of BADGE. An examination of data from sub-chronic and chronic toxicological studies support a NOAEL of 50 mg/ kg/body weight/day from the 90-day study, and a NOAEL of 15 mg/kg body weigh/day (male rats) from the 2-year carcinogenicity study. Both NOAELS are considered appropriate for risk assessment. Comparing the estimated daily human intake of 0.16 ug/kg body weight/day with the NOAELS of 50 and 15 mg/kg body weight/day shows human exposure to BADGE from can coatings is between 250,000 and 100,000-fold lower than the NOAELs from the most sensitive toxicology tests. These large margins of safety together with lack of reproductive, developmental, endocrine and carcinogenic effects supports the continued use of BADGE for use in articles intended to come into contact with foodstuffs.

Bisphenol A exhibits hormone-like properties that raise concern about its suitability in consumer products and food containers. Bisphenol A is thought to be an endocrine disruptor which can mimic oestrogen and may lead to negative health effects. More specifically, bisphenol A closely mimics the structure and function of the hormone oestradiol with the ability to bind to and activate the same oestrogen receptor as the natural hormone. Early developmental stages appear to be the period of greatest sensitivity to its effects and some studies have linked prenatal exposure to later physical and neurological difficulties. Regulatory bodies have determined safety levels for humans, but those safety levels are being questioned or are under review.

A 2009 study on Chinese workers in bisphenol A factories found that workers were four times more likely to report erectile dysfunction, reduced sexual desire and overall dissatisfaction with their sex life than workers with no heightened bisphenol A exposure. Bisphenol A workers were also seven times more likely to have ejaculation difficulties. They were also more likely to report reduced sexual function within one year of beginning employment at the factory, and the higher the exposure, the more likely they were to have sexual difficulties.

Bisphenol A in weak concentrations is sufficient to produce a negative reaction on the human testicle. The researchers found that a concentration equal to 2 ug/ litre of bisphenol A in the culture medium, a concentration equal to the average concentration generally found in the blood, urine and amniotic fluid of the population, was sufficient to produce the effects. The researchers believe that exposure of pregnant women to bisphenol A may be one of the causes of congenital masculinisation defects of the hypospadia and cryptorchidism types the frequency of which has doubled overall since the 70's. They also suggested that 'it is also possible that bisphenol A contributes to a reduction in the production of sperm and the increase in the incidence of testicular cancer in adults that have been observed in recent decades'

One review has concluded that obesity may be increased as a function of bisphenol A exposure, which '...merits concern among scientists and public health officials'

One study demonstrated that adverse neurological effects occur in non-human primates regularly exposed to bisphenol A at levels equal to the United States Environmental Protection Agency's (EPA) maximum safe dose of 50 ug/kg/day This research found a connection between bisphenol A and interference with brain cell connections vital to memory, learning, and mood.

A further review concluded that bisphenol-A has been shown to bind to thyroid hormone receptor and perhaps have selective effects on its functions. Carcinogenicity studies have shown increases in leukaemia and testicular interstitial cell tumours in male rats. However, 'these studies have not been considered as convincing evidence of a potential cancer risk because of the doubtful statistical significance of the small differences in incidences from controls'. Another in vitro study has concluded that bisphenol A is able to induce neoplastic transformation in human breast epithelial cells. [whilst a further study concluded that matemal oral exposure to low concentrations of bisphenol A, during lactation, increases mammary carcinogenesis in a rodent model. In vitro studies have suggested that bisphenol A can promote the growth of neuroblastoma cells and potently promotes invasion and metastasis of neuroblastoma cells. Newborn rats exposed to a low-dose of bisphenol A (10 ug/kg) showed increased prostate cancer susceptibility when adults. At least one study has suggested that bisphenol A auppresses DNA methylation which is involved in epigenetic changes.

Bisphenol A is the isopropyl adduct of 4,4'-dihydroxydiphenyl oxide (DHDPO). A series of DHDPO analogues have been investigated as potential oestrogen receptor/anti-tumour drug carriers in the development of a class of therapeutic drugs called 'cytostatic hormones'. Oestrogenic activity is induced with 1 to 100 mg/kg body weight in animal models. Bisphenol A sealants are frequently used in dentistry for treatment of dental pits and fissures. Samples of saliva collected from dental patients during a 1-hour period following application contain the monomer. A bisphenol-A sealant has been shown to be oestrogenic in vitro; such sealants may represent an additional source of xenoestrogens in humans and may be the cause of additional concerns in children.

Concerns have been raised about the possible developmental effects on the foetus/embryo or neonate resulting from the leaching of bisphenol A from epoxy linings in metal cans which come in contact with food-stuffs.

Many drugs, including naproxen, salicylic acid, carbamazepine and mefenamic acid can, in vitro, significantly inhibit bisphenol A glucuronidation (detoxification).

All glycidyl ethers show genotoxic potential due their alkylating properties. Those glycidyl ethers that have been investigated in long term studies exhibit more or less marked carcinogenic potential. Alkylating agents may damage the stem cell which acts as the precursor to components of the blood. Loss of the stem cell may result in pancytopenia (a reduction in the number of red and white blood cells and platelets) with a latency period corresponding to the lifetime of the individual blood cells. Granulocytopenia (a reduction in granular leukocytes) develops within days and thrombocytopenia (a disorder involving platelets), within 1-2 weeks, whilst loss of erythrocytes (red blood cells) need months to become clinically manifest. Aplastic anaemia develops due to complete destruction of the stem cells.

Glycidyl ethers have been shown to cause allergic contact dermatitis in humans. Glycidyl ethers generally cause skin sensitization in experimental animals. Necrosis of the mucous membranes of the nasal cavities was induced in mice exposed to allyl glycidyl ether.

A study of workers with mixed exposures was inconclusive with regard to the effects of specific glycidyl ethers. Phenyl glycidyl ether, but not *n*-butyl glycidyl ether, induced morphological transformation in mammalian cells *in vitro*. *n*-Butyl glycidyl ether induced micronuclei in mice *in vivo* following intraperitoneal but not oral administration. Phenyl glycidyl ether did not induce micronuclei or chromosomal aberrations *in vivo* or chromosomal aberrations in animal cells *in vitro*. Alkyl C12 or C14 glycidyl ether did not induce DNA damage in cultured human cells or mutation in cultured animal cells. Allyl glycidyl ether induced mutation in *Drosophila*. The dvictyl ethers were generally mutagenic to bacteria

Oxiranes (including glycidyl ethers and alkyl oxides, and epoxides) exhibit many common characteristics with respect to animal toxicology. One such oxirane is ethyloxirane; data presented here may be taken as representative.

for 1,2-butylene oxide (ethyloxirane):

Ethyloxirane increased the incidence of tumours of the respiratory system in male and female rats exposed via inhalation. Significant increases in nasal papillary adenomas and combined alveolar/bronchiolar adenomas and carcinomas were observed in male rats exposed to 1200 mg/m3 ethyloxirane via inhalation for 103 weeks. There was also a significant positive trend in the incidence of combined alveolar/bronchiolar adenomas and carcinomas. Nasal papillary adenomas were also observed in 2/50 high-dose female rats with none occurring in control or low-dose animals. In mice exposed chronically via inhalation, one male mouse developed a squamous cell papilloma in the nasal cavity (300 mg/m3) but other tumours were not observed. Tumours were not observed in mice exposed chronically via dermal exposure. When trichloroethylene containing 0.8% ethyloxirane was administered orally to mice for up to 35 weeks, followed by 0.4% from weeks 40 to 69, squamous-cell carcinomas of the forestomach occurred in 3/49 males (p=0.029, age-adjusted) and 1/48 females at week 106. Trichloroethylene administered alone did not induce these tumours and they were not observed in control animals . Two structurally related substances, oxirane (ethylene oxide) and methyloxirane (propylene oxide), which are also direct-acting alkylating agents, have been classified as carcinogenic

Page 14 of 20 9200FR-A Flame Retardant Structural Epoxy Adhesive (Part A)

9200FR Flame Retardant Structural Epoxy Adhesive (Part A) & DIPENTAERYTHRITOL PENTAACRYLATE	UV (ultraviolet)/ EB (electron beam) acrylates are generally of low toxicity UV/EB acrylates are divided into two groups; 'stenomeric' and 'eurymeric' acrylates. The first group consists of well-defined acrylates which can be described by a simple idealised chemical;they are low molecular weight species with a very narrow weight distribution profile. The eurymeric acrylates cannot be described by an idealised structure and may differ fundamentally between various suppliers; they are of relatively high molecular weigh and possess a wide weight distribution. Stenomeric acrylates are usually more hazardous than the eurymeric substances. Stenomeric acrylates are also well defined which allows comparison and exchange of toxicity data - this allows more accurate classification. The stenomerics cannot be classified as a group; they exhibit substantial variation. Based on the available oncogenicity data and without a better understanding of the carcinogenic mechanism the Health and Environmental Review Division (HERD), Office of Toxic Substances (OTS), of the US EPA previously concluded that all chemicals that contain the acrylate or methacrylate moiety (CH2=CHCOO or CH2=C(CH3)COO) should be considered to be a carcinogenic hazard unless shown otherwise by adequate testing. This position has now been revised and acrylates and methacrylates are no longer <i>de facto</i> carcinogens. Where no 'official' classification for acrylates and methacrylates exists, there has been cautious attempts to create classifications in the absence of contrary evidence. For example Monalkyl or monoarylesters of acrylic acids should be classified as R36/37/38 and R51/53 Monoalkyl or monoaryl esters of methacrylic acid should be classified as R36/37/38					
ALUMINIUM HYDROXIDE & DIPENTAERYTHRITOL PENTAACRYLATE	No significant acute toxicological data identified in literature search.					
Acute Toxicity	✓	Carcinogenicity	×			
Skin Irritation/Corrosion	×	Reproductivity	✓			
Serious Eye Damage/Irritation	*	STOT - Single Exposure	×			
Respiratory or Skin sensitisation	*	✓ STOT - Repeated Exposure ×				
Mutagenicity	×	Aspiration Hazard	×			
		0	er not available or does not fill the criteria for classification able to make classification			

SECTION 12 ECOLOGICAL INFORMATION

9200FR Flame Retardant	ENDPOINT	TEST DURATION (HR)		SPECIES	VALUE		SOURCE	
Structural Epoxy Adhesive (Part A)	Not Available	Not Available		Not Available	Not Availa	ble	Not Available	
bisphenol F glycidyl ether/	ENDPOINT	TEST DURATION (HR)		SPECIES	VALUE		SOURCE	
formaldehyde copolymer	Not Available	Not Available		Not Available	Not Availa	ble	Not Available	
	ENDPOINT	TEST DURATION (HR)	SPECIES	5	VA	LUE	SOURCE	
	LC50	96	Fish		0.0	01-0.134mg/L	2	
aluminium hydroxide	EC50	48	Crustace	a	0.7	364mg/L	2	
	EC50	72	Algae or o	other aquatic plants	0.0	01-0.05mg/L	2	
	NOEC	168	Crustace	a	0.0	01-mg/L	2	
	ENDPOINT	TEST DURATION (HR)	TEST DURATION (HR) SPECIES			VALUE	SOURCE	
	LC50	96	Fish	Fish		70mg/L	4	
ammonium polyphosphate	EC50	48		Crustacea		>100mg/L	2	
	EC50	72	Algae	or other aquatic plants		>97.1mg/L	2	
	NOEC	72 Alg		Algae or other aquatic plants		3.57mg/L	2	
	ENDPOINT	TEST DURATION (HR)	SPE	CIES		VALUE	SOURCE	
	LC50	96	Fish	Fish			2	
	EC50	48	Cru	stacea		1.1mg/L		
bisphenol A diglycidyl ether	EC50	72	Alga	Algae or other aquatic plants		9.4mg/L	2	
	EC0	48	Cru	Crustacea		<1mg/L	2	
	NOEC	504	Cru	stacea		0.3mg/L	2	
	ENDPOINT	TEST DURATION (HR)	SPECIES	3	VA	LUE	SOURCE	
	LC50	96			0.00		2	
zinc borate	EC50	48	Crustacea				2	
	EC50	96	Algae or o			4mg/L	2	
	NOEC	72	Algae or other aquatic plants		0.0	00001mg/L	2	

dipentaerythritol pentaacrylate	ENDPOINT	TEST DURATION (HR)	SPECIES	VALUE	SOURCE
	LC50	96	Fish	8.9mg/L	2
	EC50	48	Crustacea	18mg/L	2
	EC50	72	Algae or other aquatic plants	21mg/L	2
	NOEC	72	Algae or other aquatic plants	6.6mg/L	2
			· · · · · · · · · · · · · · · · · · ·		
Leaend:	Extracted from 1.	IUCLID Toxicity Data 2. Europe ECHA F	Registered Substances - Ecotoxicological Informat	ion - Aquatic Toxicity 3.	EPIWIN Suite V3.12

gend: Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity 3. EPIWIN Suite V3.12 (QSAR) - Aquatic Toxicity Data (Estimated) 4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data

On the basis of available evidence concerning either toxicity, persistence, potential to accumulate and or observed environmental fate and behaviour, the material may present a danger, immediate or long-term and /or delayed, to the structure and/ or functioning of natural ecosystems.

Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.

Do NOT allow product to come in contact with surface waters or to intertidal areas below the mean high water mark. Do not contaminate water when cleaning equipment or disposing of equipment wash-waters.

Wastes resulting from use of the product must be disposed of on site or at approved waste sites.

Liquid epoxy resins and some reactive diluents are not readily biodegradable, although its epoxy functional groups are hydrolysed in contact with water, they have the potential to bio-accumulate and are moderately toxic to aquatic organisms. They are generally classified as dangerous for the environment according to the European Union classification criteria.

Uncured solid resins on the other hand are not readily bio-available, not toxic to aquatic and terrestrial organisms, not readily biodegradable, but hydrolysable. They present no significant hazard for the environment.

Reactive diluents generally have a low to moderate potential for bioconcentration (tendency to accumulate in the food chain) and a high to very high potential for mobility in soil. Small amounts that escape to the atmosphere will photodegrade.

They would not be expected to persist in the environment.

Most reactive diluents should be considered slightly to moderately toxic to aquatic organisms on an acute basis while some might also be considered harmful to the environment. Environmental toxicity is a function of the n-octanol/water partition coefficient (log Pow, log Kow). Compounds with log Pow >5 act as neutral organics, but at a lower log Pow, the toxicity of epoxide-containing polymers is greater than that predicted for simple narcotics.

Significant environmental findings are limited. Oxiranes (including glycidyl ethers and alkyl oxides, and epoxides) exhibit common characteristics with respect to environmental fate and ecotoxicology. One such oxirane is ethyloxirane and data presented here may be taken as representative.

for 1,2-butylene oxide (ethyloxirane):

Environmental fate: Ethyloxirane is highly soluble in water and has a very low soil-adsorption coefficient, which suggests that if released to water, adsorption of ethyloxirane to sediment and suspended solids is not expected. Volatilisation of ethyloxirane from water surfaces would be expected based on the moderate estimated Henry's Law constant. If ethyloxirane is released to soil, it is expected to have low adsorption and thus very high mobility. Volatilisation from moist soil and dry soil surfaces is expected, based on its vapour pressure. It is expected that ethyloxirane exists solely as a vapour in ambient atmosphere, based on its very high vapour pressure. Ethyloxirane may also be removed from the atmosphere by wet deposition processes, considering its relatively high water solubility.

Persistence: The half-life in air is about 5.6 days from the reaction of ethyloxirane with photochemically produced hydroxyl radicals which indicates that this chemical meets the persistence criterion in air (half-life of = 2 days)*.

Ethyloxirane is hydrolysable, with a half-life of 6.5 days, and biodegradable up to 100% degradation and is not expected to persist in water. A further model-predicted biodegradation half-life of 15 days in water was obtained and used to predict the half-life of this chemical in soil and sediment by applying Boethling's extrapolation factors (t1/2water: 11/2 soil: t1/2sediment = 1: 1: 4) (Boethling 1995). According to these values, it can be concluded that ethyloxirane does not meet the persistence criteria in water and soil (half-lives = 182 days) and sediments (half-life = 365 days).

Experimental and modelled log Kow values of 0.68 and 0.86, respectively, indicate that the potential for bioaccumulation of ethyloxirane in organisms is likely to be low. Modelled bioaccumulation -factor (BAF) and bioconcentration -factor (BCF) values of 1 to 17 L/kg indicate that ethyloxirane does not meet the bioaccumulation criteria (BCF/BAF = 5000)* Ecotoxicity:

Experimental ecotoxicological data for ethyloxirane (OECD 2001) indicate low to moderate toxicity to aquatic organisms. For fish and water flea, acute LC50/EC50 values vary within a narrow range of 70-215 mg/L; for algae, toxicity values exceed 500 mg/L, while for bacteria they are close to 5000 mg/L

* Persistence and Bioaccumulation Regulations (Canada 2000).

Substances containing unsaturated carbons are ubiquitous in indoor environments. They result from many sources (see below). Most are reactive with environmental ozone and many produce stable products which are thought to adversely affect human health. The potential for surfaces in an enclosed space to facilitate reactions should be considered.

Source of unsaturated substances	Unsaturated substances (Reactive Emissions)	Major Stable Products produced following reaction with ozone.
Occupants (exhaled breath, ski oils, personal care products)	Isoprene, nitric oxide, squalene, unsaturated sterols, oleic acid and other unsaturated fatty acids, unsaturated oxidation products	Methacrolein, methyl vinyl ketone, nitrogen dioxide, acetone, 6MHQ, geranyl acetone, 4OPA, ¹ formaldehyde, nonanol, decanal, 9-oxo-nonanoic acid, azelaic acid, nonanoic acid.
Soft woods, wood flooring, including cypress, cedar and silver fir boards, houseplants	Isoprene, limonene, alpha-pinene, other terpenes and sesquiterpenes	Formaldehyde, 4-AMC, pinoaldehyde, pinic acid, pinonic acid, formic acid, methacrolein, methyl vinyl ketone, SOAs including ultrafine particles
Carpets and carpet backing	 Phenylcyclohexene, 4-vinylcyclohexene, styrene, 2-ethylhexyl acrylate, unsaturated fatty acids and esters 	Formaldehyde, acetaldehyde, benzaldehyde, hexanal, nonanal, 2-nonenal
Linoleum and paints/polishes containing linseed oil	Linoleic acid, linolenic acid	Propanal, hexanal, nonanal, 2-heptenal, 2-nonenal, 2-decenal, 1-pentene-3-one, propionic acid, n-butyric acid
Latex paint	Residual monomers	Formaldehyde
Certain cleaning products, polishes, waxes, air fresheners	Limonene, alpha-pinene, terpinolene, alpha-terpineol, linalool, linalyl acetate and other terpenoids, longifolene and other sesquiterpenes	Formaldehyde, acetaldehyde, glycoaldehyde, formic acid, acetic acid, hydrogen and organic dperoxides, acetone, benzaldehyde, 4-hydroxy-4-methyl-5-hexen-1-al, 5-ethenyl-dihydro-5-methyl- 2(3H)-furanone, 4-AMC, SOAs including ultrafine particles
Natural rubber adhesive	Isoprene, terpenes	Formaldehyde, methacrolein, methyl vinyl ketone
Photocopier toner, printed paper, styrene polymers	Styrene	Formaldehyde, benzaldehyde
Environmental tobacco smoke	Styrene, acrolein, nicotine	Formaldehyde, benzaldehyde, hexanal, glyoxal, N-methylformamide, nicotinaldehyde, cotinine
Soiled clothing, fabrics, bedding	Squalene, unsaturated sterols, oleic acid and other saturated fatty acids	Acetone, geranyl acetone, 6MHO, 40PA, formaldehyde, nonanal, decanal, 9-oxo-nonanoic acid, azelaic acid, nonanoic acid
Soiled particle filters	Unsaturated fatty acids from plant waxes, leaf litter, and other vegetative debris; soot; diesel particles	Formaldehyde, nonanal, and other aldehydes; azelaic acid; nonanoic acid; 9-oxo-nonanoic acid and other oxo-acids; compounds with mixed functional groups (=O, -OH, and -COOH)
Ventilation ducts and duct liners	Unsaturated fatty acids and esters, unsaturated oils, neoprene	C5 to C10 aldehydes
'Urban grime'	Polycyclic aromatic hydrocarbons	Oxidized polycyclic aromatic hydrocarbons
Perfumes, colognes, essential oils	Limonene, alpha-pinene, linalool, linalyl acetate,	Formaldehyde, 4-AMC, acetone, 4-hydroxy-4-methyl-5-hexen-1-al, 5-ethenyl-dihydro-
(e.g. lavender, eucalyptus, tea tree)	terpinene-4-ol, gamma-terpinene	5-methyl-2(3H) furanone, SOAs including ultrafine particles
Overall home emissions	Limonene, alpha-pinene, styrene	Formaldehyde, 4-AMC, pinonaldehyde, acetone, pinic acid, pinonic acid, formic acid, benzaldehyde, SOAs including ultrafine particles
Abbreviations: 4-AMC, 4-acetyl-1-me	thylcyclohexene: 6MHQ_6-methyl-5-heptene-2-one_4OPA_4	4-oxopentanal SOA Secondary Organic Aerosols

Abbreviations: 4-AMC, 4-acetyl-1-methylcyclohexene; 6MHQ, 6-methyl-5-heptene-2-one, 4OPA, 4-oxopentanal, SOA, Secondary Organic Aerosols Reference: Charles J Weschler; Environmental Helath Perspectives, Vol 114, October 2006

Secondary Organic Aerosols

Environmental toxicity is a function of the n-octanol/ water partition coefficient (log Pow, log Kow). Phenols with log Pow >7.4 are expected to exhibit low toxicity to aquatic organisms. However the toxicity of phenols with a lower log Pow is variable, ranging from low toxicity (LC50 values >100 mg/l) to highly toxic (LC50 values <1 mg/l) dependent on log Pow, molecular weight and substitutions on the aromatic ring. Dinitrophenols are more toxic than predicted from QSAR estimates. Hazard information for these groups is not generally available.

Environmental fate:

Boron is generally found in nature bound to oxygen and is never found as the free element. Atmospheric boron may be in the form of particulate matter or aerosols as borides, boron oxides, boranes, boranes, organoboron compounds, trihalide boron compounds, or borazines. Borates are relatively soluble in water, and will probably be removed from the atmosphere by precipitation and dry deposition. The half-life of airborne particles is usually on the order of days, depending on the size of the particle and atmospheric conditions.

Boron readily hydrolyses in water to form the electrically neutral, weak monobasic acid boric acid (H3BO3) and the monovalent ion, B(OH)4-. In concentrated solutions, boron may polymerise, leading to the formation of complex and diverse molecular arrangements. Because most environmentally relevant boron minerals are highly soluble in water, it is unlikely that mineral equilibria will control the fate of boron in water. Boron was found to not be significantly removed during the conventional treatment of waste water. Boron may, however, be co-precipitated with aluminum, silicon, or iron to form hydroxyborate compounds on the surfaces of minerals.

Waterborne boron may be adsorbed by soils and sediments. Adsorption-desorption reactions are expected to be the only significant mechanism that will influence the fate of boron in water. The extent of boron adsorption depends on the pH of the water and the chemical composition of the soil. The greatest adsorption is generally observed at pH 7.5-9.0. the single most important property of soil that will influence the mobility of boron is the abundance of amorphous aluminum oxide. The extent of boron adsorption has also been attributed to the levels of iron oxide, and to a lesser extent, the organic matter present in the soil, although other studies found that the amount of organic matter present was not important. The adsorption foor may not be reversible in some soils. The lack of reversibility may be the result of solid-phase formation on mineral surfaces and/or the slow release of boron by diffusion from the interior of day minerals.

It is unlikely that boron is bioconcentrated significantly by organisms from water. A bioconcentration factor (BCF) relates the concentration of a chemical in the tissues of aquatic and terrestrial animals or plants to the concentration of the chemical in water or soil. The BCFs of boron in marine and freshwater plants, fish, and invertebrates were estimated to be <100. Experimentally measured BCFs for fish have ranged from 52 to 198. These BCFs suggest that boron is not significantly bioconcentrated.

As an element, boron itself cannot be degraded in the environment; however, it may undergo various reactions that change the form of boron (e.g., precipitation, polymerization, and acid-base reactions) depending on conditions such as its concentration in water and pH. In nature, boron in generally found in its oxygenated form. In aqueous solution, boron is normally present as boric acid and borate ions, with the dominant form of inorganic boron in natural aqueous systems as undissociated boric acid. Boric acid acts as an electron acceptor in aqueous solution, accepting an hydroxide ion from water to form (B(OH)4)-ion. In dilute solution, the favored form of boron is B(OH)4. In more concentrated solutions (>0.1 M boric acid) and at neutral to alkaline pH (6–11), polymeric species are formed (e.g., B3O3(OH)4-, B5O6(OH)4-, B3O3(OH)52-, and B4O5(OH)42-)

Most boron compounds are transformed to borates in soil due to the presence of moisture. Borates themselves are not further degraded in soil. However, borates can exist in a variety of forms in soil. Borates are removed from soils by water leaching and by assimilation by plants.

The most appreciable boron exposure to the general population is likely to be ingestion of food and to a lesser extent in water. As boron is a natural component of the environment, individuals will have some exposure from foods and drinking water

Boron-containing salts (borates) are ubiquitous in the environment. Surface soil, unpolluted waterways and seawater all typically contain significant amounts of boron as borate. Boron is an essential micronutrient for healthy growth of plants, however, it can be harmful to boron sensitive plants in higher quantities. In some areas such as the American Southwest, boron occurs naturally in surface waters in concentrations that have been shown to be toxic to commercially important plants.

Based on the collected information regarding aquatic toxicity, boron is not regarded as dangerous to aquatic organisms. The concentration in treated municipal waste water is a factor 100 lower than the NOEC-value for Daphnia magna.

No quality criteria exist for the concentration of boron in soil and compost. Boron is added to farmland when sewage sludge is applied as a soil improving agent, but there is not sufficient data to evaluate its effect on soil organisms. Being an essential micro-nutrient, no adverse effects of boron are expected at low concentrations.

Ecotoxicity:

In aquatic environments low concentrations of borates generally promote the growth of algae, whereas higher concentrations inhibited algal growth. In a growth inhibition test with Scenedesmus subspicatus, an EC50 value of 34 mg B/l was determined. Boric acid toxicity in Daphnia 48 h-LC50 (static test) was found to be 95 mg B/l. In a separate study it was concluded that chronic effects of boron to Daphnia may occur at a concentration of > 10 mg/l.

The toxicity of boron in fish is often higher in soft water than in hard water. The acute toxicity of boron towards *Danio rerio* (96 h-LC50) has been determined to 14.2 mg B/l. In a fish early life stage test with rainbow trout NOEC levels of boron have been determined in the range between 0.009 and 0.103 mg B/l, whereas the EC50 ranged from 27 to 100 mg B/l dependent on the water hardness.

In air ammonia is persistent whilst, in water, it biodegrades rapidly to nitrate, producing a high oxygen demand. Ammonia is strongly adsorbed to soil. Ammonia is non-persistent in water (half-life 2 days) and is moderately toxic to fish under normal temperature and pH conditions. Ammonia is harmful to aquatic life at low concentrations but does not concentrate in the food chain. Ammonia ins may be toxic to fish at 0.3 mg/l

Drinking Water Standards:

0.5 mg/l (UK max.)

1.5 mg/l (WHO Levels)

Soil Guidelines: none available. Air Quality Standards: none available.

The principal problems of phosphate contamination of the environment relates to eutrophication processes in lakes and ponds. Phosphorus is an essential plant nutrient and is usually the limiting nutrient for blue-green algae. A lake undergoing eutrophication shows a rapid growth of algae in surface waters. Planktonic algae cause turbidity and flotation films. Shore algae cause ugly muddying, films and damage to reeds. Decay of these algae causes oxygen depletion in the deep water and shallow water near the shore. The process is self-perpetuating because anoxic conditions at the sediment/water interface causes the release of more adsorbed phosphates from the sediment. The growth of algae produces undesirable effects on the treatment of water for drinking purposes, on fisheries, and on the use of lakes for recreational purposes. **DO NOT discharge into sewer or waterways**.

12.2. Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
bisphenol A diglycidyl ether	HIGH	HIGH

12.3. Bioaccumulative potential

Ingredient	Bioaccumulation
bisphenol A diglycidyl ether	MEDIUM (LogKOW = 3.8446)

12.4. Mobility in soil

Ingredient	Mobility
bisphenol A diglycidyl ether	LOW (KOC = 1767)

12.5.Results of PBT and vPvB assessment

	Р	В	Т
Relevant available data	Not Applicable	Not Applicable	Not Applicable
PBT Criteria fulfilled?	Not Applicable	Not Applicable	Not Applicable

SECTION 13 DISPOSAL CONSIDERATIONS

13.1. Waste treatment methods

Product / Packaging disposit Product / Packaging disposit Respective containers, to prevent re-use, and bury at an authorise pertaining to the product. Waste Management Where possible retain label warnings and SDS and observe all notices pertaining to the product. Waste Management Production waste from epoxy resins and resin systems should be treated as hazardous waste in accordance with National regulations. Fire retarded resins containing halogenated compounds should also be treated as special waste. Accidental spillage of resins, curing agents and their formulations should be contained and absorbed by special mineral absorbents to prevent them from entering the environment. Containinated or supplicit should not be washed down the sink, but preferably be fully reacted to form cross-linked solids which is non-hazardous and can be more easily disposed. Finished anticles made from Mily oured epoxy resins are hard, infusible solids presenting no hazard to the environment. However, finished anticles made from epoxy resins, like other thermosets, can be recycled by grinding and used as fillers in other products. Another way of disposal and recovery is combustion with energy recovery. Legislation addressing waste disposal requirements may differ by country, state and' or territory. Each user must refer to laws operating in their area. In some areas, certain wastes must be tracked. A Hierarchy of Controls seems to be common - the user should investigate: Reduction Respecting Disposal (if all else fails) This material may chany there use, and recycling or reuse may not always be approprin		
	Product / Packaging disposal	 Return to supplier for reuse/ recycling if possible. Otherwise: If container can not be cleaned sufficiently well to ensure that residuals do not remain or if the container cannot be used to store the same product, then puncture containers, to prevent re-use, and bury at an authorised landfill. Where possible retain label warnings and SDS and observe all notices pertaining to the product. Waste Management Production waste from epoxy resins and resin systems should be treated as hazardous waste in accordance with National regulations. Fire retarded resins containing halogenated compounds should also be treated as special waste. Accidental spillage of resins, curing agents and their formulations should be contained and absorbed by special mineral absorbents to prevent them from entering the environment. Contaminated or surplus product should not be washed down the sink, but preferably be fully reacted to form cross-linked solids which is non-hazardous and can be more easily disposed. Finished articles made from fully cured epoxy resins are hard, infusible solids presenting no hazard to the environment. However, finished articles from flame-retarded material containing halogenated resins should be considered hazardous waste, and disposed as required by National laws. Articles made from epoxy resins, like disposal requirements may differ by country, state and/ or territory. Each user must refer to laws operating in their area. In some areas, certain wastes must be tracked. A Hierarchy of Controls seems to be common - the user should investigate: Recuse Recuse Recycling Disposal (if all else fails) This material may be recycled if unused, or if it has not been contaminated so as to make it unsuitable for its intended use. If it has been contaminated, it may be possible to reclaim the product by filtration, distillation or some other means. Shell life considerations should also
	Waste treatment options	Not Available
Sewage disposal options Not Available	Sewage disposal options	Not Available

SECTION 14 TRANSPORT INFORMATION

Labels Required

For 9200FR-25ML, 9200FR-50ML NOT REGULATED by Ground ADR Special Provision 375 NOT REGULATED by Air IATA Special Provision A197 NOT REGULATED by Sea IMDG per 2.10.2.7 NOT REGULATED by ADN Special Provision 274 (The provision of 3.1.2.8 apply)

Land transport (ADR)

14.1. UN number	3082		
14.2. UN proper shipping name	ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (contains bisphenol A diglycidyl ether, zinc borate and bisphenol F glycidyl ether/ formaldehyde copolymer)		
14.3. Transport hazard class(es)	Class 9 Subrisk Not Applicable		
14.4. Packing group	Ш		
14.5. Environmental hazard	Environmentally hazardous		
14.6. Special precautions for user	Hazard identification (Kemler) 90		
	Classification code M6		
	Hazard Label 9		
	Special provisions 274 335 375 601		
	Limited quantity 5 L		

Air transport (ICAO-IATA / DGR)

14.1. UN number	3082	
14.2. UN proper shipping name	Environmentally hazardou copolymer)	us substance, liquid, n.o.s. * (contains bisphenol A diglycidyl ether, zinc borate and bisphenol F glycidyl ether/ formaldehyde
14.3. Transport hazard class(es)	ICAO/IATA Class ICAO / IATA Subrisk	9 Not Applicable

	ERG Code 9L		
14.4. Packing group	Ш		
14.5. Environmental hazard	Environmentally hazardous		
	Special provisions	A97 A158 A197	
14.6. Special precautions for user	Cargo Only Packing Instructions	964	
	Cargo Only Maximum Qty / Pack	450 L	
	Passenger and Cargo Packing Instructions	964	
	Passenger and Cargo Maximum Qty / Pack	450 L	
	Passenger and Cargo Limited Quantity Packing Instructions	Y964	
	Passenger and Cargo Limited Maximum Qty / Pack	30 kg G	

Sea transport (IMDG-Code / GGVSee)

14.1. UN number	3082		
14.2. UN proper shipping name	ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (contains bisphenol A diglycidyl ether, zinc borate and bisphenol F glycidyl ether/ formaldehyde copolymer)		
14.3. Transport hazard class(es)	IMDG Class 9 IMDG Subrisk Not Applicable		
14.4. Packing group	III		
14.5. Environmental hazard	Marine Pollutant		
14.6. Special precautions for user	EMS NumberF-A , S-FSpecial provisions274 335 969Limited Quantities5 L		

Inland waterways transport (ADN)

14.2. UN proper shipping name ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (contains bisphenol A diglycidyl ether, zinc borate and bisphenol F glycidyl ether/ formaldehyde copolymer) 14.3. Transport hazard class(es) 9 Not Applicable 14.4. Packing group III Environmental based on the sector of the	14.1. UN number	3082		
class(es) 9 Not Applicable 14.4. Packing group III	14.2. UN proper shipping name			
	-	9 Not Applicable		
445 Environmental knowed Environmentally knowed are	14.4. Packing group	III III III III III III III III III II		
14.5. Environmental nazaro Environmentally nazaroous	14.5. Environmental hazard	Environmentally hazardous		
Classification code M6		Classification code M6		
Special provisions 274; 335; 375; 601	14.6. Special precautions for user	Special provisions 274; 335; 375; 601		
Limited quantity 5		Limited quantity 5 L		
Equipment required PP		Equipment required PP		
Fire cones number 0		Fire cones number 0		

14.7. Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

SECTION 15 REGULATORY INFORMATION

15.1. Safety, health and environmental regulations / legislation specific for the substance or mixture

BISPHENOL F GLYCIDYL ETHER/ FORMALDEHYDE COPOLYMER(28064-14-4) IS FOUND ON THE FOLLOWING REGULATORY LISTS

ADN - European Agreement concerning the International Carriage of Dangerous Goods by	International Air Transport Association (IATA) Dangerous Goods Regulations
Inland Waterways	International Maritime Dangerous Goods Requirements (IMDG Code)
European Agreement concerning the International Carriage of Dangerous Goods by Road (ADR 2011, Spanish)	Regulations concerning the International Carriage of Dangerous Goods by Rail - Table A: Dangerous Goods List - RID 2019 (English)
European Agreement concerning the International Carriage of Dangerous Goods by Road (ADR 2017, English)	United Nations Recommendations on the Transport of Dangerous Goods Model Regulations (English)
European Chemical Agency (ECHA) Classification & Labelling Inventory - Chemwatch Harmonised classification	
European Union (EU) Transport of Dangerous Goods by Road - Dangerous Goods List (English)	
ALUMINIUM HYDROXIDE(21645-51-2) IS FOUND ON THE FOLLOWING REGULATORY LI	515
Europe EC Inventory	Europe European Customs Inventory of Chemical Substances ECICS (Romanian)
Europe ECHA Registered Substances - Classification and Labelling - DSD-DPD	European Chemical Agency (ECHA) Classification & Labelling Inventory - Chemwatch
Europe European Customs Inventory of Chemical Substances - ECICS (Slovak)	Harmonised classification
Europe European Customs Inventory of Chemical Substances ECICS (Bulgarian)	European Customs Inventory of Chemical Substances ECICS (English)

Europe European Customs Inventory of Chemical Substances ECICS (Czech)

European Union - European Inventory of Existing Commercial Chemical Substances (EINECS) (English)

Europe EC Inventory		European Union - European Inventory of Existing Commercial Chemical Substances (EINECS	
	es - Classification and Labelling - DSD-DPD	(English)	
European Chemical Agency (ECHA) (Harmonised classification	Classification & Labelling Inventory - Chemwatch	IMO IBC Code Chapter 17: Summary of minimum requirements IMO MARPOL (Annex II) - List of Noxious Liquid Substances Carried in Bulk	
European Customs Inventory of Cherr	nical Substances ECICS (English)		
SISPHENOL A DIGLYCIDYL ETHE	R(1675-54-3) IS FOUND ON THE FOLLOWING REGUL	ATORY LISTS	
ADN - European Agreement concerni Inland Waterways	ng the International Carriage of Dangerous Goods by	European Union (EU) Regulation (EC) No 1272/2008 on Classification, Labelling and Packaging of Substances and Mixtures - Annex VI	
EU European Chemicals Agency (EC Substances	HA) Community Rolling Action Plan (CoRAP) List of	European Union (EU) Regulation (EC) No 1272/2008 on Classification, Labelling and Packaging of Substances and Mixtures - Annex VI - Chemwatch Standard Format	
Europe EC Inventory	es - Classification and Labelling - DSD-DPD	European Union (EU) Transport of Dangerous Goods by Road - Dangerous Goods List (English)	
European Agreement concerning the	International Carriage of Dangerous Goods by Road	GESAMP/EHS Composite List - GESAMP Hazard Profiles	
(ADR 2011, Spanish) European Agreement concerning the	International Carriage of Dangerous Goods by Road	IMO IBC Code Chapter 17: Summary of minimum requirements IMO MARPOL (Annex II) - List of Noxious Liquid Substances Carried in Bulk	
(ADR 2017, English)	Classification & Labelling Inventory - Chemwatch	International Agency for Research on Cancer (IARC) - Agents Classified by the IARC Monographs	
Harmonised classification		International Air Transport Association (IATA) Dangerous Goods Regulations	
European Customs Inventory of Cherr European Trade Union Confederatior	nical Substances ECICS (English) (ETUC) Priority List for REACH Authorisation	International FOSFA List of Banned Immediate Previous Cargoes International Maritime Dangerous Goods Requirements (IMDG Code)	
	of Existing Commercial Chemical Substances (EINECS)	Regulations concerning the International Carriage of Dangerous Goods by Rail - Table A: Dangerous Goods List - RID 2019 (English)	
	ctive 67/548/EEC on Classification and Labelling of \TP: 31	United Nations Recommendations on the Transport of Dangerous Goods Model Regulations (English)	
European Union (EU) No-Longer Poly	ymers List (NLP) (67/548/EEC)		
INC BORATE(12767-90-7) IS FOU	IND ON THE FOLLOWING REGULATORY LISTS		
ADN - European Agreement concerni nland Waterways	ng the International Carriage of Dangerous Goods by	European Agreement concerning the International Carriage of Dangerous Goods by Road (ADR 2017, English)	
November 2009 on cosmetic products	the European Parliament and of the Council of 30 - Annex III - List of Substances which cosmetic products	European Chemical Agency (ECHA) Classification & Labelling Inventory - Chemwatch Harmonised classification	
November 2009 on cosmetic products	the European Parliament and of the Council of 30 - Annex III - List of Substances which cosmetic products	European Customs Inventory of Chemical Substances ECICS (English) European Union - European Inventory of Existing Commercial Chemical Substances (EINEC (English)	
	the European Parliament and of the Council of 30	European Union (EU) Transport of Dangerous Goods by Road - Dangerous Goods List (English)	
must not contain except subject to the		International Air Transport Association (IATA) Dangerous Goods Regulations International Maritime Dangerous Goods Requirements (IMDG Code)	
November 2009 on cosmetic products	the European Parliament and of the Council of 30 - Annex III - List of Substances which cosmetic products	Regulations concerning the International Carriage of Dangerous Goods by Rail - Table A: Dangerous Goods List - RID 2019 (English)	
• • • •	restrictions laid down (Latvian) the European Parliament and of the Council of 30 - Annex III - List of Substances which cosmetic products	United Nations Recommendations on the Transport of Dangerous Goods Model Regulations (English)	
.,,	the European Parliament and of the Council of 30		
must not contain except subject to the	 Annex III - List of Substances which cosmetic products restrictions laid down (Portuguese) 		
Europe EC Inventory Europe ECHA Registered Substance	es - Classification and Labelling - DSD-DPD		
1 0	International Carriage of Dangerous Goods by Road		
DIPENTAERYTHRITOL PENTAACF	YLATE(60506-81-2) IS FOUND ON THE FOLLOWING F	REGULATORY LISTS	
Europe EC Inventory		European Union - European Inventory of Existing Commercial Chemical Substances (EINEC	
European Chemical Agency (ECHA) (Harmonised classification	Classification & Labelling Inventory - Chemwatch	(English)	
-	e with the following EU legislation and its adaptations - as fa 30; Regulation (EC) No 1272/2008 as updated through ATP:	r as applicable - : Directives 98/24/EC, - 92/85/EEC, - 94/33/EC, - 2008/98/EC, - 2010/75/EU; s.	
5.2. Chemical safety assessn	nent		
No Chemical Safety Assessment has	been carried out for this substance/mixture by the supplier.		
ational Inventory Status			
ational Inventory Status National Inventory	Status		

Yes	
Yes	
No (dipentaerythritol pentaacrylate; bisphenol A diglycidyl ether; bisphenol F glycidyl ether/ formaldehyde copolymer; aluminium hydroxide; ammonium polyphosphate)	
Yes	
No (bisphenol F glycidyl ether/ formaldehyde copolymer)	
No (ammonium polyphosphate)	
Yes	
Yes	
Yes	

Page 20 of 20

9200FR-A Flame Retardant Structural Epoxy Adhesive (Part A)

USA - TSCA	Yes	
Taiwan - TCSI	Yes	
Mexico - INSQ	No (dipentaerythritol pentaacrylate; bisphenol A diglycidyl ether; bisphenol F glycidyl ether/ formaldehyde copolymer; ammonium polyphosphate)	
Vietnam - NCI	Yes	
Russia - ARIPS	No (dipentaerythritol pentaacrylate)	
Thailand - TECI	No (zinc borate; dipentaerythritol pentaacrylate; bisphenol A diglycidyl ether; bisphenol F glycidyl ether/ formaldehyde copolymer)	
Legend:	Yes = All declared ingredients are on the inventory No = Not determined or one or more ingredients are not on the inventory and are not exempt from listing(see specific ingredients in brackets)	

SECTION 16 OTHER INFORMATION

Revision Date	18/03/2020
Initial Date	10/02/2018

Full text Risk and Hazard codes

H360	May damage fertility or the unborn child.
H400	Very toxic to aquatic life.
H410	Very toxic to aquatic life with long lasting effects.
H412	Harmful to aquatic life with long lasting effects.
H413	May cause long lasting harmful effects to aquatic life.

SDS Version Summary

Version	Issue Date	Sections Updated
5.9.1.1.1	13/05/2019	Physical Properties

Other information

Ingredients with multiple cas numbers

Name	CAS No	
bisphenol F glycidyl ether/ formaldehyde copolymer	28064-14-4, 42616-71-7, 59029-73-1, 94422-39-6	
aluminium hydroxide	21645-51-2, 1330-44-5, 1302-29-0, 12252-70-9, 51330-22-4	
bisphenol A diglycidyl ether	1675-54-3, 116161-20-7, 170962-54-6, 47424-12-4, 85101-00-4, 25068-38-6	
zinc borate	1332-07-6, 108749-27-5, 13826-88-5, 12767-90-7, 139354-75-9, 14720-55-9, 12230-20-5, 12536-65-1, 12007-67-9, 115887-05-3, 12007-72-6, 12008-25-2	
dipentaerythritol pentaacrylate	60506-81-2, 1384855-91-7, 115083-64-2, 122269-29-8, 125913-45-3, 78949-72-1	

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered. For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

Definitions and abbreviations

PC-TWA: Permissible Concentration-Time Weighted Average

PC-STEL: Permissible Concentration-Short Term Exposure Limit

IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists

STEL: Short Term Exposure Limit

TEEL: Temporary Emergency Exposure Limit。

IDLH: Immediately Dangerous to Life or Health Concentrations

OSF: Odour Safety Factor

NOAEL :No Observed Adverse Effect Level LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value

BCF: BioConcentration Factors

BEI: Biological Exposure Index

Reason For Change

A-2.02 - Update to the emergency phone number information.