### **3V Lithium Coin Cell**

# multicomp PRO



### **Specifications**

| Item                                |                         | Values  | Conditions   |  |
|-------------------------------------|-------------------------|---|--|--|
| Nominal Voltage                     |                         | 3V  | Standard Discharge   |  |
| Nominal Capacity                    |                         | 150mAh  |  |  |
| Instantaneous short-circuit current |                         | ≥300mA  | Time ≤0.5 second   |  |
| Off-load Voltage                    |                         | ≥3.2V   | Unit Cell  |  |
| Storage Temperature                 |                         | 0-35°C  | -  |  |
| Standard Weigh                      |                         | 2.5g  | Unit Cell  |  |
| Service Output                      | Initial                 | 95 hours  | Continuous discharge with<br>load 2kΩ, till 2V<br>end-voltage at 20°C ~ 25°C |  |
|                                     | After 12 months storage | 93 hours  |  |  |
| Self-discharge Rate                 |                         | Stored for 12 months at normal tempera-<br>ture, then continuously discharged with<br>15kΩ load till 2V end-voltage | Less than ≤2%  |  |

| Item                                   | Test Methods   | Standard   |                    |  |
|--|--|--|--------------------|--|
| Dimensions                             | Using vernier calliper (accuracy ≥ 0.02) while avoiding  | Diameter   | 20mm (-0.15mm)     |  |
| Dimensions                             | short-circuit  | Height   | 2.5mm (-0.2mm)     |  |
| Off-load Voltage                       | Using multimeter (accuracy $\geq$ 0.25%) Internal Resistance $\geq$ 1M $\Omega$  | ≥3.2V  |                    |  |
| Instantaneous<br>Short-circuit Current | Time of short-circuit should be less than 0.5<br>Second and avoid repeated test within half an hour  | ≥300mA   |                    |  |
| Appearance                             | Eyeballing   | Bright, clean, no rust,<br>no leakage, and no flaw |                    |  |
| Capacity                               | Continuously discharge for 8 hour with load 2kΩ, temperature<br>at 20~25°C,humidity at 65 ±20% till 2V end-voltage<br>(for fresh battery only: within 3 months)                | ≥95h   |                    |  |
| Vibration Test                         | Put battery on the platform of the vibrations Machine, start the machine and adjust the Frequency form 10 times per minute to 15 Times per minute. keep it running for an hour | Characteristics keep stability                     |                    |  |
| Leakage at high temperature            | Stored under temperature (45°C) for 30 days  | Leakage rate ≤0.5%                                 |                    |  |
| Over Discharge Test                    | Discharge Test After 2V end-voltage, continuously discharged for 5 hours   |  | No leakage allowed |  |


Newark.com/multicomp-pro Farnell.com/multicomp-pro Element14.com/multicomp-pro




## multicomp PRO

#### **Discharge Characteristics**

#### With load 2kQ (CR2025)



#### Diagram



#### Part Number Table

|                        | Description                                | Part Number |  |
|------------------------|--|-------------|--|
| mensions : Millimetres | 3V Lithium Manganese Dioxide, 150mAh, 20mm | 298-0035    |  |

Important Notice : This data sheet and its contents (the "Information") belong to the members of the AVNET group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp Pro is the registered trademark of Premier Farnell Limited 2019.

Newark.com/multicomp-pro Farnell.com/multicomp-pro Element14.com/multicomp-pro

